

PEGASUS GOLD AUSTRALIA PTY LTD

**SEL9679 BARNJARN
MT TODD DISTRICT, NT**

**ANNUAL REPORT FOR EXPLORATION
YEAR ONE OF TENURE
26 NOVEMBER 1996 – 25 NOVEMBER 1997**

APPENDIX 2

SOIL SAMPLE ASSAY RESULTS



ASSAYCORP

Report Code: AC 37772

Samples Received: 03/08/97

Number of Samples: 357

Pegasus Gold Exploration

PO BOX 971

KATHERINE 0852

ASSAYCORP PTY LTD

A.C.N. 052 982 911

174 Ward St

Pine Creek NT 0847

Ph (08) 8976 1262

Fax (08) 8976 1310

Report Distribution

Nick Burn

Reference: 0773

Project:

Cost Code:

Page 1 of 16

Sample Preparation:

Assay Data:

Analysis	Analytical Method	Digest	Technique	Precision & Accuracy	Detection Limit	Data Units
Au	FALL	FA	AAS	Acc. $\pm$ 15 %	1	ppb
Au(R)	FALL	FA	AAS	Acc. $\pm$ 15 %	1	ppb
As	G300I	MA3	ICP-OES	Prec. $\pm$ 10 %	1	ppm
Bi	G300I	MA3	ICP-OES	Prec. $\pm$ 10 %	10	ppm
Cu	G300I	MA3	ICP-OES	Prec. $\pm$ 10 %	1	ppm
Pb	G300I	MA3	ICP-OES	Prec. $\pm$ 10 %	5	ppm
Zn	G300I	MA3	ICP-OES	Prec. $\pm$ 10 %	2	ppm

BJ 001 to BJ 357

Report Comment: This cover sheet is an integral part of the report. This report can only be reproduced in full.

Authorisation: Ray Wooldridge

Report Dated: 28/08/97



ASSAYCORP

ASSAY CODE: AC 37772

Page 2 of 16

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Bi (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0001	1	1	2	<10	14	28	16
BJ0002	1		8	<10	14	25	16
BJ0003	3		10	<10	8	19	11
BJ0004	2		10	<10	11	32	14
BJ0005	1	1	20	<10	16	44	25
BJ0006	2		35	<10	28	233	167
BJ0007	2		11	<10	12	29	12
BJ0008	4		7	<10	10	73	19
BJ0009	3		17	<10	20	39	32
BJ0010	4	3	11	<10	41	36	12
BJ0011	4	3	14	<10	27	48	26
BJ0012	8		7	<10	15	25	27
BJ0013	6		7	<10	6	35	13
BJ0014	6	4	4	<10	11	38	27
BJ0015	5		12	<10	13	31	27
BJ0016	2		23	<10	8	15	20
BJ0017	2	1	18	<10	12	19	18
BJ0018	3		15	<10	12	22	20
BJ0019	2		28	<10	35	67	17
BJ0020	1	<1	28	<10	22	33	11
BJ0021	2		19	<10	26	35	16
BJ0022	1		15	<10	16	14	9
BJ0023	1		5	<10	8	10	6
BJ0024	1		6	<10	10	11	7
BJ0025	1		10	<10	21	20	24
Method	FALL	FALL	G300I	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37772

Page 3 of 16

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Bi (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0026	1	1	10	<10	32	45	34
BJ0027	2		14	<10	32	57	65
BJ0028	1		9	<10	30	32	33
BJ0029	3		5	<10	18	20	26
BJ0030	4		10	<10	18	25	28
BJ0031	3		7	<10	17	29	32
BJ0032	5		12	<10	20	15	24
BJ0033	3		22	<10	17	19	21
BJ0034	7	7	9	<10	27	29	23
BJ0035	5	4	10	<10	20	71	42
BJ0036	2		14	<10	14	57	15
BJ0037	3		5	<10	14	10	10
BJ0038	1		11	<10	23	68	20
BJ0039	1		12	<10	25	188	67
BJ0040	1		14	<10	16	34	12
BJ0041	3		11	<10	18	45	14
BJ0042	1		17	<10	14	21	11
BJ0043	2	2	15	<10	28	57	40
BJ0044	2		21	<10	24	43	43
BJ0045	1		6	<10	16	36	24
BJ0046	1		15	<10	11	22	15
BJ0047	1	1	27	<10	13	26	19
BJ0048	1		25	<10	12	25	16
BJ0049	2		19	<10	73	19	25
BJ0050	1		4	<10	26	41	58
Method	FALL	FALL	G300I	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37772

Page 4 of 16

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Bi (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0051	1		4	<10	25	33	33
BJ0052	1		4	<10	24	33	27
BJ0053	1		3	<10	20	29	23
BJ0054	1		3	<10	23	27	22
BJ0055	1	<1	3	<10	23	23	19
BJ0056	1	1	5	<10	26	23	21
BJ0057	1		4	<10	27	18	21
BJ0058	2		3	<10	20	16	16
BJ0059	1		5	<10	19	16	18
BJ0060	1		4	<10	15	16	18
BJ0061	1		13	<10	20	26	39
BJ0062	1		11	<10	25	109	169
BJ0063	<1	<1	20	<10	32	109	224
BJ0064	1		7	<10	12	21	31
BJ0065	1		10	<10	18	18	44
BJ0066	1		16	<10	17	56	57
BJ0067	1		15	<10	19	66	38
BJ0068	<1		16	<10	19	71	34
BJ0069	1		11	<10	15	44	25
BJ0070	1		20	<10	24	58	31
BJ0071	1		22	<10	31	43	56
BJ0072	1		20	<10	29	24	50
BJ0073	1		22	<10	26	48	36
BJ0074	1	<1	8	<10	12	12	19
BJ0075	1		7	<10	13	19	23
Method	FALL	FALL	G300I	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37772

Page 5 of 16

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Bi (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0076	<1		6	<10	12	21	23
BJ0077	1	<1	8	<10	16	15	10
BJ0078	1		12	<10	23	27	15
BJ0079	1		13	<10	18	58	28
BJ0080	<1		18	<10	10	8	6
BJ0081	<1		15	<10	9	11	9
BJ0082	<1		8	<10	6	11	15
BJ0083	1		15	<10	7	11	14
BJ0084	<1		17	<10	8	12	10
BJ0085	1		103	<10	20	22	20
BJ0086	1	<1	5	<10	17	23	23
BJ0087	1		4	<10	18	21	24
BJ0088	1		3	<10	16	16	22
BJ0089	1		4	<10	16	31	38
BJ0090	3	3	17	<10	27	22	30
BJ0091	3	1	5	<10	16	18	28
BJ0092	4	3	7	<10	35	10	27
BJ0093	2	2	4	<10	28	14	37
BJ0094	1		3	<10	16	16	36
BJ0095	1		3	<10	18	12	24
BJ0096	2		16	<10	28	33	52
BJ0097	4		8	<10	38	66	91
BJ0098	3		5	<10	31	28	50
BJ0099	2		3	<10	32	22	34
BJ0100	3		4	<10	19	22	24
Method	FALL	FALL	G300I	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37772

Page 6 of 16

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Bi (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0101	2		6	<10	20	30	32
BJ0102	3		13	<10	27	65	91
BJ0103	7		13	<10	28	80	69
BJ0104	7	6	8	<10	18	62	86
BJ0105	8	6	18	<10	21	15	34
BJ0106	4	5	11	<10	28	62	66
BJ0107	5		12	<10	28	60	64
BJ0108	12	10	14	<10	24	21	63
BJ0109	10	10	6	<10	21	15	31
BJ0110	5		3	<10	11	13	22
BJ0111	5	5	12	<10	16	17	14
BJ0112	4		6	<10	14	37	17
BJ0113	2		28	<10	17	11	12
BJ0114	2		11	<10	7	7	9
BJ0115	2		12	<10	8	<5	8
BJ0116	2		10	<10	6	8	9
BJ0117	1	1	14	<10	5	7	9
BJ0118	1		32	<10	8	5	7
BJ0119	1		17	<10	7	11	12
BJ0120	2		26	<10	15	22	17
BJ0121	1		32	10	19	26	19
BJ0122	2		24	<10	18	33	25
BJ0123	3	2	26	<10	25	50	31
BJ0124	1		4	<10	6	7	61
BJ0125	2		72	<10	56	35	23
Method	FALL	FALL	G300I	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37772

Page 7 of 16

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Bi (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0126	1		52	<10	32	35	27
BJ0127	2		41	<10	24	26	19
BJ0128	1		23	<10	14	15	11
BJ0129	1		25	<10	13	14	11
BJ0130	1		30	<10	7	10	9
BJ0131	1	1	27	<10	8	9	7
BJ0132	2		37	<10	16	11	19
BJ0133	1		58	<10	14	13	11
BJ0134	1		118	<10	19	34	32
BJ0135	1		44	<10	20	38	20
BJ0136	2		52	<10	27	58	31
BJ0137	2		36	<10	25	54	34
BJ0138	1		12	<10	17	42	50
BJ0139	1		5	<10	15	36	37
BJ0140	2		14	<10	25	39	50
BJ0141	2		10	<10	24	34	45
BJ0142	3		5	<10	21	41	50
BJ0143	4	4	12	<10	30	63	67
BJ0144	3		3	<10	26	31	66
BJ0145	1		3	<10	22	26	32
BJ0146	4		21	<10	405	280	182
BJ0147	2		2	<10	35	38	63
BJ0148	32	21	20	<10	30	38	71
BJ0149	1		15	<10	23	33	50
BJ0150	1	<1	4	<10	22	28	40
Method	FALL	FALL	G300I	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37772

Page 8 of 16

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Bi (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0151	1		5	<10	32	62	52
BJ0152	2		12	<10	21	24	30
BJ0153	2		15	<10	19	24	32
BJ0154	<1		10	<10	16	18	25
BJ0155	<1		6	<10	15	20	24
BJ0156	59	66	31	<10	19	6	35
BJ0157	64	50	32	<10	31	14	42
BJ0158	220	240	15	<10	32	23	36
BJ0159	3		26	<10	31	54	93
BJ0160	6		21	<10	25	48	81
BJ0161	8	9	22	<10	25	47	76
BJ0162	6	2	21	<10	17	38	54
BJ0163	5		19	<10	29	36	44
BJ0164	2		4	<10	13	11	16
BJ0165	1		5	<10	12	12	15
BJ0166	2		16	<10	18	14	15
BJ0167	1		11	<10	13	10	10
BJ0168	<1		3	<10	16	12	13
BJ0169	1		18	<10	43	25	24
BJ0170	2		9	<10	43	21	24
BJ0171	8	2	24	<10	42	32	56
BJ0172	79	75	18	<10	14	12	24
BJ0173	170	200	7	<10	9	5	19
BJ0174	6		10	<10	9	9	16
BJ0175	6	8	18	<10	9	9	15
Method	FALL	FALL	G300I	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37772

Page 9 of 16

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Bi (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0176	1		12	<10	7	12	12
BJ0177	1		1	<10	6	11	12
BJ0178	<1		2	<10	16	22	20
BJ0179	1		4	<10	13	22	18
BJ0180	1		5	<10	12	21	17
BJ0181	<1		4	<10	7	10	8
BJ0182	2		4	<10	10	10	9
BJ0183	2	1	5	<10	8	7	5
BJ0184	2		7	<10	12	9	7
BJ0185	1		7	<10	7	5	5
BJ0186	23	19	11	<10	14	22	17
BJ0187	2		2	<10	8	12	16
BJ0188	1		5	<10	8	8	13
BJ0189	3		6	<10	9	15	20
BJ0190	2		1	<10	8	12	13
BJ0191	1		2	<10	10	17	15
BJ0192	2		3	<10	10	16	14
BJ0193	1		7	<10	8	27	18
BJ0194	2		29	<10	16	59	24
BJ0195	1		8	<10	8	16	11
BJ0196	1	1	5	<10	10	14	10
BJ0197	1		3	<10	9	11	11
BJ0198	<1		5	<10	23	51	34
BJ0199	1		12	<10	25	15	17
BJ0200	1		3	<10	15	28	36
Method	FALL	FALL	G300I	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37772

Page 10 of 16

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Bi (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0201	<1		2	<10	20	21	33
BJ0202	2		7	<10	15	16	22
BJ0203	2	2	16	<10	32	54	40
BJ0204	1		7	<10	14	18	17
BJ0205	1		2	<10	12	18	14
BJ0206	<1		3	<10	11	16	14
BJ0207	1		2	<10	9	6	6
BJ0208	1		3	<10	7	11	5
BJ0209	<1		3	<10	7	6	7
BJ0210	<1		5	<10	7	5	6
BJ0211	1		14	<10	14	<5	19
BJ0212	2		15	<10	17	<5	24
BJ0213	1		14	<10	9	5	13
BJ0214	1		13	<10	9	6	12
BJ0215	2		14	<10	7	6	14
BJ0216	4	4	55	<10	12	19	24
BJ0217	3	1	18	<10	11	8	21
BJ0218	2		7	<10	9	6	13
BJ0219	1		11	<10	10	11	13
BJ0220	4		18	<10	10	19	21
BJ0221	4	2	13	<10	17	33	51
BJ0222	5	4	31	<10	27	47	73
BJ0223	4	5	22	<10	23	40	64
BJ0224	3		25	<10	29	50	88
BJ0225	1		15	<10	11	15	13
Method	FALL	FALL	G300I	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37772

Page 11 of 16

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Bi (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0226	1		5	<10	12	15	15
BJ0227	<1		4	<10	14	15	14
BJ0228	2		8	<10	19	20	13
BJ0229	1		9	<10	16	15	15
BJ0230	1		14	<10	25	18	15
BJ0231	<1		14	<10	17	15	14
BJ0232	2		9	<10	15	20	14
BJ0233	1		16	<10	19	8	8
BJ0234	1		14	<10	19	9	9
BJ0235	2		12	<10	18	9	8
BJ0236	1		6	<10	15	14	20
BJ0237	1	1	13	<10	27	15	21
BJ0238	2		12	<10	15	13	22
BJ0239	1		7	<10	14	17	35
BJ0240	2		16	<10	21	6	18
BJ0241	1		9	<10	23	17	14
BJ0242	<1		7	<10	15	11	9
BJ0243	<1		8	<10	12	10	10
BJ0244	1		8	<10	17	15	25
BJ0245	1		5	<10	15	14	27
BJ0246	2		4	<10	13	8	14
BJ0247	1		6	<10	13	10	17
BJ0248	1		8	<10	13	9	20
BJ0249	<1		9	<10	12	6	23
BJ0250	1		3	<10	9	7	11
Method	FALL	FALL	G300I	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37772

Page 12 of 16

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Bi (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0251	1		3	<10	11	10	9
BJ0252	2		29	<10	54	41	51
BJ0253	<1		13	<10	18	16	23
BJ0254	6	4	26	<10	25	24	24
BJ0255	8	10	18	<10	16	14	41
BJ0256	1		10	<10	12	14	19
BJ0257	2		19	<10	21	21	60
BJ0258	1	1	28	<10	18	36	67
BJ0259	1		18	<10	23	38	136
BJ0260	2		25	<10	31	21	63
BJ0261	1		16	<10	12	17	24
BJ0262	1		16	<10	9	13	22
BJ0263	<1		12	<10	9	16	26
BJ0264	1		21	<10	12	18	24
BJ0265	1		23	<10	17	22	26
BJ0266	1		35	<10	24	17	27
BJ0267	<1		58	<10	36	25	31
BJ0268	1		48	<10	34	11	28
BJ0269	1		37	<10	34	12	16
BJ0270	1		43	<10	22	11	6
BJ0271	1		71	<10	15	11	7
BJ0272	<1		95	<10	14	11	11
BJ0273	1		70	<10	30	20	8
BJ0274	1		40	<10	32	18	10
BJ0275	1		26	<10	28	10	9
Method	FALL	FALL	G300I	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37772

Page 13 of 16

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Bi (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0276	1		51	<10	33	30	22
BJ0277	2		45	<10	52	27	59
BJ0278	1		37	<10	17	10	19
BJ0279	1		14	<10	15	13	29
BJ0280	2		19	<10	12	11	16
BJ0281	1		26	<10	16	17	16
BJ0282	2		25	<10	15	13	16
BJ0283	<1	<1	22	<10	15	14	17
BJ0284	1		25	<10	17	15	15
BJ0285	<1		7	<10	19	21	24
BJ0286	1	1	11	<10	14	22	17
BJ0287	2		12	<10	11	16	14
BJ0288	1		6	<10	11	18	12
BJ0289	1		24	<10	24	10	16
BJ0290	<1		13	<10	8	11	8
BJ0291	1		8	<10	8	7	8
BJ0292	<1	<1	6	<10	7	12	9
BJ0293	1		8	<10	10	14	10
BJ0294	<1		10	<10	15	7	12
BJ0295	1		9	<10	14	5	14
BJ0296	<1		9	<10	17	7	18
BJ0297	1		7	<10	17	<5	18
BJ0298	1		4	<10	15	6	13
BJ0299	1		7	<10	28	6	13
BJ0300	1		5	<10	15	16	17
Method	FALL	FALL	G300I	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37772

Page 14 of 16

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Bi (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0301	<1		6	<10	21	22	16
BJ0302	1		4	<10	14	13	13
BJ0303	2		6	<10	15	14	13
BJ0304	<1		5	<10	13	10	11
BJ0305	<1		4	<10	12	11	16
BJ0306	<1		3	<10	11	7	20
BJ0307	1	<1	7	<10	10	8	12
BJ0308	1		9	<10	16	14	20
BJ0309	1		9	<10	14	<5	17
BJ0310	<1		10	<10	13	14	18
BJ0311	<1		11	<10	13	13	19
BJ0312	<1	<1	12	<10	20	8	21
BJ0313	10	12	5	<10	9	7	14
BJ0314	<1		5	<10	14	7	13
BJ0315	<1		5	<10	15	13	24
BJ0316	<1		9	<10	15	7	19
BJ0317	<1		3	<10	6	5	10
BJ0318	18	28	7	<10	8	8	16
BJ0319	<1		8	<10	8	<5	16
BJ0320	<1		5	<10	12	7	18
BJ0321	<1		4	<10	15	5	21
BJ0322	<1		9	<10	19	18	18
BJ0323	<1		13	<10	19	18	19
BJ0324	<1		18	<10	24	5	25
BJ0325	<1		25	<10	27	13	32
Method	FALL	FALL	G300I	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37772

Page 15 of 16

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Bi (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0326	<1		12	<10	34	34	21
BJ0327	<1		21	<10	20	9	24
BJ0328	2		8	<10	11	9	21
BJ0329	<1	<1	9	<10	11	12	12
BJ0330	<1		10	<10	33	24	74
BJ0331	<1		11	<10	34	23	76
BJ0332	<1		11	<10	28	26	42
BJ0333	<1		12	<10	31	26	53
BJ0334	<1		17	<10	27	23	45
BJ0335	1		22	<10	29	20	50
BJ0336	<1		8	<10	22	18	25
BJ0337	<1		11	<10	11	17	18
BJ0338	<1		8	<10	9	8	15
BJ0339	<1		14	<10	17	11	23
BJ0340	<1	<1	11	<10	18	13	22
BJ0341	<1		9	<10	15	12	22
BJ0342	<1		18	<10	21	18	25
BJ0343	<1		12	<10	22	12	25
BJ0344	<1		70	<10	36	40	31
BJ0345	<1		26	<10	14	12	24
BJ0346	<1		44	<10	26	19	20
BJ0347	8	8	49	<10	106	13	56
BJ0348	<1		26	<10	23	20	30
BJ0349	<1		21	<10	23	18	62
BJ0350	<1		15	<10	88	6	43
Method	FALL	FALL	G300I	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37772

Page 16 of 16

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Bi (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0351	<1		21	<10	39	10	45
BJ0352	2		27	<10	51	8	45
BJ0353	<1		28	<10	42	8	59
BJ0354	2		28	<10	30	41	56
BJ0355	2	2	25	<10	28	47	51
BJ0356	2		26	<10	25	41	52
BJ0357	3		28	<10	25	42	52
Method	FALL	FALL	G300I	G300I	G300I	G300I	G300I



ASSAYCORP

Report Code: AC 37962

Samples Received: 15/08/97

Number of Samples: 471

Pegasus Gold Exploration

PO BOX 971

KATHERINE 0852

Assaycorp Pty Ltd

A.C.N. 052 982 911

174 Ward St

Pine Creek NT 0847

Ph (08) 8976 1262

Fax (08) 8976 1310

Report Distribution

Nick Burn

Reference: 0786

Project:

Cost Code:

Page 1 of 20

Sample Preparation:

Assay Data:

Analysis	Analytical Method	Digest	Technique	Precision & Accuracy	Detection Limit	Data Units
Au	FALL	FA	AAS	Acc. $\pm$ 15 %	1	ppb
Au(R)	FALL	FA	AAS	Acc. $\pm$ 15 %	1	ppb
As	G300I	MA3	ICP-OES	Prec. $\pm$ 10 %	1	ppb
Cu	G300I	MA3	ICP-OES	Prec. $\pm$ 10 %	1	ppm
Pb	G300I	MA3	ICP-OES	Prec. $\pm$ 10 %	5	ppm
Zn	G300I	MA3	ICP-OES	Prec. $\pm$ 10 %	2	ppm

BJ 0358 to BJ 0828

Report Comment: This cover sheet is an integral part of the report. This report can only be reproduced in full.

Authorisation: Ray Wooldridge

Report Dated: 01/09/97



ASSAYCORP

ASSAY CODE: AC 37962

Page 2 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0358	2		4	14	7	17
BJ0359	2		2	11	<5	12
BJ0360	3	2	5	21	8	20
BJ0361	2		2	15	5	16
BJ0362	1		<1	16	19	16
BJ0363	2		<1	17	21	14
BJ0364	<1		<1	15	9	14
BJ0365	<1		2	15	13	14
BJ0366	2	2	2	16	13	15
BJ0367	<1		3	18	13	16
BJ0368	<1		3	22	18	19
BJ0369	1		2	26	13	35
BJ0370	<1		<1	20	6	28
BJ0371	3	2	<1	20	6	28
BJ0372	1	2	<1	17	<5	20
BJ0373	2		2	24	<5	22
BJ0374	1		<1	21	<5	22
BJ0375	<1		<1	19	<5	24
BJ0376	<1		<1	14	7	17
BJ0377	<1		<1	19	<5	23
BJ0378	<1		<1	18	7	26
BJ0379	<1		<1	18	9	26
BJ0380	2		<1	15	11	15
BJ0381	10	6	<1	24	63	25
BJ0382	2		<1	19	<5	24
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 3 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0383	1		<1	26	54	51
BJ0384	2		<1	19	25	20
BJ0385	2		2	24	9	31
BJ0386	1		<1	15	6	30
BJ0387	2		3	14	<5	14
BJ0388	2		2	13	6	14
BJ0389	1		<1	17	8	17
BJ0390	2		3	19	15	17
BJ0391	2		4	15	10	13
BJ0392	3		14	16	6	13
BJ0393	2		2	9	5	6
BJ0394	13	16	23	20	10	11
BJ0395	9		8	9	9	6
BJ0396	7		<1	9	7	5
BJ0397	21	16	10	13	17	9
BJ0398	485	290	20	12	33	11
BJ0399	950	1060	41	16	140	15
BJ0400	11	12	17	12	32	9
BJ0401	21	15	16	13	31	9
BJ0402	1	1	7	13	35	9
BJ0403	4	5	11	13	33	11
BJ0404	4		18	12	38	10
BJ0405	2		36	9	58	12
BJ0406	1		16	12	27	10
BJ0407	3		5	18	18	12
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 4 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0408	2		6	41	55	27
BJ0409	<1		5	27	34	24
BJ0410	2	2	12	37	22	25
BJ0411	1		6	14	23	26
BJ0412	<1		6	16	19	26
BJ0413	<1		6	37	120	31
BJ0414	1		3	21	12	24
BJ0415	2		5	27	22	23
BJ0416	<1		9	38	285	52
BJ0417	<1		3	20	27	38
BJ0418	1	2	5	19	14	21
BJ0419	<1		4	22	22	39
BJ0420	2	1	4	9	15	15
BJ0421	2		7	13	16	21
BJ0422	1		7	13	15	20
BJ0423	1		5	27	22	27
BJ0424	<1		4	21	10	21
BJ0425	<1		5	56	76	53
BJ0426	<1		5	18	19	19
BJ0427	<1		9	18	14	19
BJ0428	<1		8	41	19	43
BJ0429	1	<1	6	25	11	37
BJ0430	2		9	28	15	22
BJ0431	<1		2	20	7	20
BJ0432	<1	<1	3	17	8	16
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 5 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0433	2		3	28	8	18
BJ0434	<1		5	26	7	12
BJ0435	<1		3	32	10	13
BJ0436	<1		7	13	12	11
BJ0437	1		20	14	10	16
BJ0438	<1		21	12	10	14
BJ0439	<1	1	9	12	15	10
BJ0440	2		11	10	15	10
BJ0441	2	2	8	11	6	18
BJ0442	<1		11	10	5	13
BJ0443	<1		13	10	8	13
BJ0444	3	3	6	17	63	49
BJ0445	<1	1	7	23	57	56
BJ0446	1	2	4	22	53	46
BJ0447	1		4	8	18	9
BJ0448	1	1	2	8	20	8
BJ0449	1		7	7	9	8
BJ0450	<1	1	11	9	16	11
BJ0451	2		9	9	8	10
BJ0452	1		7	13	<5	11
BJ0453	3	2	6	12	8	12
BJ0454	1		6	14	10	12
BJ0455	2	1	7	12	5	13
BJ0456	2		6	15	9	14
BJ0457	2		1	25	41	21
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 6 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0458	3		<1	22	9	26
BJ0459	1		<1	29	37	35
BJ0460	2	2	3	21	62	46
3J0461	3	3	5	25	48	46
BJ0462	1		7	19	89	87
BJ0463	3		2	21	39	32
BJ0464	2		2	30	55	53
BJ0465	2	2	<1	28	57	50
BJ0466	1		<1	15	8	16
BJ0467	1		<1	13	15	17
BJ0468	1		<1	11	<5	20
BJ0469	1		1	18	9	30
BJ0470	1	1	<1	17	<5	17
BJ0471	1		<1	12	9	17
BJ0472	1		<1	10	5	14
BJ0473	1		<1	21	6	12
BJ0474	1		<1	17	5	11
BJ0475	1	1	<1	7	6	8
BJ0476	1		1	14	14	13
BJ0477	1		<1	11	13	14
BJ0478	1	1	1	11	12	15
BJ0479	2		<1	15	11	19
BJ0480	1		<1	8	10	15
BJ0481	1		<1	14	6	21
BJ0482	1		1	15	6	16
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 7 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0483	1		<1	16	13	21
BJ0484	1	1	1	17	12	27
BJ0485	1		1	19	9	20
BJ0486	8	8	13	18	8	11
BJ0487	9	8	17	12	6	7
BJ0488	4	5	13	17	7	10
BJ0489	2	2	15	8	5	9
BJ0490	1		14	12	5	11
BJ0491	3	4	8	13	8	10
BJ0492	1		9	9	8	14
BJ0493	2		9	12	7	18
BJ0494	2		6	13	23	20
BJ0495	2		7	5	7	9
BJ0496	8	8	10	18	50	34
BJ0497	2		5	9	46	24
BJ0498	5	5	5	20	157	74
BJ0499	4		4	20	81	54
BJ0500	2	2	4	21	81	38
BJ0501	2		7	22	51	59
BJ0502	2		6	15	34	44
BJ0503	3		6	25	33	81
BJ0504	2		8	47	795	203
BJ0505	2	2	3	21	126	32
BJ0506	2		2	21	39	36
BJ0507	2		4	15	25	33
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 8 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0508	2		6	14	28	33
BJ0509	2		6	22	22	76
BJ0510	2		6	20	28	63
BJ0511	1		3	21	32	49
BJ0512	1		5	20	32	52
BJ0513	2		4	18	22	40
BJ0514	2		4	20	51	46
BJ0515	2		3	10	34	26
BJ0516	1		2	11	34	23
BJ0517	1	1	2	12	33	22
BJ0518	2		3	14	32	35
BJ0519	1		2	10	25	21
BJ0520	1		5	13	15	21
BJ0521	1		2	9	12	20
BJ0522	2		3	7	15	14
BJ0523	1		<1	7	19	14
BJ0524	2		2	9	40	19
BJ0525	2		<1	8	27	15
BJ0526	1		<1	5	17	9
BJ0527	1		<1	6	20	12
BJ0528	2		3	8	29	27
BJ0529	2		3	10	45	26
BJ0530	1	1	2	9	41	25
BJ0531	1		3	6	26	12
BJ0532	1		3	7	104	34
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 9 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0533	2		2	6	32	22
BJ0534	1		<1	6	34	13
BJ0535	2		<1	8	52	16
BJ0536	2		<1	12	34	17
BJ0537	2	3	2	11	44	21
BJ0538	2		6	9	30	13
BJ0539	1		3	8	29	14
BJ0540	1		5	9	24	15
BJ0541	<1	1	2	8	21	10
BJ0542	<1		5	6	25	11
BJ0543	1		4	9	51	14
BJ0544	1		2	8	13	11
BJ0545	2		9	13	26	23
BJ0546	2		7	20	20	19
BJ0547	1		5	19	36	22
BJ0548	1		2	9	73	11
BJ0549	2		2	7	38	10
BJ0550	7	8	15	10	106	41
BJ0551	8	8	16	19	247	212
BJ0552	2		5	13	72	58
BJ0553	1		<1	8	27	16
BJ0554	1		3	13	26	17
BJ0555	2		4	15	35	28
BJ0556	1		4	15	32	29
BJ0557	1		2	17	31	30
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 10 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0558	2		<1	22	30	60
BJ0559	1		<1	20	23	49
BJ0560	1		<1	21	25	47
BJ0561	<1		<1	9	11	9
BJ0562	1		3	13	16	15
BJ0563	<1		7	18	13	30
BJ0564	1		15	16	18	26
BJ0565	1		4	19	9	25
BJ0566	<1		3	17	13	21
BJ0567	1		<1	12	7	18
BJ0568	1		3	18	11	20
BJ0569	2		2	13	6	15
BJ0570	1		3	8	10	8
BJ0571	<1		3	21	15	38
BJ0572	2	1	<1	15	9	16
BJ0573	1		<1	28	9	53
BJ0574	1		<1	17	12	22
BJ0575	<1		<1	13	8	24
BJ0576	1		<1	15	11	18
BJ0577	1		<1	15	16	17
BJ0578	1	1	<1	10	13	17
BJ0579	<1		3	15	7	16
BJ0580	2		6	14	7	18
BJ0581	<1		4	18	9	22
BJ0582	2		12	12	7	18
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 11 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0583	2		8	15	7	18
BJ0584	1		8	13	9	15
BJ0585	<1		7	13	10	15
BJ0586	2		10	11	94	15
BJ0587	<1		4	7	55	15
BJ0588	1		<1	10	6	14
BJ0589	<1		<1	7	5	15
BJ0590	<1		<1	8	5	11
BJ0591	1		<1	6	6	8
BJ0592	1	2	<1	7	<5	9
BJ0593	<1		6	15	<5	19
BJ0594	1		9	10	5	17
BJ0595	1		4	8	<5	15
BJ0596	<1		<1	8	<5	13
BJ0597	3	3	4	13	8	15
BJ0598	1		4	11	<5	12
BJ0599	1		<1	13	<5	28
BJ0600	1	1	<1	19	<5	34
BJ0601	1		2	22	<5	31
BJ0602	1		<1	22	<5	31
BJ0603	<1		<1	9	<5	18
BJ0604	<1		<1	16	<5	22
BJ0605	1	1	<1	24	<5	24
BJ0606	2		<1	18	<5	26
BJ0607	1		<1	22	<5	32
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 12 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0608	<1		<1	18	<5	26
BJ0609	1		<1	23	7	32
BJ0610	1		<1	17	<5	18
BJ0611	<1		<1	14	6	19
BJ0612	<1		<1	26	7	43
BJ0613	1	1	<1	14	<5	28
BJ0614	1		2	17	5	29
BJ0615	<1		2	18	8	25
BJ0616	1		2	16	6	23
BJ0617	1		2	12	6	19
BJ0618	1		2	12	5	16
BJ0619	<1		2	15	5	18
BJ0620	<1		2	13	6	24
BJ0621	<1		<1	13	5	22
BJ0622	1		2	16	6	30
BJ0623	<1		2	15	<5	30
BJ0624	8	10	13	13	87	19
BJ0625	1		6	9	90	19
BJ0626	2		9	11	146	29
BJ0627	1		7	10	91	19
BJ0628	1	1	3	8	59	22
BJ0629	1	1	5	9	103	28
BJ0630	4		4	12	53	57
BJ0631	1		4	10	25	37
BJ0632	4		2	6	12	14
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 13 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0633	7	5	6	15	29	16
BJ0634	15	17	9	16	23	18
BJ0635	1		2	6	8	8
BJ0636	3		2	8	11	15
BJ0637	1	1	3	6	13	9
BJ0638	3		5	11	10	13
BJ0639	3	5	9	8	7	9
BJ0640	111	167	11	24	6	8
BJ0641	331	215	5	15	10	15
BJ0642	14	13	4	12	28	22
BJ0643	7		3	15	9	24
BJ0644	1		<1	19	8	41
BJ0645	1	1	<1	14	8	23
BJ0646	1		3	19	14	38
BJ0647	1	1	5	22	15	39
BJ0648	1		4	27	14	45
BJ0649	2		5	20	23	39
BJ0650	1		3	16	23	29
BJ0651	<1		2	14	12	23
BJ0652	<1		1	13	15	35
BJ0653	1		<1	14	13	29
BJ0654	1		2	9	<5	16
BJ0655	2		2	11	9	17
BJ0656	1	1	<1	18	7	23
BJ0657	1		<1	13	11	17
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 14 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0658	2		<1	18	5	25
BJ0659	2		2	12	8	18
BJ0660	1		2	13	10	16
BJ0661	1		<1	19	18	35
BJ0662	2		<1	21	31	29
BJ0663	1		2	22	33	40
BJ0664	1		2	18	21	37
BJ0665	<1		5	21	20	37
BJ0666	1		5	18	19	35
BJ0667	1	2	5	17	18	24
BJ0668	1		5	19	17	35
BJ0669	9		61	26	17	8
BJ0670	43	48	117	65	22	22
BJ0671	35	35	73	81	27	16
BJ0672	42	42	68	33	56	18
BJ0673	51	59	117	42	104	22
BJ0674	27	29	62	55	65	14
BJ0675	2		15	35	37	14
BJ0676	9		54	54	25	19
BJ0677	9		51	56	21	20
BJ0678	14	15	66	64	92	42
BJ0679	3		21	64	29	28
BJ0680	5		48	49	87	25
BJ0681	2		50	42	26	24
BJ0682	5		82	45	31	22
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 15 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0683	2		58	30	17	17
BJ0684	3	3	46	45	59	53
BJ0685	15		19	16	227	39
BJ0686	11	12	12	13	37	24
BJ0687	7		57	25	135	15
BJ0688	6		64	16	104	17
BJ0689	4		43	24	335	10
BJ0690	8	10	10	26	27	12
BJ0691	4		20	33	23	9
BJ0692	2		39	33	16	9
BJ0693	<1		23	24	10	5
BJ0694	2		19	10	7	3
BJ0695	1	1	36	16	9	5
BJ0696	2		47	32	14	12
BJ0697	1		31	14	7	3
BJ0698	2		24	18	8	5
BJ0699	1		43	10	19	9
BJ0700	3		37	16	32	8
BJ0701	3		35	14	33	5
BJ0702	3	2	66	23	14	6
BJ0703	3		98	34	8	10
BJ0704	2		74	43	15	63
BJ0705	2		48	33	7	9
BJ0706	2		20	18	13	7
BJ0707	3		33	18	10	7
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 16 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0708	1		41	14	8	6
BJ0709	1		22	13	12	4
BJ0710	1		32	32	8	6
BJ0711	2	2	52	45	11	6
BJ0712	2		42	37	9	7
BJ0713	3		38	28	14	4
BJ0714	1		28	19	32	5
BJ0715	1		37	28	16	6
BJ0716	3		69	27	21	7
BJ0717	2		40	12	10	6
BJ0718	2		66	14	11	7
BJ0719	2	2	65	17	12	6
BJ0720	3	3	66	17	19	5
BJ0721	2		37	11	47	5
BJ0722	1		31	11	48	4
BJ0723	2		53	19	375	10
BJ0724	2	2	44	8	10	3
BJ0725	1		36	7	<5	2
BJ0726	1		19	8	6	<2
BJ0727	2		26	28	6	3
BJ0728	1		20	12	6	7
BJ0729	1		38	10	6	5
BJ0730	<1		57	10	7	3
BJ0731	<1		23	10	6	6
BJ0732	1		145	13	7	5
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 17 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0733	3	2	24	20	27	8
BJ0734	1		12	13	33	8
BJ0735	2		55	13	5	3
BJ0736	3	2	52	15	<5	5
BJ0737	1		24	10	<5	6
BJ0738	<1		22	13	<5	6
BJ0739	1		37	12	<5	5
BJ0740	<1		30	17	<5	5
BJ0741	1		25	16	<5	9
BJ0742	1	1	10	22	<5	9
BJ0743	2		11	21	5	8
BJ0744	2	2	38	20	9	11
BJ0745	1		11	8	<5	8
BJ0746	1		9	13	7	8
BJ0747	2		10	14	7	6
BJ0748	<1		17	10	5	9
BJ0749	1		8	11	7	9
BJ0750	1		10	13	5	4
BJ0751	1		12	14	<5	6
BJ0752	1		13	17	<5	5
BJ0753	1		13	23	<5	2
BJ0754	1		56	33	25	27
BJ0755	5	4	39	75	37	23
BJ0756	14	13	74	63	27	10
BJ0757	24	21	99	41	66	12
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 18 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0758	14	13	173	80	21	17
BJ0759	21	23	151	50	39	7
BJ0760	6		93	68	15	8
BJ0761	1		44	72	7	8
BJ0762	2		82	33	24	9
BJ0763	6		96	55	46	8
BJ0764	5	5	141	13	206	4
BJ0765	6	7	159	13	208	6
BJ0766	3		88	22	51	5
BJ0767	1	2	98	30	12	5
BJ0768	1		125	13	17	2
BJ0769	2		129	41	11	8
BJ0770	28	27	110	24	6	2
BJ0771	7		87	21	5	3
BJ0772	4		143	24	<5	4
BJ0773	2		60	39	7	3
BJ0774	8	7	98	21	12	3
BJ0775	6		60	24	10	2
BJ0776	9	8	67	16	12	<2
BJ0777	<1		102	20	11	<2
BJ0778	<1		88	20	21	<2
BJ0779	2		174	36	15	2
BJ0780	1		152	25	9	3
BJ0781	<1	<1	87	33	7	2
BJ0782	1		135	48	7	4
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 19 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0783	4		197	111	14	12
BJ0784	5	6	305	78	20	11
BJ0785	2		150	35	5	4
BJ0786	2		165	36	7	4
BJ0787	3		59	23	13	6
BJ0788	1		66	29	9	6
BJ0789	1		69	25	<5	4
BJ0790	2		100	53	12	8
BJ0791	2		45	14	7	3
BJ0792	4		34	17	7	4
BJ0793	2		62	20	6	4
BJ0794	4	4	33	40	8	7
BJ0795	2		38	20	<5	7
BJ0796	2		34	14	<5	3
BJ0797	<1		39	15	<5	2
BJ0798	2	2	51	18	<5	4
BJ0799	2		82	20	<5	2
BJ0800	2		46	23	<5	5
BJ0801	2		46	25	<5	4
BJ0802	2		46	23	<5	3
BJ0803	1		77	22	<5	3
BJ0804	1		22	11	<5	4
BJ0805	1		43	13	<5	2
BJ0806	2	1	84	17	<5	2
BJ0807	1		37	21	<5	2
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 37962

Page 20 of 20

Sample	Au (ppb)	Au(R) (ppb)	As (ppb)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ0808	1		43	44	<5	2
BJ0809	1		39	23	<5	6
BJ0810	1		36	22	<5	5
BJ0811	2	2	91	24	<5	8
BJ0812	2		116	28	<5	8
BJ0813	2		147	40	<5	4
BJ0814	2	2	99	29	<5	6
BJ0815	1	<1	113	46	<5	6
BJ0816	1		45	30	<5	6
BJ0817	1		55	21	6	4
BJ0818	1		22	14	<5	3
BJ0819	1		27	15	<5	4
BJ0820	1		42	17	<5	5
BJ0821	<1	<1	16	19	<5	5
BJ0822	1		18	12	<5	5
BJ0823	1		18	12	<5	6
BJ0824	<1	<1	35	15	7	4
BJ0825	2		65	15	6	4
BJ0826	1		58	15	5	3
BJ0827	1		30	19	7	4
BJ0828	2		23	18	5	4
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

Report Code: AC 38359

Samples Received: 05/09/97

Number of Samples: 255

Pegasus Gold Exploration

PO BOX 971

KATHERINE 0852

Assaycorp Pty Ltd

A.C.N. 052 982 911

174 Ward St

Pine Creek NT 0847

Ph (08) 8976 1262

Fax (08) 8976 1310

Report Distribution

Nick Burn

Reference: 0304

Project:

Cost Code:

Page 1 of 12

Sample Preparation:

Assay Data:

Analysis	Analytical Method	Digest	Technique	Precision & Accuracy	Detection Limit	Data Units
Au	FALL	FA	AAS	Acc. $\pm 15\%$	1	ppb
Au(R)	FALL	FA	AAS	Acc. $\pm 15\%$	1	ppb
As	G300I	MA3	ICP-OES	Prec. $\pm 10\%$	1	ppm
Cu	G300I	MA3	ICP-OES	Prec. $\pm 10\%$	1	ppm
Pb	G300I	MA3	ICP-OES	Prec. $\pm 10\%$	5	ppm
Zn	G300I	MA3	ICP-OES	Prec. $\pm 10\%$	2	ppm

BJ 829 to BJ 1083

Report Comment: This cover sheet is an integral part of the report. This report can only be reproduced in full.
BJ8394 and BJ855 Possible contamination
bags were broken.

Authorisation: Ray Wooldridge

Report Dated: 17/09/97



ASSAYCORP

ASSAY CODE: AC 38359

Page 2 of 12

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ829	1		3	82	17	39
BJ830	4	4	4	132	38	39
BJ831	1		2	8	12	7
BJ832	2	1	2	9	9	5
BJ833	1		1	6	5	4
BJ834	1		1	4	5	6
BJ835	<1		1	4	<5	9
BJ836	1		1	4	<5	11
BJ837	1	2	1	5	<5	7
BJ838	1		1	11	<5	22
BJ839	<1		2	5	<5	9
BJ840	1		1	3	<5	9
BJ841	1		1	<1	<5	5
BJ842	2		2	8	<5	11
BJ843	1		2	12	<5	9
BJ844	<1		4	16	24	11
BJ845	3	2	12	11	5	7
BJ846	1		3	10	<5	17
BJ847	1		3	9	<5	20
BJ848	1		2	8	<5	19
BJ849	1	<1	<1	12	<5	12
BJ850	1		2	9	<5	10
BJ851	<1		2	8	<5	13
BJ852	<1		1	9	<5	16
BJ853	<1		2	9	<5	20
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38359

Page 3 of 12

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ854	6	5	1	6	<5	11
BJ855	1		2	9	<5	9
BJ856	7	4	2	8	<5	12
BJ857	8	5	5	14	<5	9
BJ858	1	1	4	11	<5	10
BJ859	2		8	22	<5	10
BJ860	1		9	11	<5	12
BJ861	2		4	10	<5	19
BJ862	<1		3	12	<5	13
BJ863	1		3	15	<5	56
BJ864	1		1	6	<5	31
BJ865	<1		1	6	<5	17
BJ866	<1		1	8	<5	23
BJ867	1		4	7	<5	14
BJ868	1		2	10	<5	13
BJ869	1		2	24	<5	17
BJ870	<1	<1	<1	14	<5	26
BJ871	<1		1	18	<5	32
BJ872	3	2	1	10	<5	11
BJ873	3	2	2	12	<5	13
BJ874	1		1	10	<5	8
BJ875	<1		1	8	<5	5
BJ876	<1		1	9	<5	8
BJ877	<1	<1	1	7	7	7
BJ878	<1		2	7	5	6
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38359

Page 4 of 12

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ879	<1	1	1	13	<5	8
BJ880	<1		1	12	<5	14
BJ881	4	4	1	16	6	11
BJ882	<1		2	7	<5	B
BJ883	1		3	15	7	11
BJ884	11	11	<1	33	9	31
BJ885	3		3	19	8	15
BJ886	12	9	6	23	6	27
BJ887	<1		B	19	<5	29
BJ888	<1		4	8	<5	9
BJ889	<1	1	5	8	<5	9
BJ890	<1		3	6	<5	15
BJ891	<1		2	10	9	11
BJ892	<1		1	39	37	27
BJ893	<1		1	40	38	27
BJ894	1		2	32	<5	24
BJ895	<1		3	29	<5	21
BJ896	1		<1	9	<5	13
BJ897	1	<1	<1	15	<5	15
BJ898	2		3	18	<5	11
BJ899	1	1	4	23	<5	37
BJ900	<1		2	5	9	10
BJ901	<1		2	4	5	7
BJ902	<1		<1	6	5	7
BJ903	<1		<1	7	7	7
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38359

Page 5 of 12

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ904	<1		2	6	13	10
BJ905	<1		1	6	<5	10
BJ906	<1		<1	8	5	11
BJ907	<1		2	9	14	11
BJ908	4	4	4	12	6	12
BJ909	<1		2	8	<5	10
BJ910	<1		4	10	<5	13
BJ911	<1		9	5	12	10
BJ912	<1		9	7	<5	11
BJ913	1		9	7	<5	11
BJ914	<1	<1	8	9	<5	12
BJ915	5	6	3	9	<5	8
BJ916	1		2	7	<5	10
BJ917	15	16	9	22	8	14
BJ918	3	3	17	13	<5	49
BJ919	2		7	13	7	20
BJ920	4	6	4	16	<5	11
BJ921	1		5	10	5	10
BJ922	1		4	8	<5	29
BJ923	1		7	7	5	10
BJ924	1		3	6	<5	5
BJ925	<1		6	8	<5	10
BJ926	2	2	2	47	6	16
BJ927	<1		1	14	<5	17
BJ928	1		3	9	<5	21
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38359

Page 6 of 12

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ929	1		2	16	<5	72
BJ930	1		1	15	<5	37
BJ931	3	4	5	14	<5	44
BJ932	1	<1	2	10	<5	18
BJ933	1		3	73	8	14
BJ934	<1		2	72	9	14
BJ935	1		2	25	<5	22
BJ936	<1		2	19	<5	17
BJ937	<1		12	4	<5	8
BJ938	2		20	15	<5	11
BJ939	<1		3	13	<5	20
BJ940	<1		2	<1	<5	7
BJ941	<1		2	<1	<5	3
BJ942	<1		3	<1	6	9
BJ943	<1		2	<1	7	5
BJ944	<1	<1	2	<1	<5	4
BJ945	<1		7	5	<5	21
BJ946	2		4	2	<5	20
BJ947	1		4	6	<5	13
BJ948	5	10	7	5	<5	10
BJ949	520	580	14	7	<5	26
BJ950	2		8	9	<5	7
BJ951	4		6	16	6	14
BJ952	3		4	17	6	15
BJ953	<1		<1	4	<5	10
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38359

Page 7 of 12

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ954	<1	<1	1	4	<5	8
BJ955	1		8	5	<5	7
BJ956	2		5	4	<5	11
BJ957	<1		4	7	<5	9
BJ958	<1		4	6	<5	8
BJ959	1		3	6	<5	15
BJ960	20	14	4	20	<5	27
BJ961	1		2	14	<5	10
BJ962	<1		2	48	<5	18
BJ963	<1		<1	2	6	12
BJ964	3	2	<1	6	<5	11
BJ965	<1		2	5	<5	15
BJ966	3		2	5	<5	7
BJ967	1	<1	1	6	<5	6
BJ968	1		1	6	<5	6
BJ969	1		<1	8	<5	17
BJ970	260	300	1	5	5	14
BJ971	1		1	11	<5	14
BJ972	3		<1	7	<5	7
BJ973	2		<1	7	<5	7
BJ974	3		9	12	<5	5
BJ975	17	11	41	16	<5	6
BJ976	4		22	9	<5	8
BJ977	2	2	7	6	<5	11
BJ978	1		5	9	<5	20
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38359

Page 8 of 12

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ979	<1		5	6	<5	11
BJ980	<1		4	14	<5	25
BJ981	<1		5	11	<5	14
BJ982	<1		11	22	<5	19
BJ983	3	3	9	7	<5	30
BJ984	1		10	7	<5	18
BJ985	19	15	8	9	<5	22
BJ986	39	42	7	8	<5	12
BJ987	21	21	7	7	<5	11
BJ988	4		3	24	<5	19
BJ989	1		2	16	<5	10
BJ990	<1		2	15	<5	10
BJ991	1		1	6	<5	20
BJ992	5	5	1	8	<5	16
BJ993	1		<1	8	<5	20
BJ994	<1		1	10	<5	27
BJ995	<1		<1	6	<5	24
BJ996	1	1	2	4	8	40
BJ997	<1	<1	1	4	6	21
BJ998	<1	<1	<1	6	<5	29
BJ999	<1		1	6	<5	21
BJ1000	<1		<1	6	<5	17
BJ1001	<1		<1	8	<5	12
BJ1002	<1		<1	4	<5	26
BJ1003	<1		<1	5	<5	23
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38359

Page 9 of 12

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ1004	1		2	7	<5	13
BJ1005	<1	<1	1	5	<5	21
BJ1006	2		1	6	7	21
BJ1007	2		7	8	9	30
BJ1008	2		6	27	8	28
BJ1009	3		4	28	9	16
BJ1010	2	2	3	10	6	10
BJ1011	1		3	13	7	8
BJ1012	1		6	9	9	11
BJ1013	1		5	11	11	10
BJ1014	2	2	4	7	10	11
BJ1015	1		4	8	9	15
BJ1016	1		2	5	8	11
BJ1017	1		2	5	7	15
BJ1018	3		4	6	8	19
BJ1019	6	8	3	5	5	14
BJ1020	11	9	3	8	<5	30
BJ1021	4		2	4	<5	24
BJ1022	2		6	5	<5	17
BJ1023	5		3	6	11	16
BJ1024	1	1	8	4	<5	11
BJ1025	21	26	15	3	<5	11
BJ1026	32	27	13	5	<5	11
BJ1027	130	120	15	5	<5	10
BJ1028	140	80	16	6	5	9
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38359

Page 10 of 12

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ1029	38	40	20	11	63	11
BJ1030	35		10	5	18	11
BJ1031	19		6	6	<5	12
BJ1032	40	29	10	2	<5	10
BJ1033	15		6	5	<5	20
BJ1034	16		15	8	<5	18
BJ1035	5	7	7	4	<5	11
BJ1036	8		5	4	<5	15
BJ1037	1		4	4	<5	9
BJ1038	1		5	2	6	6
BJ1039	1		3	3	<5	7
BJ1040	1		8	3	<5	7
BJ1041	1		2	2	<5	6
BJ1042	1		1	2	<5	5
BJ1043	<1	<1	1	6	8	14
BJ1044	<1		<1	4	<5	22
BJ1045	1		1	3	<5	10
BJ1046	1		<1	2	<5	14
BJ1047	1		<1	2	<5	11
BJ1048	1		2	6	<5	11
BJ1049	2	1	3	5	<5	10
BJ1050	<1		2	8	12	10
BJ1051	<1		4	8	13	11
BJ1052	<1	<1	3	3	14	18
BJ1053	2		5	17	21	14
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38359

Page 11 of 12

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ1054	2	1	3	31	67	13
BJ1055	<1		2	7	9	8
BJ1056	<1		2	6	10	7
BJ1057	<1	<1	2	3	6	5
BJ1058	<1		1	4	11	8
BJ1059	<1		<1	5	11	7
BJ1060	<1		2	4	8	8
BJ1061	1	1	<1	5	8	5
BJ1062	1		2	8	9	7
BJ1063	1	1	3	6	10	6
BJ1064	2	2	5	6	9	7
BJ1065	1	1	4	9	7	8
BJ1066	1		26	10	<5	7
BJ1067	1		21	11	<5	8
BJ1068	<1		15	9	<5	8
BJ1069	1		10	14	<5	6
BJ1070	1		6	7	<5	5
BJ1071	<1	1	5	4	<5	7
BJ1072	<1		4	6	<5	6
BJ1073	<1	1	6	6	<5	12
BJ1074	<1		3	9	<5	23
BJ1075	<1	<1	4	20	<5	21
BJ1076	1		4	27	<5	25
BJ1077	1	1	4	16	<5	22
BJ1078	<1		4	11	<5	17
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38359

Page 12 of 12

Sample	Au (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ1079	<1		2	9	<5	7
BJ1080	<1	<1	3	8	<5	9
BJ1081	<1		2	7	8	22
BJ1082	<1	<1	<1	16	<5	8
BJ1083	<1	<1	<1	11	<5	10
Method	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

Report Code: AC 38427

Samples Received: 10/09/97

Number of Samples: 174

Pegasus Gold Exploration

PO BOX 971

KATHERINE 0852

Assaycorp Pty Ltd

A.C.N. 052 982 911

174 Ward St

Pine Creek NT 0847

Ph (08) 8976 1262

Fax (08) 8976 1310

Report Distribution

Nick Burn

Reference: 0307

Project:

Cost Code:

Page 1 of 8

Sample Preparation:

Assay Data:

Analysis	Analytical Method	Digest	Technique	Precision & Accuracy	Detection Limit	Data Units
Au	FALL	FA	AAS	Acc. $\pm 15\%$	1	ppb
Au(R)	FALL	FA	AAS	Acc. $\pm 15\%$	1	ppb
Au(R)	FALL	FA	AAS	Acc. $\pm 15\%$	1	ppb
Au(R)	FALL	FA	AAS	Acc. $\pm 15\%$	1	ppb
As	G300I	MA3	ICP-OES	Prec. $\pm 10\%$	1	ppm
Cu	G300I	MA3	ICP-OES	Prec. $\pm 10\%$	1	ppm
Pb	G300I	MA3	ICP-OES	Prec. $\pm 10\%$	5	ppm
Zn	G300I	MA3	ICP-OES	Prec. $\pm 10\%$	2	ppm

BJ 1084 to BJ 1257

Report Comment: This cover sheet is an integral part of the report. This report can only be reproduced in full.

Authorisation: Ray Wooldridge

Report Dated: 18/09/97



ASSAYCORP

ASSAY CODE: AC 38427

Page 2 of 8

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1084	2				4	12	5	29
BJ 1085	<1				<1	8	7	18
BJ 1086	1				<1	11	<5	19
BJ 1087	1				3	47	<5	12
BJ 1088	1				6	64	<5	9
BJ 1089	5				4	11	<5	10
BJ 1090	4				9	10	<5	10
BJ 1091	3				3	22	<5	13
BJ 1092	1	<1			1	16	<5	19
BJ 1093	1				1	11	7	15
BJ 1094	1				1	12	12	14
BJ 1095	1				1	11	10	18
BJ 1096	1	<1			<1	10	6	12
BJ 1097	1				<1	13	7	25
BJ 1098	1				1	20	7	16
BJ 1099	1				<1	11	<5	20
BJ 1100	18	12			<1	12	5	19
BJ 1101	14	12			4	14	<5	9
BJ 1102	1				8	30	<5	8
BJ 1103	<1				21	22	20	19
BJ 1104	<1				3	8	<5	22
BJ 1105	<1				<1	10	<5	22
BJ 1106	<1				2	5	5	30
BJ 1107	<1	2			<1	7	<5	21
BJ 1108	<1				<1	6	<5	15
Method	FALL	FALL	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38427

Page 3 of 8

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1109	<1				<1	9	<5	19
BJ 1110	<1				<1	8	<5	11
BJ 1111	<1				<1	7	6	16
BJ 1112	<1				<1	13	<5	29
BJ 1113	<1				1	11	<5	19
BJ 1114	<1				<1	10	5	20
BJ 1115	<1				<1	10	6	18
BJ 1116	3				3	24	<5	15
BJ 1117	<1	<1			6	24	<5	8
BJ 1118	4				3	13	<5	12
BJ 1119	2				2	20	<5	14
BJ 1120	1				<1	2	<5	9
BJ 1121	<1				<1	<1	<5	13
BJ 1122	<1				<1	5	<5	17
BJ 1123	<1				<1	11	<5	13
BJ 1124	<1				<1	10	<5	12
BJ 1125	2	1			3	73	<5	21
BJ 1126	4				2	12	<5	13
BJ 1127	7				6	168	<5	12
BJ 1128	1				2	49	<5	12
BJ 1129	<1				1	6	6	17
BJ 1130	<1				<1	11	10	17
BJ 1131	<1	1			<1	13	<5	13
BJ 1132	<1				<1	11	5	27
BJ 1133	<1				<1	7	6	23
Method	FALL	FALL	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38427

Page 4 of 8

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1134	<1				<1	2	<5	16
BJ 1135	<1				<1	6	<5	17
BJ 1136	<1				<1	7	<5	19
BJ 1137	2				<1	12	5	27
BJ 1138	<1				<1	8	8	27
BJ 1139	<1				<1	6	9	24
BJ 1140	<1				<1	10	<5	12
BJ 1141	<1				4	9	<5	9
BJ 1142	1				4	9	<5	10
BJ 1143	2	2			1	22	<5	24
BJ 1144	<1	1			<1	5	<5	30
BJ 1145	<1				<1	9	<5	28
BJ 1146	<1				<1	17	<5	31
BJ 1147	1				<1	7	5	21
BJ 1148	<1				<1	3	<5	12
BJ 1149	<1				<1	6	<5	14
BJ 1150	<1				<1	3	<5	20
BJ 1151	<1				2	32	<5	13
BJ 1152	3				2	36	<5	23
BJ 1153	1				<1	12	<5	15
BJ 1154	3				<1	11	<5	21
BJ 1155	1				<1	11	<5	22
BJ 1156	1				<1	8	<5	16
BJ 1157	<1				<1	12	8	20
BJ 1158	<1				<1	3	<5	23
Method	FALL	FALL	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38427

Page 5 of 8

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1159	<1				<1	13	<5	42
BJ 1160	<1				<1	7	<5	19
BJ 1161	<1				<1	8	<5	15
BJ 1162	<1				1	9	<5	37
BJ 1163	2				4	15	<5	21
BJ 1164	2				2	17	<5	18
BJ 1165	2				2	9	<5	10
BJ 1166	1				2	37	<5	27
BJ 1167	2				6	21	<5	27
BJ 1168	3				4	3	5	14
BJ 1169	<1				1	<1	<5	22
BJ 1170	2				<1	<1	<5	23
BJ 1171	1				<1	<1	8	22
BJ 1172	1				<1	7	<5	15
BJ 1173	<1				<1	4	<5	17
BJ 1174	<1				<1	<1	<5	17
BJ 1175	<1	<1			<1	6	5	20
BJ 1176	1				<1	5	<5	12
BJ 1177	1				<1	7	12	28
BJ 1178	1				<1	7	5	21
BJ 1179	2	3			<1	9	<5	23
BJ 1180	11				<1	11	<5	29
BJ 1181	1				2	17	<5	11
BJ 1182	2				6	31	<5	12
BJ 1183	1				5	11	<5	12
Method	FALL	FALL	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38427

Page 6 of 8

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1184	2				4	10	<5	7
BJ 1185	1				5	10	<5	5
BJ 1186	2	3			4	9	7	7
BJ 1187	5	4			10	33	5	6
BJ 1188	<1				4	22	<5	11
BJ 1189	1	<1			6	10	<5	11
BJ 1190	1				2	16	6	17
BJ 1191	1				<1	5	6	16
BJ 1192	<1				<1	7	6	14
BJ 1193	<1				<1	5	<5	13
BJ 1194	1				<1	3	7	16
BJ 1195	<1	<1			<1	5	9	27
BJ 1196	1				<1	6	<5	19
BJ 1197	1				2	9	7	30
BJ 1198	1				<1	9	<5	19
BJ 1199	<1				<1	<1	<5	20
BJ 1200	<1				3	9	7	17
BJ 1201	1				1	7	9	27
BJ 1202	<1				1	9	8	20
BJ 1203	1				<1	3	<5	17
BJ 1204	1				<1	7	<5	19
BJ 1205	1				<1	11	<5	29
BJ 1206	<1				<1	4	<5	21
BJ 1207	1				<1	6	<5	20
BJ 1208	<1				<1	4	<5	20
Method	FALL	FALL	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38427

Page 7 of 8

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1209	<1				<1	6	6	18
BJ 1210	1				<1	9	5	19
BJ 1211	2				<1	4	<5	29
BJ 1212	<1				<1	7	<5	32
BJ 1213	<1				<1	8	<5	17
BJ 1214	1				<1	8	<5	21
BJ 1215	1				<1	7	<5	24
BJ 1216	1				<1	2	<5	30
BJ 1217	<1	1			<1	6	<5	31
BJ 1218	<1				2	6	<5	21
BJ 1219	1				2	7	<5	16
BJ 1220	14	13			11	10	10	14
BJ 1221	34	24			17	11	27	29
BJ 1222	105	10	250	39	27	11	28	32
BJ 1223	4				10	11	37	42
BJ 1224	1				7	24	<5	9
BJ 1225	4				3	43	<5	10
BJ 1226	<1				2	32	<5	4
BJ 1227	1				2	7	<5	12
BJ 1228	<1				3	10	<5	13
BJ 1229	<1				1	11	<5	12
BJ 1230	<1				5	8	11	13
BJ 1231	1				6	9	9	13
BJ 1232	1				<1	10	7	13
BJ 1233	8	B			<1	5	<5	10
Method	FALL	FALL	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38427

Page 8 of 8

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1234	3	3			<1	3	<5	7
BJ 1235	2				8	28	<5	13
BJ 1236	2				5	4	<5	11
BJ 1237	7	12			4	3	<5	6
BJ 1238	3				2	<1	<5	6
BJ 1239	1				2	19	<5	11
BJ 1240	<1				3	15	<5	13
BJ 1241	1				3	10	<5	17
BJ 1242	<1				<1	6	<5	15
BJ 1243	1	<1			<1	9	<5	11
BJ 1244	1				2	14	<5	13
BJ 1245	1				<1	14	<5	20
BJ 1246	<1				3	13	<5	21
BJ 1247	<1				<1	6	<5	18
BJ 1248	1				<1	7	7	20
BJ 1249	<1	1			1	5	5	18
BJ 1250	1				1	10	9	19
BJ 1251	1				<1	9	8	20
BJ 1252	<1				1	5	<5	22
BJ 1253	<1				1	2	<5	15
BJ 1254	1				1	<1	<5	19
BJ 1255	<1				1	2	<5	25
BJ 1256	<1	<1			2	3	<5	10
BJ 1257	1				1	4	<5	10
Method	FALL	FALL	FALL	FALL	G300I	G300I	G300I	G300I



ASSAYCORP

Report Code: AC 38485

Samples Received: 15/09/97

Number of Samples: 233

Pegasus Gold Exploration

PO BOX 971

KATHERINE 0852

Assaycorp Pty Ltd

A.C.N. 052 982 911

174 Ward St

Pine Creek NT 0847

Ph (08) 8976 1262

Fax (08) 8976 1310

Report Distribution

Nick Burn

Reference: 0311

Project:

Cost Code:

Page 1 of 11

Sample Preparation:

Assay Data:

Analysis	Analytical Method	Digest	Technique	Precision & Accuracy	Detection Limit	Data Units
Au	FALL	FA	AAS	Acc. $\pm 15\%$	1	ppb
Au(R)	FALL	FA	AAS	Acc. $\pm 15\%$	1	ppb
Au(R)	FALL	FA	AAS	Acc. $\pm 15\%$	1	ppb
As	G300H	MA3	HYDRIDE	Prec. $\pm 10\%$	1	ppm
Cu	G300I	MA3	ICP-OES	Prec. $\pm 10\%$	1	ppm
Pb	G300I	MA3	ICP-OES	Prec. $\pm 10\%$	5	ppm
Zn	G300I	MA3	ICP-OES	Prec. $\pm 10\%$	2	ppm

BJ 1258 - BJ 1490

Report Comment: This cover sheet is an integral part of the report. This report can only be reproduced in full.

Note that no sample in bags BJ 1389,1421

1425,1432-1436,1445-1447,1451,1452,1475

1480

Authorisation: Ray Wooldridge

Report Dated: 01/10/97



ASSAYCORP

ASSAY CODE: AC 38485

Page 2 of 11

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1258	1			2	12	19	23
BJ 1259	2			38	38	35	38
BJ 1260	3			41	36	30	42
BJ 1261	3			39	38	33	38
BJ 1262	4	5		34	36	32	37
BJ 1263	4			44	37	38	39
BJ 1264	3			36	33	37	29
BJ 1265	2			18	17	25	11
BJ 1266	2	2		11	13	19	8
BJ 1267	2			9	15	26	14
BJ 1268	2			7	13	23	13
BJ 1269	1			5	10	20	15
BJ 1270	1			3	10	18	18
BJ 1271	1			35	6	104	37
BJ 1272	<1	<1		2	13	34	26
BJ 1273	<1			1	10	18	17
BJ 1274	2			8	15	21	14
BJ 1275	2			4	9	16	12
BJ 1276	1			2	12	16	17
BJ 1277	1			3	11	23	23
BJ 1278	1			3	13	9	21
BJ 1279	<1			2	9	11	18
BJ 1280	1			11	13	16	38
BJ 1281	2	2		11	25	49	47
BJ 1282	2			11	25	46	46
Method	FALL	FALL	FALL	G300H	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38485

Page 3 of 11

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1283	<< Sample not received >>						
BJ 1284	<< Sample not received >>						
BJ 1285	1			26	18	26	8
1286	12	10		10	29	28	10
BJ 1287	9	9		27	33	28	12
BJ 1288	12	12		35	25	22	9
BJ 1289	10	11		56	19	20	8
BJ 1290	<1			<1	13	31	15
BJ 1291	<1			1	9	26	10
BJ 1292	<1			1	11	11	14
BJ 1293	<1			<1	9	10	13
BJ 1294	<1			1	10	12	13
BJ 1295	<1			1	14	23	18
RJ 1296	<1			1	17	34	32
BJ 1297	1			1	10	25	28
BJ 1298	1	1		3	34	64	61
BJ 1299	<1			2	15	35	37
BJ 1300	1			1	10	15	19
BJ 1301	<1			2	11	15	11
BJ 1302	1			1	11	12	13
BJ 1303	2			1	9	9	12
BJ 1304	1			1	10	9	16
BJ 1305	1			2	14	49	21
BJ 1306	2			4	13	55	22
BJ 1307	1			2	12	13	20
Method	FALL	FALL	FALL	G300H	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38485

Page 4 of 11

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1308	2			4	12	24	20
BJ 1309	1			4	14	21	24
BJ 1310	1			3	10	15	16
BJ 1311	2			7	24	98	47
BJ 1312	5			14	12	49	17
BJ 1313	1			9	11	140	40
BJ 1314	3			9	12	138	27
BJ 1315	11			99	13	260	32
BJ 1316	2			3	9	61	18
BJ 1317	1	1		3	9	31	13
BJ 1318	2	2		12	20	48	17
BJ 1319	2			16	28	38	21
BJ 1320	4			33	67	34	31
BJ 1321	3			38	65	34	30
BJ 1322	8	6		34	57	69	28
BJ 1323	2			35	22	73	19
BJ 1324	2			17	12	31	14
BJ 1325	1			12	8	11	5
BJ 1326	2			5	7	10	8
BJ 1327	1			9	8	11	6
BJ 1328	1			9	8	13	6
BJ 1329	1			10	9	12	4
BJ 1330	2			15	15	31	10
BJ 1331	1			3	8	54	13
BJ 1332	1	1		10	13	41	11
Method	FALL	FALL	FALL	G300H	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38485

Page 5 of 11

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1333	2			5	10	73	16
BJ 1334	2			2	17	45	39
BJ 1335	2			5	23	38	44
BJ 1336	3			10	14	55	22
BJ 1337	2			17	17	161	23
BJ 1338	2			13	18	174	25
BJ 1339	2			12	12	54	24
BJ 1340	2			12	21	62	15
BJ 1341	1	1		12	11	250	35
BJ 1342	4			14	19	42	32
BJ 1343	4			27	9	60	29
BJ 1344	21	19		31	10	79	24
BJ 1345	3			11	12	95	18
RJ 1346	1			7	8	62	13
LJ 1347	3			15	25	126	41
BJ 1348	1	1		2	20	53	61
BJ 1349	<1			5	15	27	21
BJ 1350	<1			3	11	21	18
BJ 1351	<< Sample not received >>						
BJ 1352	2			3	8	45	27
BJ 1353	<1			14	12	70	51
BJ 1354	1			8	10	72	88
BJ 1355	4			6	10	177	55
BJ 1356	5	3		12	7	152	65
BJ 1357	7			5	9	86	43
Method	FALL	FALL	FALL	G300H	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38485

Page 6 of 11

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1358	265	43	139	23	16	168	137
BJ 1359	17	18		9	13	88	94
BJ 1360	6			15	20	65	137
BJ 1361	5	9		15	21	63	140
BJ 1362	10			10	16	31	45
BJ 1363	3			5	16	28	45
BJ 1364	4			10	10	70	65
BJ 1365	8			21	18	60	49
BJ 1366	3			11	17	53	71
BJ 1367	1	2		5	16	55	72
BJ 1368	<1			3	18	51	55
BJ 1369	2			11	18	22	38
BJ 1370	5			1	12	19	33
BJ 1371	<1			<1	11	15	21
BJ 1372	1			<1	15	13	32
BJ 1373	2			<1	20	33	60
BJ 1374	3			<1	19	15	41
BJ 1375	10	9		2	20	22	33
BJ 1376	2			10	16	13	48
BJ 1377	<1			2	16	16	45
BJ 1378	<1	1		<1	19	32	43
BJ 1379	1			<1	16	28	47
BJ 1380	1			<1	10	13	21
BJ 1381	1			<1	17	16	51
BJ 1382	240	70	80	<1	17	82	35
Method	FALL	FALL	FALL	G300H	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38485

Page 7 of 11

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1383	71	50	30	<1	17	22	36
BJ 1384	11			11	16	37	38
BJ 1385	2	1		3	49	210	213
BJ 1386	2	1		2	12	16	23
BJ 1387	1			1	17	43	43
BJ 1388	1	1		2	23	26	61
BJ 1389	-IS-			-IS-	-IS-	-IS-	-IS-
BJ 1390	2			2	18	17	49
BJ 1391	1			1	21	6	38
BJ 1392	<1			2	25	76	27
BJ 1393	1			2	10	16	16
BJ 1394	1			4	24	27	24
BJ 1395	2			3	24	13	33
BJ 1396	1			1	12	<5	24
BJ 1397	2			2	15	6	18
BJ 1398	2			4	11	<5	16
BJ 1399	<1	1		7	21	35	18
BJ 1400	3	2		<1	16	23	14
BJ 1401	2			<1	16	15	14
BJ 1402	3			1	27	10	21
BJ 1403	5			<1	16	7	11
BJ 1404	2			<1	18	10	14
BJ 1405	4	6		5	28	9	24
BJ 1406	3			3	30	14	33
BJ 1407	3			35	24	209	30
Method	FALL	FALL	FALL	G300H	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38485

Page 8 of 11

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1408	1			6	31	74	26
BJ 1409	1			2	23	28	24
BJ 1410	1			<1	16	19	18
BJ 1411	1			2	25	5	22
BJ 1412	1			7	41	9	23
BJ 1413	2			13	29	20	38
BJ 1414	2			5	22	23	30
BJ 1415	1			5	25	37	30
BJ 1416	2	2		3	28	12	28
BJ 1417	2			7	23	64	31
BJ 1418	2	1		3	30	74	57
BJ 1419	2			2	28	34	37
BJ 1420	1			1	24	58	35
BJ 1421	-IS-			-IS-	-IS-	-IS-	-IS-
BJ 1422	1	2		2	19	10	32
BJ 1423	2			1	15	19	26
BJ 1424	2	2		2	20	25	22
BJ 1425	-IS-			-IS-	-IS-	-IS-	-IS-
BJ 1426	1			4	37	66	75
BJ 1427	1			<1	20	19	32
BJ 1428	10	10		<1	10	10	24
BJ 1429	1			<1	6	8	7
BJ 1430	3			<1	8	9	10
BJ 1431	1			<1	9	11	9
BJ 1432	-IS-			-IS-	-IS-	-IS-	-IS-
Method	FALL	FALL	FALL	G300H	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38485

Page 9 of 11

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1433	-IS-			-IS-	-IS-	-IS-	-IS-
BJ 1434	-IS-			-IS-	-IS-	-IS-	-IS-
BJ 1435	-IS-			-IS-	-IS-	-IS-	-IS-
I 1436	-IS-			-IS-	-IS-	-IS-	-IS-
BJ 1437	<1			<1	9	42	13
BJ 1438	4			<1	5	21	6
BJ 1439	<1			<1	6	14	8
BJ 1440	1			<1	6	13	8
BJ 1441	1	<1		<1	9	29	10
BJ 1442	<1			<1	10	30	11
BJ 1443	4			1	11	30	10
BJ 1444	1	<1		<1	11	29	12
BJ 1445	-IS-			-IS-	-IS-	-IS-	-IS-
BJ 1446	-IS-			-IS-	-IS-	-IS-	-IS-
BJ 1447	-IS-			-IS-	-IS-	-IS-	-IS-
BJ 1448	2	2		5	7	12	12
BJ 1449	1			6	17	14	56
BJ 1450	1	1		12	16	61	47
BJ 1451	-IS-			-IS-	-IS-	-IS-	-IS-
BJ 1452	-IS-			-IS-	-IS-	-IS-	-IS-
BJ 1453	2	1		5	10	70	27
BJ 1454	1			3	7	65	20
BJ 1455	<1			13	7	62	21
BJ 1456	<1			12	7	52	28
BJ 1457	<1			10	8	90	31
Method	FALL	FALL	FALL	G300H	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38485

Page 10 of 11

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1458	<1	<1		2	5	19	15
8J 1459	<1			10	8	24	31
BJ 1460	1			12	13	43	96
I 1461	2			24	8	94	63
8J 1462	23	37	23	16	12	164	295
BJ 1463	2			16	8	56	68
BJ 1464	3			14	7	60	45
BJ 1465	3			40	11	55	162
BJ 1466	1			21	10	28	55
BJ 1467	1	1		23	10	30	61
BJ 1468	379	330		14	8	35	61
8J 1469	<< Sample not received >>						
BJ 1470	3			37	8	39	33
BJ 1471	1			11	8	24	16
J 1472	9			26	13	61	30
BJ 1473	2			16	14	31	18
BJ 1474	<1	1		15	21	16	75
BJ 1475	-IS-			-IS-	-IS-	-IS-	-IS-
BJ 1476	<1			19	8	26	34
BJ 1477	2			27	10	35	49
BJ 1478	2	2		6	24	30	83
BJ 1479	3			14	15	41	62
BJ 1480	-IS-			-IS-	-IS-	-IS-	-IS-
BJ 1481	6			2	12	19	37
BJ 1482	27	28		4	12	25	27
Method	FALL	FALL	FALL	G300H	G300I	G300I	G300I



ASSAYCORP

ASSAY CODE: AC 38485

Page 11 of 11

Sample	Au (ppb)	Au(R) (ppb)	Au(R) (ppb)	As (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)
BJ 1483	2			5	16	46	73
BJ 1484	2			2	12	15	21
BJ 1485	<1			1	14	13	18
J 1486	1			1	12	13	20
BJ 1487	1			1	16	12	16
BJ 1488	<1			1	5	6	6
BJ 1489	<1	1		<1	5	9	11
BJ 1490	<1			<1	5	7	10
Method	FALL	FALL	FALL	G300H	G300I	G300I	G300I