

Cameco Australia

NTEL - Geochemistry Methods

	Element Analysis	Analytical Method	Unit	Detection Limit	Digestion	Technique	Precision	Sample size submitted	Jaw Crushers 6 to 10mm	Rollers <1 to 2mm	Milled .75 microns	Riffle Split
Fire assay, B and LOI	LOI	C110	%	0.1		GRAV	PREC±10%	>25 mm	Yes	No	Keegor	No
	SiO2	Calc	per	0.1			PREC±10%	>25 mm	Yes	No	Keegor	No
	Au	FAPMM	ppb	1 FA	AAS	PREC±10%	>25 mm	Yes	No	LM1	No	
	Pd	FAPMM	ppb	0.5 FA	ICP-MS	PREC±10%	>25 mm	Yes	No	Keegor	No	
	Pt	FAPMM	ppb	0.5 FA	ICP-MS	PREC±10%	>25 mm	Yes	No	Keegor	No	
	B	G140I	ppm	20 F140	ICP-OES	PREC±10%	>25 mm	Yes	No	LM1	No	
	Al2O3	G400I	ppm	100 MA4	ICP-OES	PREC±10%	<10 mm	No	Yes	No	Yes	
Standard 400G series	Ba	G400I	ppm	2 MA4	ICP-OES	PREC±10%	<10 mm	No	Yes	No	Yes	
	CaO	G400I	ppm	20 MA4	ICP-OES	PREC±10%	<10 mm	No	Yes	No	Yes	
	Cu	G400I	ppm	1 MA4	ICP-OES	PREC±10%	<10 mm	No	Yes	No	Yes	
	Fe2O3	G400I	ppm	50 MA4	ICP-OES	PREC±10%	<10 mm	No	Yes	No	Yes	
	K2O	G400I	ppm	100 MA4	ICP-OES	PREC±10%	<10 mm	No	Yes	No	Yes	
	Li	G400I	ppm	1 MA4	ICP-OES	PREC±10%	<10 mm	No	Yes	No	Yes	
	MgO	G400I	ppm	20 MA4	ICP-OES	PREC±10%	<10 mm	No	Yes	No	Yes	
	MnO	G400I	ppm	2 MA4	ICP-OES	PREC±10%	<10 mm	No	Yes	No	Yes	
	Na2O	G400I	ppm	100 MA4	ICP-OES	PREC±10%	<10 mm	No	Yes	No	Yes	
	P2O5	G400I	ppm	50 MA4	ICP-OES	PREC±10%	<10 mm	No	Yes	No	Yes	
	S	G400I	ppm	20 MA4	ICP-OES	PREC±10%	<10 mm	No	Yes	No	Yes	
	TiO	G400I	ppm	20 MA4	ICP-OES	PREC±10%	<10 mm	No	Yes	No	Yes	
	V	G400I	ppm	2 MA4	ICP-OES	PREC±10%	<10 mm	No	Yes	No	Yes	
	Zn	G400I	ppm	2 MA4	ICP-OES	PREC±10%	<10 mm	No	Yes	No	Yes	
	Ag	G400M	ppm	0.05 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	As	G400M	ppm	0.5 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Be	G400M	ppm	0.1 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Bi	G400M	ppm	0.02 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Ce	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Co	G400M	ppm	0.05 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Dy	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Er	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Eu	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Gd	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Ho	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	La	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Lu	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Mo	G400M	ppm	0.05 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Nb	G400M	ppm	0.02 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Nd	G400M	ppm	0.02 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Ni	G400M	ppm	0.2 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Pb	G400M	ppm	0.2 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Pb-204	G400M	ppm	0.2 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Pb-206	G400M	ppm	0.2 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Pb-207	G400M	ppm	0.2 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Pb-208	G400M	ppm	0.2 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Pr	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Rb	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Se	G400M	ppm	2 G400	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Sm	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Sr	G400M	ppm	0.05 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Tb	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Th	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Tm	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	U(t)	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Y	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Yb	G400M	ppm	0.01 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
	Zr	G400M	ppm	0.1 MA4	ICP-MS	PREC±10%	<10 mm	No	Yes	No	Yes	
Standard G950 series	Pb204	G950M	ppb	0.1	G950	ICPMS	PREC±10%	<10 mm	No	Yes	No	Yes
	Pb205	G950M	ppb	0.1	G950	ICPMS	PREC±10%	<10 mm	No	Yes	No	Yes
	Pb207	G950M	ppb	0.1	G950	ICPMS	PREC±10%	<10 mm	No	Yes	No	Yes
	Pb208	G950M	ppb	0.1	G950	ICPMS	PREC±10%	<10 mm	No	Yes	No	Yes
	PbTOT	G950M	ppb	0.1	G950	ICPMS	PREC±10%	<10 mm	No	Yes	No	Yes
	U	G950M	ppb	0.01	G950	ICPMS	PREC±10%	<10 mm	No	Yes	No	Yes