

Cameco Australia Pty Ltd
EL22784 & 22785: Sample Geochem

project_nu	Sample Nu	Northing -	Easting -	m Elevation -	Assay Code	Rock_Type	Lithology	Lab Refere	U	Th	U-Th ratio	U-Zr ratio	Au ppb	Ag	AL203	As	Ba	Be	Bi	B
MD	MD080001	8644362	357009.6	69	ASSAY	SDST	Variably ha	EL12566	0.79	3	0.2633	0.0549	-1	-0.05	5500	2	8	0.1	0.02	20
MD	MD080002	8644285	357141.6	100	ASSAY	SDST	Fine-graine	EL12566	0.46	2.41	0.1909	0.0267	-1	-0.05	4900	2	10	0.1	-0.02	-20
MD	MD080003	8644445	357127.6	62	ASSAY	SDST	Coarse-grai	EL12566	0.59	2.34	0.2521	0.0434	-1	0.15	800	2	8	-0.1	-0.02	-20
MD	MD080004	8641577	353640.6	46	ASSAY	GRST	Very coars	EL12566	1.14	5.28	0.2159	0.0298	1	0.15	12600	2.5	34	0.1	0.04	60
MD	MD080004	8641577	353640.6	46	L_ASSAY	GRST	Very coars	EL12566	1.17	5.31	0.2203	0.021		0.15	13100	3	36	0.1	0.04	40
MD	MD080005	8641705	353725.6	67	ASSAY	PEST	Non-heam	EL12566	0.6	4.22	0.1422	0.0165	2	0.25	12800	1.5	14	-0.1	-0.02	20
MD	MD080006	8641980	353921.6	46	ASSAY	SDST	Coarse-grai	EL12566	0.82	4.2	0.1952	0.0168	-1	-0.05	14300	2	158	0.2	0.02	40
MD	MD080007	8624381	360540.3	286	ASSAY	SDST	Fine-graine	EL12566	0.5	2.32	0.2155	0.0081	3	-0.05	27100	1.5	12	-0.1	-0.02	40
MD	MD080403	8644504	357050.6	37	ASSAY	SDST	SDST with	EL12566	0.72	2.69	0.2677	0.04	-1	-0.05	3100	1.5	12	-0.1	-0.02	-20
MD	MD080404	8641450	353655.6	48	ASSAY	SDST	A moderat	EL12566	0.69	3.8	0.1816	0.0283	-1	-0.05	12900	2	10	0.1	0.04	60
MD	MD080501	8644582	357107.6	36	ASSAY	SDST	SANDSTON	EL12566	0.64	2.51	0.255	0.0193	-1	-0.05	4100	1	8	0.1	0.04	20
MD	MD080502	8644622	357165.6	39	ASSAY	SDST	sandstone	EL12566	0.88	2.89	0.3045	0.0433	-1	-0.05	3500	2	18	0.1	-0.02	-20
MD	MD080503	8644636	357172.6	42	ASSAY	SDST	Sandstone	EL12566	0.6	2.41	0.249	0.0682	10	-0.05	1200	2.5	12	0.1	-0.02	-20
MD	MD080504	8641333	353475.6	57	ASSAY	SDST	sandstone	EL12566	0.88	9.26	0.095	0.0118	1	-0.05	16600	2	34	0.2	-0.02	60
MD	MD080505	8641109	353297.6	64	ASSAY	SDST	Sandstone	EL12566	1.51	5.12	0.2949	0.0259	-1	-0.05	19600	2.5	30	0.2	0.04	60
MD	MD080505	8641109	353297.6	64	L_ASSAY	SDST	Sandstone	EL12566	1.5	5.05	0.297	0.026		-0.05	19900	2.5	30	0.1	0.02	60
MD	MD083001	8623781	360087.3	310	ASSAY	SDST	Medium-gr	EL12566	0.78	2.32	0.3362	0.0497	-1	-0.05	6300	0.5	16	0.1	-0.02	-20

Cao	Ce	Co	Cr	Cu	Dy	Er	Eu	Fe2O3	Gd	Hf	Ho	K2O	La	Li	Lu	LOI	MgO	MnO	Mo	Na2O
100	14	0.45	-5	-1	0.7	0.36	0.12	4850	0.83	0.46	0.13	700	7.12	1	0.04	0.3	140	28	0.15	-100
140	11.4	0.3	-5	1	0.3	0.16	0.08	8300	0.44	0.56	0.06	1000	5.54	2	0.03	0.2	220	38	0.25	-100
120	15.7	0.8	-5	2	0.62	0.31	0.1	3550	0.74	0.44	0.12	100	7.97	1	0.04	-0.1	100	26	0.15	-100
580	35	0.45	5	1	1.31	0.53	0.35	18700	1.7	1.1	0.21	2600	16	-1	0.08	0.5	220	104	0.3	-100
620	34.9	0.45	5	1	1.3	0.53	0.35	19400	1.68	1.52	0.21	2700	16	-1	0.08	0.5	260	110	0.35	-100
200	21.1	0.45	-5	1	0.3	0.15	0.2	13000	0.87	0.99	0.05	2000	10.4	2	0.03	0.5	200	36	0.15	100
260	28.7	0.15	-5	-1	0.59	0.18	0.25	5350	1.31	1.46	0.08	3300	13.8	-1	0.04	0.5	280	24	0.2	100
180	26	0.25	-5	-1	0.66	0.39	0.4	9200	1.1	1.62	0.13	2500	13.6	4	0.06	0.9	340	20	0.35	-100
100	12.9	0.5	-5	1	1.08	0.57	0.15	8050	1.11	0.87	0.21	700	6.14	1	0.07	0.2	100	22	0.2	-100
140	26.9	0.2	5	-1	0.47	0.21	0.28	12900	1.17	0.95	0.08	3400	11.8	1	0.04	0.3	240	26	0.35	-100
140	9.55	0.2	-5	-1	0.44	0.25	0.09	3700	0.55	1.03	0.09	1000	4.81	1	0.04	0.1	160	26	0.3	-100
140	12.4	0.2	-5	-1	0.84	0.46	0.13	6250	0.85	0.77	0.16	400	5.79	2	0.06	0.2	120	24	0.2	-100
120	14.3	0.2	-5	-1	0.35	0.17	0.11	7750	0.61	0.43	0.06	200	6.85	2	0.03	-0.1	100	42	0.25	-100
280	35	0.45	-5	1	0.9	0.42	0.43	17400	1.93	2.13	0.16	4700	15.2	1	0.06	0.4	320	52	0.25	-100
540	32.5	0.2	5	-1	0.76	0.22	0.29	5950	1.6	1.66	0.1	4700	15.2	-1	0.04	0.6	300	34	0.3	-100
560	31.6	0.2	-5	-1	0.77	0.22	0.28	5950	1.59	1.62	0.09	4800	14.9	-1	0.04	0.5	280	30	0.2	-100
200	20.1	0.2	-5	-1	0.93	0.43	0.24	3150	1.07	0.21	0.17	1500	9.17	1	0.05	0.2	280	24	0.4	-100

Nb	Nd	Ni	Pb206	Pb207	Pb208	Pb204 ppb	Pb206 ppb	Pb207 ppb	Pb208 ppb	PbTOT ppb	Pb	Pd ppb	Pr	Pt ppb	Rb	S	Se	Sm	Sn	Sr
0.35	5.8	0.6	0.2	-0.2	0.4	12.2	211	199	452	875	0.8	-1	1.52	-1	1.65	20	-2	1.09	-0.2	8.95
0.55	4.4	0.6	0.4	0.2	0.6	0.95	26.5	17	38.6	83	1.2	-1	1.22	1	2.51	20	-2	0.69	-0.2	11
0.75	7.1	0.4	0.4	-0.2	0.6	1.11	49.1	23.3	58.6	132	1	-1	1.86	-1	0.64	-20	-2	1.17	0.2	10.2
1.45	12.2	0.6	0.6	0.4	1.2	0.08	4.75	2.28	5.96	13.1	2	-1	3.29	-1	3.73	360	-2	2.04	0.6	995
1.75	12.1	0.6	0.6	0.4	1.2	0.09	5.02	2.48	6.1	13.7	2.2		3.26		3.74	380	-2	2.07	0.8	1020
1.45	7.65	0.4	0.4	0.2	0.8	0.52	16.9	9.48	23.7	50.6	1.4	-1	2.08	-1	2.83	60	-2	1.28	0.6	115
0.9	10.1	0.6	0.4	0.2	0.8	0.18	7.66	4.47	11.4	23.7	1.4	-1	2.73	-1	4.62	200	-2	1.71	0.4	541
1.2	11.5	0.6	0.4	0.2	0.8	0.88	21.3	16.3	39	77.5	1.4	-1	3.01	-1	3.55	40	-2	1.88	-0.2	83.7
0.4	6	0.4	0.2	-0.2	0.4	0.46	18.9	8.39	19	46.8	0.8	-1	1.5	-1	1.36	40	-2	1.06	0.2	116
0.8	10.8	0.6	0.2	-0.2	0.4	0.45	20.3	10.5	26	57.2	0.8	1	2.83	-1	4.34	40	-2	2	0.4	61
0.7	4.05	0.6	0.4	-0.2	0.6	1.35	41.6	24.8	56.9	125	1	-1	1.07	-1	1.77	-20	-2	0.76	-0.2	18.9
0.55	5.15	0.4	0.4	-0.2	0.6	0.61	23.6	11.3	27.3	62.9	1	-1	1.3	-1	1.28	-20	-2	0.94	-0.2	35.9
0.3	5.05	0.4	0.6	0.4	1.2	2.07	54.2	36.2	84.1	177	2.2	1	1.38	-1	0.57	-20	-2	0.89	-0.2	45
1.75	14.3	0.4	0.4	-0.2	0.8	-0.01	2.22	1.06	3.35	6.64	1.4	-1	3.63	-1	5.84	80	-2	2.63	1.2	195
1.1	11.4	0.6	0.6	0.2	0.8	0.02	3.24	1.87	3.71	8.83	1.6	-1	3.24	-1	5.22	280	-2	1.9	1	788
1.15	11.1	0.6	0.6	0.2	0.8	-0.01	3.17	1.57	3.43	8.15	1.6		3.18		5.29	280	-2	1.89	1	783
0.45	7.5	0.6	0.2	-0.2	0.4	0.23	9.44	5.87	14.8	30.3	0.8	-1	2.02	-1	2.71	40	-2	1.29	-0.2	88.6

Ta	Tb	TiO2	Tm	U ppb	V	W	Y	Zn	Zr	Date_Collected
-0.02	0.12	180	0.05	114	2	1.05	3.53	-2	14.4	20/09/2008
0.04	0.06	220	0.03	65.5	4	0.4	1.57	-2	17.2	20/09/2008
-0.02	0.11	140	0.05	104	-2	0.75	3.18	2	13.6	20/09/2008
-0.02	0.26	800	0.08	125	8	1	5.34	2	38.3	20/09/2008
-0.02	0.26	820	0.08	119	6	1.15	5.24	2	55.7	20/09/2008
0.1	0.08	600	0.03	113	4	1.95	1.32	2	36.4	20/09/2008
0.12	0.15	280	0.03	86.3	4	0.5	1.94	2	48.7	20/09/2008
0.08	0.13	480	0.06	44.1	8	0.35	3.52	2	61.8	23/09/2008
0.02	0.18	180	0.08	107	2	1.35	6.03	-2	18	22/09/2008
0.08	0.11	280	0.03	116	4	0.5	2.27	2	24.4	18/09/2008
0.06	0.07	280	0.04	108	2	0.65	2.51	-2	33.1	20/09/2008
0.02	0.14	360	0.07	98.1	4	0.55	4.96	-2	20.3	20/09/2008
-0.02	0.07	160	0.03	116	4	0.85	1.82	-2	8.8	20/09/2008
0.2	0.2	800	0.06	72.3	4	1.55	4.37	2	74.6	20/09/2008
0.16	0.22	440	0.03	103	6	0.65	2.17	2	58.2	20/09/2008
0.16	0.22	460	0.03	109	4	0.65	2.21	2	57.8	20/09/2008
-0.02	0.17	340	0.05	77	-2	0.2	4.74	-2	15.7	27/07/2008