



Jinning Testing & Inspection

Analytical Report

JOB NUMBER	JTI1909919
REPORT DATE	September 25 2019
SAMPLES	5
DATE RECEIVED	September 20 2019

AUTHORISATION

Rick Pearce - Laboratory Manager

CLIENT	Hanking Australia Investment Pty Ltd
ADDRESS	Level 26, 140 St. George Tce, Perth
CONTACT	Fan.Wu@hanking.com.au

PROJECT	
P/O#	MB012

All orders are accepted and all reports and certificates issued subject to the Terms and Conditions of Service which are attached separately.

Tyler Huang
Managing Director
14 Bell Street, Canning Vale, WA, 6155
JINNING PTY LTD
T: +61 8 6107 4655
M: 0432 711 220
[E: tyler.huang@jinning.com.au](mailto:tyler.huang@jinning.com.au)
www.jinning.com.au

Rick Pearce MRACI CChem
Laboratory Manager
14 Bell Street, Canning Vale, WA, 6155
JINNING PTY LTD
T: +61 8 6107 4655
M: 0439 640 292
[E: rick.pearce@jinning.com.au](mailto:rick.pearce@jinning.com.au)
www.jinning.com.au

JTI1909919	Au1	Au2	Au3	WT1
Scheme	FA30A	FA30A	FA30A	Weight
Units	ppm	ppm	ppm	g
Detection Limit	0.01	0.01	0.01	0.01
Blank 1	<0.01			30.00
HKR03598	0.04			28.57
HKR03598Rpt	0.02			30.55
HKR03599	4.62	4.63	4.70	15.72
HKR03600	0.01			29.53
HKR03601	0.05			28.90
HKR03602	0.02			29.29
HKR03602Rpt	0.02			31.53
Nominal	0.78			
STD 1 AUOE-12	0.78			30.46
Nominal	3.77	3.77		
STD 2 AUSK-7	3.79	3.79		29.21

WT1

Weight of sample used for analysis.

SCHEME FA50A/FA30A

A nominal charge sample of 50g/30g is fired and cupelled as per the classical lead collection fire assay process. The noble metal prill is parted with nitric acid, dissolved in aqua regia and diluted for analysis. Analyses are performed via AAS.

Due to the nature of some samples charge weights may have been reduced.