

Appendix 6 - Standards

Hole_ID	Sample ID	QAQC	STD_ID	JOB	Fe	Al2O3	CaO	Cr2O3	K2O	MgO	MnO	Na2O	P	S	SiO2	TiO2	V2O5	LOI	Total	Result
RR00596D	RR56150	STD	GIOP115	SHD440	61.3	1.71	0.22	0.02	0.02	0.16	0.02	0.08	0.01	0.007	8.99	0.21	0.01	0.8	99.8	PASS
RR00598D	RR56200	STD	GIOP15	SHD443	50.5	4.05	0.16	0.03	1.22	0.04	0.19	0.35	0.031	0.004	20.3	0.04	0.02	1.35	99.7	PASS
RR00599D	RR56250	STD	GIOP52	SHD446	56.5	2.6	0.18	0.02	-0.01	0.16	0.11	0.02	0.041	0.015	5.81	0.16	0.01	9.83	99.7	PASS
RR00599D	RR56300	STD	GIOP115	SHD446	61.3	1.74	0.23	0.02	0.02	0.15	0.02	0.08	0.01	0.009	8.98	0.21	0.01	0.88	100	PASS
RR00601D	RR56350	STD	GIOP15	SHD448	50.5	4.03	0.16	0.01	1.22	0.06	0.19	0.36	0.031	0.003	20.3	0.04	0.02	1.35	99.6	PASS
RR00602D	RR56400	STD	GIOP15	SHD450	50.6	4.04	0.16	0.02	1.21	0.05	0.19	0.35	0.032	0.004	20.1	0.04	0.02	1.31	99.6	PASS