



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: **u282154**
Date Finished: 01/12/2017
Order: NC_003
Project: Wollogorang
Date Received: 13/11/2017
Samples Analysed: **405**

FINAL ANALYSIS REPORT

Analysis of Mineral Samples

for

Northern Cobalt Ltd

67 Goodwood Rd Wayville SA 5034

Attention: Mr. M Schwarz

Authorised By:

Tom Lowther

Operations Manager

Bureau Veritas Minerals Pty Ltd



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 1 of 49

| | Au1 ppb | Au2 ppb | Pt ppb | Pd ppb | Ca % | Cr ppm | Fe % | K % |
|-----------------|------------|------------|-----------|-----------|---------|-----------|---------|--------|
| Detection Limit | 1 | 1 | 5 | 5 | 0.01 | 10 | 0.01 | 0.01 |
| 149389 | 3 | NR | <5 | <5 | 0.33 | 60 | 10.8 | 5.96 |
| 149390 | 3 | NR | <5 | <5 | 0.76 | 20 | 1.35 | 11.6 |
| 13630 | 4 | NR | <5 | <5 | 0.62 | 20 | 1.60 | 8.41 |
| 13631 | 3 | NR | <5 | <5 | 0.11 | 10 | 0.72 | 1.79 |
| 13631 Rpt | 3 | NR | <5 | <5 | 0.11 | <10 | 0.70 | 1.70 |
| 13632 | 1 | NR | <5 | <5 | 0.07 | <10 | 0.85 | 2.25 |
| 13632 Rpt | 3 | NR | <5 | <5 | 0.07 | <10 | 0.85 | 2.30 |
| 13633 | 1 | NR | <5 | <5 | 0.09 | 10 | 0.95 | 2.96 |
| 13634 | 2 | NR | <5 | <5 | 0.09 | 10 | 1.28 | 3.34 |
| 13635 | 7 | NR | 5 | <5 | 0.15 | 40 | 4.41 | 7.61 |
| 13636 | <1 | NR | <5 | <5 | 0.07 | 10 | 1.32 | 2.82 |
| 13637 | <1 | NR | <5 | <5 | 0.04 | <10 | 1.03 | 1.91 |
| 13638 | 1 | NR | <5 | <5 | 0.05 | <10 | 0.69 | 1.58 |
| 13639 | 3 | NR | <5 | <5 | 0.09 | 10 | 1.85 | 4.32 |
| 13640 | 2 | NR | <5 | <5 | 0.09 | 10 | 1.79 | 4.52 |
| 13641 | 6 | NR | <5 | <5 | 0.16 | 30 | 3.42 | 7.45 |
| 13642 | 3 | NR | <5 | <5 | 0.20 | 30 | 4.39 | 7.76 |
| 149391 | 2 | NR | <5 | <5 | 3.32 | 30 | 3.96 | 6.40 |
| Std Nominal | 52 | 52 | 45 | 45 | 0.10 | 1.70% | 47.5 | <0.01 |
| Determined | 51 | NR | 45 | 40 | 0.11 | 1.47% | 48.0 | 0.01 |
| 149392 | 1 | NR | <5 | <5 | 3.18 | 30 | 3.47 | 6.24 |
| 13651 | 2 | NR | <5 | <5 | 3.67 | 30 | 4.79 | 6.81 |
| 13652 | 2 | NR | <5 | <5 | 3.11 | 30 | 4.63 | 6.67 |
| 13653 | <1 | NR | <5 | <5 | 4.19 | 30 | 4.02 | 6.27 |
| 13654 | <1 | NR | <5 | <5 | 4.23 | 30 | 4.88 | 6.70 |
| 149393 | 2 | NR | <5 | <5 | 6.70 | 20 | 4.58 | 5.69 |
| 149394 | 5 | NR | <5 | <5 | 4.17 | 10 | 4.70 | 7.88 |
| 13664 | 3 | NR | <5 | <5 | 2.10 | 20 | 9.24 | 6.48 |
| 13665 | 1 | NR | <5 | <5 | 3.18 | 10 | 8.09 | 6.18 |
| 13666 | <1 | NR | <5 | <5 | 2.36 | 20 | 9.10 | 6.24 |
| Std Nominal | 1.37M | 1.37M | | | 1.53 | 1670 | 9.20 | 0.09 |
| Determined | 1.34M | NR | <5 | <5 | 1.53 | 1190 | 9.28 | 0.09 |
| 13667 | 3 | NR | <5 | <5 | 2.42 | 20 | 5.70 | 8.24 |
| 13668 | <1 | NR | <5 | <5 | 2.57 | 20 | 7.59 | 7.28 |
| 13668 Rpt | 1 | NR | <5 | <5 | 2.58 | 20 | 7.55 | 7.20 |
| 13669 | <1 | NR | <5 | <5 | 1.84 | 20 | 8.60 | 6.83 |
| 13670 | <1 | NR | <5 | <5 | 1.56 | 20 | 9.78 | 6.71 |
| 13671 | <1 | NR | <5 | <5 | 2.09 | 10 | 9.34 | 6.56 |
| 13672 | <1 | NR | <5 | <5 | 3.05 | 10 | 5.43 | 8.41 |
| 13673 | <1 | NR | <5 | <5 | 1.58 | 10 | 11.1 | 5.79 |
| 13674 | 1 | NR | <5 | <5 | 1.31 | 20 | 12.3 | 5.49 |
| 13675 | 1 | NR | <5 | <5 | 1.15 | 10 | 12.8 | 4.78 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 2 of 49

| | Au1 ppb | Au2 ppb | Pt ppb | Pd ppb | Ca % | Cr ppm | Fe % | K % |
|-----------------|------------|------------|-----------|-----------|---------|-----------|---------|--------|
| Detection Limit | 1 | 1 | 5 | 5 | 0.01 | 10 | 0.01 | 0.01 |
| 149395 | <1 | NR | <5 | <5 | 1.17 | 20 | 10.1 | 6.31 |
| 149396 | <1 | NR | <5 | <5 | 0.86 | 20 | 8.38 | 7.37 |
| 149397 | 2 | NR | <5 | <5 | 0.71 | 20 | 6.30 | 8.98 |
| 149398 | 1 | NR | <5 | <5 | 0.74 | 20 | 7.80 | 8.10 |
| 149398 Rpt | 1 | NR | <5 | <5 | 0.73 | 10 | 7.68 | 7.94 |
| 13693 | 1 | NR | <5 | <5 | 2.66 | 10 | 4.10 | 9.20 |
| 13694 | <1 | NR | <5 | <5 | 12.3 | 10 | 6.24 | 2.93 |
| 13695 | 1 | NR | <5 | <5 | 9.00 | 10 | 6.93 | 4.31 |
| 13696 | <1 | NR | <5 | <5 | 14.1 | <10 | 5.41 | 2.33 |
| 13697 | 1 | NR | <5 | <5 | 14.7 | <10 | 5.03 | 2.29 |
| 13698 | 1 | NR | 5 | <5 | 11.1 | 10 | 6.51 | 3.33 |
| 13699 | 1 | NR | <5 | <5 | 3.10 | 20 | 6.42 | 4.02 |
| 13700 | IS | NR | IS | IS | 1.71 | 6430 | 24.4 | 0.10 |
| 13700 Rpt | NR | NR | NR | NR | 1.69 | 6460 | 24.6 | 0.09 |
| 13701 | <1 | NR | <5 | <5 | 10.5 | 30 | 6.02 | 3.84 |
| Std Nominal | 860 | 860 | 910 | 690 | 8.22 | 30 | 6.27 | 0.21 |
| Determined | 870 | NR | 915 | 695 | 8.19 | 20 | 6.21 | 0.20 |
| 13702 | 10 | NR | <5 | <5 | 10.4 | 20 | 6.49 | 3.64 |
| 13702 Rpt | 10 | NR | <5 | <5 | 10.3 | 20 | 6.34 | 3.54 |
| 13703 | 2 | NR | <5 | <5 | 7.70 | 20 | 5.63 | 5.14 |
| 13704 | 2 | NR | <5 | <5 | 6.79 | <10 | 4.03 | 7.51 |
| 13705 | 3 | NR | <5 | <5 | 3.93 | <10 | 8.47 | 6.39 |
| 13706 | 3 | NR | <5 | <5 | 2.21 | <10 | 9.91 | 5.80 |
| 13707 | <1 | NR | <5 | <5 | 4.31 | <10 | 7.28 | 6.32 |
| 13708 | <1 | NR | <5 | <5 | 2.95 | <10 | 6.88 | 6.64 |
| 13709 | 1 | NR | <5 | <5 | 1.98 | <10 | 10.6 | 5.41 |
| 13710 | <1 | NR | <5 | <5 | 2.73 | <10 | 11.4 | 5.06 |
| 13711 | 1 | NR | <5 | <5 | 4.10 | <10 | 9.24 | 4.89 |
| 13712 | 1 | NR | <5 | <5 | 3.09 | <10 | 11.0 | 4.74 |
| 13713 | <1 | NR | <5 | <5 | 1.72 | <10 | 12.0 | 5.00 |
| 13714 | <1 | NR | <5 | <5 | 2.24 | <10 | 12.0 | 4.45 |
| 13715 | <1 | NR | <5 | <5 | 0.74 | <10 | 14.1 | 4.06 |
| 13716 | <1 | NR | <5 | <5 | 0.73 | <10 | 15.3 | 3.25 |
| 13717 | <1 | NR | <5 | <5 | 0.82 | <10 | 15.4 | 3.08 |
| 13718 | <1 | NR | <5 | <5 | 0.71 | <10 | 12.2 | 3.42 |
| 13719 | <1 | NR | <5 | <5 | 0.75 | <10 | 14.1 | 3.13 |
| 13720 | IS | NR | IS | IS | 0.06 | 20 | 8.76 | 0.16 |
| 13720 Rpt | NR | NR | NR | NR | 0.06 | 20 | 8.75 | 0.15 |
| 13721 | <1 | NR | <5 | <5 | 0.72 | <10 | 15.0 | 3.03 |
| 13722 | <1 | NR | <5 | <5 | 0.76 | <10 | 15.2 | 3.19 |
| 13723 | <1 | NR | <5 | <5 | 0.77 | <10 | 12.3 | 4.08 |
| 13724 | 1 | NR | <5 | <5 | 1.34 | <10 | 11.8 | 4.96 |
| 13725 | 3 | NR | <5 | <5 | 4.30 | <10 | 9.72 | 4.27 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 3 of 49

| | Au1 ppb | Au2 ppb | Pt ppb | Pd ppb | Ca % | Cr ppm | Fe % | K % |
|-----------------|------------|------------|-----------|-----------|---------|-----------|---------|--------|
| Detection Limit | 1 | 1 | 5 | 5 | 0.01 | 10 | 0.01 | 0.01 |
| 13726 | <1 | NR | <5 | <5 | 12.9 | <10 | 5.82 | 2.01 |
| 13728 | 3 | NR | <5 | <5 | 0.11 | 90 | 18.0 | 1.12 |
| 13729 | 5 | NR | <5 | <5 | 0.05 | 50 | 10.0 | 4.67 |
| 13730 | 1 | NR | <5 | <5 | 0.65 | 40 | 4.01 | 9.92 |
| 13731 | 1 | NR | <5 | <5 | 0.69 | 30 | 2.58 | 11.0 |
| 13732 | 1 | NR | <5 | <5 | 0.69 | 20 | 1.99 | 11.5 |
| 13732 Rpt | 1 | NR | <5 | <5 | 0.71 | 20 | 2.01 | 11.7 |
| 13733 | 4 | NR | <5 | <5 | 0.67 | 20 | 2.57 | 11.4 |
| 13734 | 2 | NR | <5 | <5 | 0.70 | 20 | 2.06 | 11.1 |
| 13735 | 1 | NR | <5 | <5 | 0.73 | 20 | 1.79 | 11.1 |
| 13736 | 10 | NR | <5 | <5 | 0.93 | 20 | 1.60 | 11.7 |
| 13737 | 1 | NR | 5 | <5 | 0.39 | 20 | 1.41 | 9.00 |
| Std Nominal | 2.42M | 2.42M | | | 5.91 | 230 | 9.63 | 0.60 |
| Determined | 2.36M | NR | <5 | <5 | 5.95 | 150 | 9.72 | 0.62 |
| 13738 | 1 | NR | <5 | <5 | 0.08 | <10 | 0.83 | 1.65 |
| 13739 | <1 | NR | <5 | <5 | 0.08 | <10 | 1.00 | 2.41 |
| 13740 | 1 | NR | <5 | <5 | 0.07 | <10 | 1.18 | 2.40 |
| 13741 | 1 | NR | <5 | <5 | 0.09 | 10 | 1.29 | 3.47 |
| 13742 | 8 | NR | <5 | <5 | 0.08 | 10 | 1.47 | 3.37 |
| 13743 | 5 | NR | <5 | <5 | 0.11 | 30 | 3.27 | 7.29 |
| 13744 | 2 | NR | <5 | <5 | 0.09 | 20 | 1.62 | 3.48 |
| 13745 | <1 | NR | <5 | <5 | 0.07 | <10 | 0.66 | 1.60 |
| 13746 | 2 | NR | <5 | <5 | 0.10 | 20 | 1.67 | 2.85 |
| 13747 | <1 | NR | <5 | <5 | 0.07 | 10 | 0.87 | 2.18 |
| 13748 | 2 | NR | <5 | <5 | 0.07 | 10 | 1.34 | 2.74 |
| 13749 | 3 | NR | <5 | <5 | 3.60 | 30 | 3.58 | 6.10 |
| 13750 | 8 | NR | <5 | <5 | 3.68 | 20 | 3.76 | 5.83 |
| 13751 | 3 | NR | <5 | <5 | 4.49 | 20 | 3.07 | 5.82 |
| 13751 Rpt | 5 | NR | <5 | <5 | 4.53 | 30 | 3.10 | 5.86 |
| 13752 | 1 | NR | <5 | <5 | 2.77 | 30 | 4.18 | 6.82 |
| 13753 | 1 | NR | <5 | <5 | 1.46 | 30 | 6.05 | 6.53 |
| 13754 | 1 | NR | <5 | <5 | 4.10 | 30 | 3.91 | 6.42 |
| 13755 | 3 | NR | <5 | <5 | 4.42 | 30 | 4.53 | 5.95 |
| 13756 | 1 | NR | <5 | <5 | 3.99 | 30 | 4.18 | 6.26 |
| 13757 | 1 | NR | <5 | <5 | 4.34 | 30 | 4.19 | 6.17 |
| 13757 Rpt | 1 | NR | <5 | <5 | 4.37 | 20 | 4.20 | 6.18 |
| 13758 | 3 | NR | <5 | <5 | 4.33 | 20 | 4.40 | 6.42 |
| Std Nominal | 4.94M | 4.94M | | | 0.58 | 10 | 1.47 | 4.16 |
| Determined | 4.94M | NR | <5 | <5 | 0.59 | <10 | 1.43 | 4.02 |
| 13759 | 2 | NR | <5 | <5 | 4.92 | 30 | 4.70 | 6.31 |
| 13760 | IS | NR | IS | IS | 1.72 | 6710 | 24.8 | 0.10 |
| 13761 | 1 | NR | <5 | <5 | 4.50 | 40 | 5.06 | 6.47 |
| 13762 | 1 | NR | <5 | <5 | 4.27 | 30 | 4.53 | 6.71 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 4 of 49

| | Au1 ppb | Au2 ppb | Pt ppb | Pd ppb | Ca % | Cr ppm | Fe % | K % |
|-----------------|------------|------------|-----------|-----------|---------|-----------|---------|--------|
| Detection Limit | 1 | 1 | 5 | 5 | 0.01 | 10 | 0.01 | 0.01 |
| 13763 | 1 | NR | <5 | <5 | 4.21 | 30 | 5.20 | 6.30 |
| 13764 | 2 | NR | <5 | <5 | 4.30 | 40 | 4.27 | 5.92 |
| 13764 Rpt | 2 | NR | <5 | <5 | 4.46 | 30 | 4.43 | 6.13 |
| 13765 | 2 | NR | <5 | <5 | 4.40 | 40 | 7.40 | 6.33 |
| 13765 Rpt | 4 | NR | <5 | <5 | 4.34 | 30 | 7.32 | 6.34 |
| 13766 | 2 | NR | <5 | <5 | 11.1 | 20 | 7.25 | 3.56 |
| 13767 | 2 | NR | <5 | <5 | 3.51 | 20 | 5.89 | 3.76 |
| 13768 | 3 | NR | <5 | <5 | 5.84 | 10 | 4.35 | 8.41 |
| 13769 | 4 | NR | <5 | <5 | 3.79 | 10 | 5.80 | 8.12 |
| Std Nominal | 52 | 52 | 45 | 45 | 2.48 | 170 | 8.65 | 2.35 |
| Determined | 53 | NR | 40 | 40 | 2.51 | 120 | 8.53 | 2.36 |
| 13770 | 8 | NR | <5 | <5 | 4.15 | 20 | 5.01 | 8.02 |
| 149399 | 2 | NR | <5 | <5 | 2.82 | 20 | 7.02 | 7.91 |
| 149400 | 1 | NR | <5 | <5 | 2.66 | 30 | 7.02 | 7.97 |
| 149401 | 9 | NR | <5 | <5 | 3.73 | 10 | 6.26 | 7.10 |
| 149402 | 1 | NR | <5 | <5 | 2.36 | 20 | 6.39 | 7.64 |
| 149403 | <1 | NR | <5 | <5 | 1.96 | 20 | 8.77 | 6.54 |
| 149404 | 6 | NR | <5 | <5 | 1.32 | 20 | 7.66 | 7.57 |
| 149405 | 2 | NR | <5 | <5 | 1.00 | 10 | 8.03 | 7.45 |
| 13796 | 1 | NR | <5 | <5 | 0.76 | 10 | 4.95 | 8.67 |
| 13797 | 2 | NR | <5 | <5 | 0.73 | 10 | 6.14 | 6.72 |
| 13798 | 5 | NR | <5 | <5 | 0.73 | 10 | 6.20 | 8.26 |
| 13799 | 6 | NR | <5 | <5 | 0.78 | 20 | 6.98 | 7.96 |
| 13800 | IS | NR | IS | IS | 0.07 | 20 | 9.00 | 0.16 |
| 13801 | 6 | NR | <5 | <5 | 0.86 | 20 | 6.02 | 9.79 |
| 13802 | 6 | NR | <5 | <5 | 1.11 | 10 | 5.36 | 10.1 |
| 13803 | 5 | NR | <5 | <5 | 2.52 | 10 | 4.22 | 9.09 |
| 13804 | 3 | NR | <5 | <5 | 1.22 | 30 | 6.76 | 8.25 |
| 13805 | 2 | NR | <5 | <5 | 0.33 | 30 | 6.48 | 8.24 |
| 13806 | <1 | NR | <5 | <5 | 0.18 | 20 | 2.37 | 2.61 |
| 13807 | 5 | NR | <5 | <5 | 0.17 | 20 | 2.45 | 3.70 |
| 13808 | 9 | NR | <5 | <5 | 0.20 | 30 | 4.07 | 5.91 |
| Std Nominal | 1.37M | 1.37M | | | 0.54 | 90 | 0.18 | <0.01 |
| Determined | 1.38M | NR | <5 | <5 | 0.56 | 30 | 0.17 | <0.01 |
| 13809 | 3 | NR | <5 | <5 | 6.10 | 40 | 7.81 | 5.14 |
| 13810 | 7 | NR | <5 | <5 | 2.90 | 40 | 5.97 | 7.68 |
| 13810 Rpt | 9 | NR | <5 | <5 | 2.98 | 40 | 5.80 | 8.24 |
| 149406 | 3 | NR | <5 | <5 | 0.83 | <10 | 4.72 | 9.61 |
| 149407 | 2 | NR | <5 | <5 | 0.84 | <10 | 5.90 | 9.39 |
| 149408 | 1 | NR | <5 | <5 | 1.69 | <10 | 5.49 | 8.83 |
| 149409 | 1 | NR | <5 | <5 | 1.23 | <10 | 6.61 | 8.46 |
| 13828 | 6 | NR | <5 | <5 | 1.75 | 10 | 5.13 | 8.74 |
| 13829 | 5 | NR | <5 | <5 | 8.33 | <10 | 5.09 | 5.84 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 5 of 49

| | Au1 ppb | Au2 ppb | Pt ppb | Pd ppb | Ca % | Cr ppm | Fe % | K % |
|-----------------|------------|------------|-----------|-----------|---------|-----------|---------|--------|
| Detection Limit | 1 | 1 | 5 | 5 | 0.01 | 10 | 0.01 | 0.01 |
| 13830 | 3 | NR | <5 | <5 | 16.6 | <10 | 4.58 | 2.17 |
| 13831 | 4 | NR | <5 | <5 | 17.2 | <10 | 5.04 | 1.18 |
| 13834 | 31 | NR | <5 | <5 | 0.12 | 50 | 3.76 | 10.2 |
| 13835 | 32 | NR | <5 | 5 | 0.09 | 40 | 2.68 | 10.4 |
| 13836 | 30 | NR | <5 | <5 | 0.17 | 30 | 2.36 | 11.2 |
| 13837 | 8 | NR | <5 | <5 | 0.21 | 30 | 4.00 | 9.21 |
| 13838 | 19 | NR | <5 | <5 | 0.31 | 30 | 3.51 | 9.33 |
| 13838 Rpt | 19 | NR | <5 | <5 | 0.30 | 30 | 3.51 | 9.50 |
| 13839 | 28 | NR | <5 | <5 | 0.75 | 30 | 3.32 | 8.88 |
| 13840 | 14 | NR | <5 | <5 | 0.74 | 30 | 3.26 | 8.92 |
| 13841 | 24 | NR | <5 | <5 | 0.76 | 40 | 2.78 | 4.78 |
| 13842 | 10 | NR | <5 | <5 | 0.74 | 20 | 2.06 | 8.95 |
| 13843 | 7 | NR | <5 | <5 | 0.70 | 20 | 2.09 | 10.6 |
| Std Nominal | 860 | 860 | 910 | 690 | 0.20 | 2600 | 11.9 | 0.01 |
| Determined | 862 | NR | 940 | 705 | 0.20 | 1890 | 12.0 | 0.03 |
| 13844 | 4 | NR | <5 | <5 | 0.72 | 30 | 2.21 | 10.7 |
| 13845 | 16 | NR | <5 | <5 | 0.77 | 20 | 2.11 | 11.2 |
| 13845 Rpt | 17 | NR | <5 | <5 | 0.75 | 20 | 2.07 | 10.2 |
| 13846 | 14 | NR | <5 | <5 | 0.85 | 20 | 1.79 | 8.63 |
| 13847 | 4 | NR | <5 | <5 | 1.00 | 20 | 1.51 | 8.77 |
| 13848 | 5 | NR | <5 | <5 | 1.05 | 20 | 1.26 | 3.92 |
| 13849 | 27 | NR | <5 | 5 | 1.24 | 40 | 1.82 | 3.10 |
| 13850 | 5 | NR | <5 | <5 | 0.19 | 20 | 1.26 | 4.20 |
| 13851 | 3 | NR | <5 | <5 | 0.24 | 30 | 2.99 | 9.38 |
| 13852 | 8 | NR | <5 | <5 | 0.16 | 20 | 1.88 | 9.13 |
| 13853 | 4 | NR | <5 | <5 | 0.16 | 20 | 1.55 | 8.94 |
| 13854 | <1 | NR | <5 | <5 | 0.11 | 10 | 0.93 | 2.00 |
| 13855 | 1 | NR | <5 | <5 | 0.10 | 20 | 0.83 | 3.77 |
| 13856 | 2 | NR | <5 | <5 | 0.07 | 10 | 0.83 | 1.51 |
| 13857 | 12 | NR | <5 | <5 | 0.16 | 30 | 2.36 | 3.39 |
| 13858 | 3 | NR | <5 | <5 | 0.11 | 30 | 2.49 | 2.58 |
| 13859 | 4 | NR | <5 | <5 | 0.12 | 30 | 3.19 | 6.60 |
| 13859 Rpt | 6 | NR | <5 | <5 | 0.11 | 30 | 3.13 | 7.11 |
| 13860 | IS | NR | IS | IS | 1.67 | 6760 | 24.8 | 0.10 |
| 13861 | 1 | NR | <5 | <5 | 0.16 | 30 | 2.07 | 7.46 |
| 13862 | 2 | NR | <5 | <5 | 0.20 | 40 | 2.17 | 8.37 |
| 13862 Rpt | 3 | NR | <5 | <5 | 0.20 | 40 | 2.20 | 7.89 |
| 13863 | 2 | NR | <5 | <5 | 0.18 | 40 | 2.28 | 9.44 |
| 13864 | 1 | NR | <5 | <5 | 0.18 | 40 | 2.53 | 6.30 |
| 13865 | <1 | NR | <5 | <5 | 0.16 | 40 | 3.01 | 3.67 |
| 13866 | 1 | NR | <5 | <5 | 0.15 | 30 | 2.88 | 3.18 |
| 13867 | 2 | NR | <5 | <5 | 0.16 | 40 | 3.00 | 8.01 |
| 13868 | <1 | NR | <5 | <5 | 0.46 | 40 | 5.06 | 5.95 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 6 of 49

| | Au1 ppb | Au2 ppb | Pt ppb | Pd ppb | Ca % | Cr ppm | Fe % | K % |
|-----------------|------------|------------|-----------|-----------|---------|-----------|---------|--------|
| Detection Limit | 1 | 1 | 5 | 5 | 0.01 | 10 | 0.01 | 0.01 |
| 13869 | <1 | NR | <5 | <5 | 0.49 | 40 | 5.55 | 5.93 |
| 13870 | 3 | NR | <5 | <5 | 0.22 | 40 | 5.29 | 5.28 |
| 13871 | 6 | NR | <5 | <5 | 0.22 | 40 | 4.28 | 8.95 |
| 13872 | 4 | NR | <5 | <5 | 3.95 | 40 | 4.03 | 2.58 |
| 13873 | <1 | NR | <5 | <5 | 3.78 | 20 | 2.55 | 8.06 |
| 149410 | <1 | NR | <5 | <5 | 1.71 | 10 | 3.10 | 8.33 |
| Std Nominal | 2.42M | 2.42M | | | 14.0 | 180 | 7.52 | 0.02 |
| Determined | 2.38M | NR | <5 | <5 | 13.9 | 100 | 7.43 | 0.03 |
| 149411 | 2 | NR | <5 | <5 | 1.03 | 20 | 4.21 | 7.53 |
| 13883 | <1 | NR | <5 | <5 | 2.43 | 20 | 4.04 | 6.18 |
| 13883 Rpt | <1 | NR | <5 | <5 | 2.54 | 20 | 4.18 | 6.57 |
| 13884 | <1 | NR | <5 | <5 | 2.54 | 20 | 4.69 | 6.55 |
| 13885 | <1 | NR | <5 | <5 | 1.00 | 20 | 2.97 | 7.54 |
| 13886 | <1 | NR | <5 | <5 | 0.90 | 20 | 3.86 | 7.45 |
| 13887 | <1 | NR | <5 | <5 | 4.64 | 20 | 4.38 | 5.88 |
| 13888 | 1 | NR | <5 | <5 | 7.06 | 10 | 3.62 | 2.16 |
| 149412 | 10 | NR | <5 | <5 | 4.75 | 30 | 3.79 | 5.23 |
| 13893 | 12 | NR | <5 | <5 | 3.58 | 50 | 4.85 | 5.41 |
| 13894 | <1 | NR | <5 | <5 | 3.66 | 30 | 4.73 | 3.74 |
| Std Nominal | 4.94M | 4.94M | | | 0.10 | 1.70% | 47.5 | <0.01 |
| Determined | 4.97M | NR | <5 | <5 | 0.11 | 1.40% | 46.9 | <0.01 |
| 13895 | 1 | NR | <5 | <5 | 4.83 | 40 | 4.72 | 5.36 |
| 13896 | 1 | NR | <5 | <5 | 4.34 | 40 | 4.94 | 4.81 |
| 13897 | <1 | NR | <5 | <5 | 4.14 | 30 | 4.51 | 5.87 |
| 13898 | <1 | NR | <5 | <5 | 4.36 | 40 | 4.31 | 5.05 |
| 13899 | <1 | NR | <5 | <5 | 4.72 | 30 | 4.42 | 4.47 |
| 13899 Rpt | <1 | NR | <5 | <5 | 4.86 | 30 | 4.52 | 3.85 |
| 13900 | IS | NR | IS | IS | 0.07 | 40 | 8.66 | 0.16 |
| 13901 | <1 | NR | <5 | <5 | 4.36 | 40 | 4.88 | 5.80 |
| 13902 | <1 | NR | <5 | <5 | 4.16 | 30 | 4.26 | 2.71 |
| 13903 | 1 | NR | <5 | <5 | 4.47 | 30 | 4.31 | 5.56 |
| 13904 | 1 | NR | <5 | <5 | 4.29 | 20 | 3.67 | 4.79 |
| 13905 | 2 | NR | <5 | <5 | 13.7 | 10 | 3.57 | 2.90 |
| 13906 | 1 | NR | <5 | <5 | 14.1 | 10 | 4.13 | 3.25 |
| 13906 Rpt | 1 | NR | <5 | <5 | 13.8 | 20 | 4.00 | 3.07 |
| 13907 | <1 | NR | <5 | <5 | 7.67 | 40 | 4.48 | 3.44 |
| 13908 | <1 | NR | <5 | <5 | 3.99 | 40 | 3.60 | 2.40 |
| 13909 | <1 | NR | <5 | <5 | 4.27 | 40 | 4.43 | 2.09 |
| 13910 | <1 | NR | <5 | <5 | 3.60 | 40 | 4.30 | 2.30 |
| 13911 | 1 | NR | 5 | <5 | 3.45 | 20 | 2.11 | 1.84 |
| 13912 | 1 | NR | <5 | <5 | 5.63 | 10 | 3.86 | 1.53 |
| 13913 | <1 | NR | <5 | <5 | 7.09 | 10 | 4.42 | 5.81 |
| 149413 | <1 | NR | <5 | <5 | 4.83 | 10 | 7.52 | 3.21 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 7 of 49

| | Au1 ppb | Au2 ppb | Pt ppb | Pd ppb | Ca % | Cr ppm | Fe % | K % |
|-----------------|------------|------------|-----------|-----------|---------|-----------|---------|--------|
| Detection Limit | 1 | 1 | 5 | 5 | 0.01 | 10 | 0.01 | 0.01 |
| 149414 | 3 | NR | <5 | <5 | 1.60 | 20 | 10.8 | 5.13 |
| 149415 | 2 | NR | <5 | <5 | 3.32 | 40 | 9.68 | 2.10 |
| 149415 Rpt | 3 | NR | <5 | <5 | 3.28 | 20 | 9.68 | 1.95 |
| 149416 | 1 | NR | <5 | <5 | 3.40 | 20 | 8.72 | 3.73 |
| 149417 | <1 | NR | <5 | <5 | 2.07 | 30 | 9.50 | 5.21 |
| 149418 | <1 | NR | <5 | <5 | 2.15 | 10 | 9.59 | 4.27 |
| 13938 | 1 | NR | <5 | <5 | 0.07 | 70 | 15.5 | 0.76 |
| 13939 | 1 | NR | <5 | <5 | 0.04 | 50 | 10.0 | 1.62 |
| 13940 | 3 | NR | <5 | <5 | 0.03 | 50 | 10.8 | 1.59 |
| 13941 | 5 | NR | <5 | <5 | 0.03 | 50 | 1.74 | 8.08 |
| 13942 | 8 | NR | <5 | <5 | 0.03 | 40 | 2.25 | 9.22 |
| 13943 | 1 | NR | <5 | <5 | 0.70 | 30 | 1.00 | 3.25 |
| 13944 | 5 | NR | <5 | <5 | 0.36 | 40 | 2.82 | 2.78 |
| 13945 | 7 | NR | <5 | <5 | 0.09 | 40 | 2.32 | 8.00 |
| 13945 Rpt | 5 | NR | <5 | <5 | 0.09 | 40 | 2.35 | 8.75 |
| 13946 | 3 | NR | <5 | <5 | 0.14 | 50 | 1.56 | 4.72 |
| 13947 | 2 | NR | <5 | <5 | 0.26 | 40 | 1.15 | 8.27 |
| 13948 | 2 | NR | <5 | <5 | 0.36 | 30 | 1.31 | 7.69 |
| 13949 | <1 | NR | <5 | <5 | 0.42 | 40 | 1.78 | 9.08 |
| Std Nominal | 52 | 52 | 45 | 45 | 1.53 | 1670 | 9.20 | 0.09 |
| Determined | 51 | 54 | 45 | 45 | 1.51 | 1230 | 9.19 | 0.08 |
| 13950 | 1 | NR | <5 | <5 | 0.80 | 50 | 1.37 | 7.57 |
| 13951 | <1 | NR | <5 | <5 | 0.50 | 50 | 1.28 | 6.86 |
| 13952 | 1 | NR | <5 | <5 | 0.28 | 40 | 1.48 | 6.66 |
| 13953 | 1 | NR | <5 | <5 | 0.26 | 40 | 1.53 | 5.20 |
| 13954 | 4 | NR | <5 | <5 | 0.25 | 50 | 1.83 | 5.32 |
| 13955 | 4 | NR | <5 | <5 | 0.24 | 50 | 2.30 | 7.96 |
| 13956 | 1 | NR | <5 | <5 | 0.24 | 50 | 1.84 | 5.11 |
| 13957 | <1 | NR | <5 | <5 | 0.35 | 40 | 1.64 | 8.34 |
| 13958 | <1 | NR | <5 | <5 | 0.26 | 40 | 1.55 | 9.15 |
| 13959 | 2 | NR | <5 | <5 | 0.36 | 40 | 1.53 | 8.35 |
| 13959 Rpt | 1 | NR | <5 | <5 | 0.35 | 50 | 1.53 | 9.04 |
| 13960 | IS | NR | IS | IS | 1.70 | 6660 | 24.6 | 0.11 |
| 13961 | 6 | NR | <5 | <5 | 0.22 | 40 | 1.51 | 4.61 |
| 13962 | 1 | NR | <5 | <5 | 0.24 | 50 | 1.60 | 7.94 |
| 13963 | 2 | NR | <5 | <5 | 0.23 | 60 | 1.73 | 8.92 |
| 13964 | 2 | NR | <5 | <5 | 0.58 | 50 | 1.47 | 4.85 |
| Std Nominal | 1.37M | 1.37M | | | 8.22 | 30 | 6.27 | 0.21 |
| Determined | 1.41M | NR | <5 | <5 | 8.39 | 20 | 6.35 | 0.20 |
| 13965 | 1 | NR | <5 | <5 | 0.31 | 30 | 1.35 | 9.31 |
| 13966 | 3 | NR | <5 | <5 | 0.32 | 30 | 1.48 | 6.08 |
| 13967 | 1 | NR | <5 | <5 | 0.24 | 40 | 1.82 | 6.10 |
| 13968 | 4 | NR | <5 | <5 | 0.26 | 50 | 2.47 | 9.16 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 8 of 49

| | Au1 ppb | Au2 ppb | Pt ppb | Pd ppb | Ca % | Cr ppm | Fe % | K % |
|-----------------|------------|------------|-----------|-----------|---------|-----------|---------|--------|
| Detection Limit | 1 | 1 | 5 | 5 | 0.01 | 10 | 0.01 | 0.01 |
| 13969 | 2 | NR | <5 | <5 | 0.33 | 40 | 1.48 | 9.19 |
| 13970 | 3 | NR | <5 | <5 | 0.28 | 40 | 1.49 | 9.78 |
| 13971 | 2 | NR | <5 | <5 | 0.27 | 40 | 1.39 | 6.42 |
| 13972 | 7 | NR | <5 | <5 | 0.39 | 40 | 1.97 | 3.39 |
| 13973 | 3 | NR | <5 | <5 | 0.37 | 20 | 2.31 | 2.41 |
| 13974 | 5 | NR | <5 | <5 | 1.12 | 20 | 2.56 | 4.25 |
| 13974 Rpt | 3 | NR | <5 | <5 | 1.11 | 20 | 2.53 | 4.40 |
| 13975 | 5 | NR | <5 | <5 | 0.69 | 20 | 1.65 | 10.7 |
| 13976 | 60 | 71 | 10 | 10 | 0.33 | 30 | 2.81 | 10.3 |
| 13977 | 41 | NR | 5 | 10 | 1.22 | 50 | 2.91 | 9.78 |
| 13978 | 7 | NR | <5 | <5 | 0.15 | 20 | 2.10 | 7.26 |
| Std Nominal | 860 | 860 | 910 | 690 | 5.91 | 230 | 9.63 | 0.60 |
| Determined | 851 | NR | 875 | 670 | 5.96 | 180 | 9.70 | 0.61 |
| 13979 | 4 | NR | 5 | <5 | 0.21 | 30 | 2.45 | 10.2 |
| 13980 | IS | NR | IS | IS | 0.07 | 40 | 8.83 | 0.16 |
| 13980 Rpt | NR | NR | NR | NR | 0.06 | 40 | 8.88 | 0.15 |
| 13981 | 2 | NR | 5 | 5 | 0.28 | 30 | 2.59 | 11.0 |
| 13982 | 3 | NR | <5 | <5 | 0.24 | 50 | 7.82 | 7.91 |
| 13983 | 2 | NR | <5 | <5 | 8.40 | 30 | 5.36 | 5.34 |
| 13984 | 1 | NR | <5 | <5 | 0.36 | 50 | 6.83 | 6.89 |
| 13985 | 1 | NR | <5 | <5 | 0.47 | 50 | 7.02 | 5.29 |
| 13986 | 1 | NR | <5 | <5 | 4.38 | 30 | 4.48 | 4.96 |
| 13987 | 2 | NR | 5 | <5 | 2.30 | 40 | 4.04 | 4.57 |
| 13988 | 3 | NR | <5 | <5 | 0.32 | 50 | 4.35 | 7.13 |
| 13989 | 2 | NR | <5 | <5 | 5.41 | 40 | 5.89 | 5.13 |
| 13990 | 1 | NR | <5 | <5 | 5.66 | 40 | 6.12 | 5.10 |
| 13990 Rpt | <1 | NR | <5 | <5 | 5.63 | 40 | 6.13 | 5.65 |
| 13991 | 1 | NR | <5 | <5 | 5.63 | 30 | 5.89 | 6.21 |
| 13992 | <1 | NR | <5 | <5 | 4.70 | 30 | 5.54 | 2.50 |
| 13993 | 1 | NR | <5 | <5 | 5.01 | 40 | 6.09 | 3.69 |
| 13994 | <1 | NR | <5 | <5 | 3.92 | 30 | 5.00 | 4.97 |
| 13995 | <1 | NR | <5 | <5 | 3.14 | 30 | 5.37 | 5.06 |
| 13996 | 1 | NR | <5 | <5 | 3.63 | 30 | 4.22 | 4.76 |
| 13997 | <1 | NR | <5 | <5 | 3.18 | 30 | 5.02 | 4.08 |
| 149419 | <1 | NR | <5 | <5 | 3.29 | 30 | 3.45 | 4.67 |
| 149420 | IS | NR | IS | IS | 1.69 | 6910 | 24.8 | 0.11 |
| 149421 | 1 | NR | <5 | <5 | 3.48 | 40 | 3.49 | 5.02 |
| Std Nominal | 2.42M | 2.42M | | | 0.58 | 10 | 1.47 | 4.16 |
| Determined | 2.32M | NR | <5 | <5 | 0.57 | 10 | 1.45 | 4.06 |
| 149422 | 3 | NR | <5 | <5 | 5.17 | 20 | 4.04 | 5.14 |
| 14011 | 2 | NR | <5 | <5 | 4.57 | 20 | 3.64 | 4.20 |
| 14012 | 1 | NR | <5 | <5 | 3.82 | 20 | 3.96 | 4.45 |
| 14013 | <1 | NR | <5 | <5 | 3.32 | 30 | 4.28 | 3.15 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 9 of 49

| | Au1 ppb | Au2 ppb | Pt ppb | Pd ppb | Ca % | Cr ppm | Fe % | K % |
|-----------------|------------|------------|-----------|-----------|---------|-----------|---------|--------|
| Detection Limit | 1 | 1 | 5 | 5 | 0.01 | 10 | 0.01 | 0.01 |
| 14014 | <1 | NR | <5 | <5 | 3.82 | 30 | 3.85 | 5.90 |
| 14014 Rpt | <1 | NR | <5 | <5 | 3.81 | 30 | 3.79 | 5.77 |
| 14015 | <1 | NR | <5 | <5 | 3.88 | 30 | 3.74 | 5.17 |
| 14016 | 2 | NR | <5 | <5 | 3.91 | 30 | 4.76 | 6.10 |
| 14016 Rpt | 2 | NR | <5 | <5 | 3.92 | 40 | 4.89 | 5.42 |
| 14017 | 1 | NR | <5 | <5 | 3.45 | 40 | 4.56 | 4.84 |
| 14018 | 1 | NR | <5 | <5 | 3.35 | 20 | 3.10 | 3.40 |
| 14019 | <1 | NR | <5 | <5 | 5.27 | <10 | 3.07 | 1.53 |
| 14020 | <1 | NR | <5 | <5 | 5.26 | 10 | 3.21 | 1.49 |
| 14021 | <1 | NR | <5 | <5 | 1.86 | 10 | 1.88 | 1.74 |
| 149423 | 2 | NR | <5 | <5 | 5.63 | 10 | 5.37 | 5.65 |
| 149424 | 2 | NR | <5 | <5 | 3.41 | 20 | 4.00 | 4.25 |
| 149425 | 1 | NR | <5 | <5 | 3.73 | 20 | 5.83 | 4.65 |
| 149426 | 1 | NR | <5 | <5 | 4.15 | 20 | 4.30 | 4.16 |
| 149427 | 2 | NR | <5 | <5 | 3.32 | 30 | 5.28 | 5.38 |
| 14044 | 1 | NR | 5 | <5 | 0.05 | 90 | 18.1 | 0.74 |
| 14045 | <1 | NR | <5 | <5 | 0.03 | 70 | 14.8 | 1.07 |
| 14046 | 1 | NR | <5 | <5 | 0.07 | 50 | 11.0 | 3.94 |
| 14047 | 2 | NR | <5 | <5 | 0.29 | 50 | 6.66 | 7.02 |
| 14048 | <1 | NR | <5 | <5 | 0.39 | 40 | 4.33 | 8.79 |
| 14049 | 3 | NR | <5 | <5 | 0.46 | 40 | 5.32 | 7.94 |
| 14049 Rpt | 2 | NR | <5 | <5 | 0.46 | 50 | 5.31 | 7.94 |
| 14050 | 5 | NR | <5 | <5 | 0.31 | 30 | 1.69 | 7.27 |
| 14051 | 12 | NR | <5 | <5 | 0.61 | 40 | 2.60 | 9.89 |
| 14052 | 8 | NR | <5 | <5 | 2.03 | 30 | 1.50 | 10.1 |
| 14053 | 5 | NR | <5 | <5 | 1.38 | 30 | 1.14 | 11.1 |
| Std Nominal | 4.94M | 4.94M | | | 2.48 | 170 | 8.65 | 2.35 |
| Determined | 4.98M | NR | <5 | <5 | 2.45 | 160 | 8.53 | 2.37 |
| 14054 | 3 | NR | <5 | <5 | 1.08 | 30 | 1.17 | 10.9 |
| 14055 | 3 | NR | <5 | <5 | 1.16 | 40 | 1.59 | 10.7 |
| 14056 | 1 | NR | <5 | <5 | 0.85 | 30 | 0.91 | 9.68 |
| 14057 | 1 | NR | <5 | <5 | 0.86 | 30 | 0.73 | 11.2 |
| 14058 | <1 | NR | <5 | <5 | 0.80 | 20 | 1.05 | 10.5 |
| 14059 | 1 | NR | <5 | <5 | 1.01 | 30 | 1.28 | 10.9 |
| 14061 | 3 | NR | <5 | <5 | 0.71 | 60 | 1.93 | 9.49 |
| 14062 | 6 | NR | <5 | <5 | 0.69 | 30 | 1.46 | 10.9 |
| 14062 Rpt | 7 | NR | <5 | <5 | 0.70 | 30 | 1.52 | 10.3 |
| 14063 | 5 | NR | 5 | <5 | 0.35 | 50 | 2.86 | 9.27 |
| 14064 | 3 | NR | <5 | <5 | 0.71 | 30 | 1.23 | 11.2 |
| 14065 | 6 | NR | 5 | <5 | 0.66 | 40 | 1.25 | 9.68 |
| 14066 | 4 | NR | <5 | <5 | 0.85 | 30 | 1.17 | 10.3 |
| 14067 | 2 | NR | <5 | <5 | 0.44 | 30 | 1.39 | 10.1 |
| 14068 | 7 | NR | <5 | <5 | 0.28 | 60 | 2.77 | 9.23 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 10 of 49

| | Au1 ppb | Au2 ppb | Pt ppb | Pd ppb | Ca % | Cr ppm | Fe % | K % |
|-----------------|------------|------------|-----------|-----------|---------|-----------|---------|--------|
| Detection Limit | 1 | 1 | 5 | 5 | 0.01 | 10 | 0.01 | 0.01 |
| 14069 | 6 | NR | 5 | 5 | 0.19 | 60 | 4.96 | 9.28 |
| 14070 | 5 | NR | <5 | <5 | 0.32 | 60 | 4.19 | 9.13 |
| 14071 | 3 | NR | <5 | <5 | 0.31 | 60 | 2.97 | 10.2 |
| 14072 | 20 | NR | 5 | <5 | 0.34 | 30 | 1.46 | 10.9 |
| 14073 | 19 | NR | 25 | 20 | 0.25 | 40 | 1.45 | 9.89 |
| 14074 | 106 | NR | 35 | 30 | 0.29 | 40 | 1.36 | 10.2 |
| 14074 Rpt | 107 | NR | 35 | 30 | 0.30 | 40 | 1.39 | 10.6 |
| 14075 | 22 | NR | 5 | 20 | 0.17 | 40 | 3.31 | 10.1 |
| 14076 | 19 | NR | 15 | 10 | 0.26 | 30 | 2.38 | 9.55 |
| 14077 | 4 | NR | <5 | <5 | 0.16 | 30 | 2.95 | 9.54 |
| 14078 | 19 | NR | 5 | 10 | 0.28 | 50 | 4.48 | 9.68 |
| 14079 | 24 | NR | <5 | 5 | 0.21 | 20 | 3.36 | 9.59 |
| 14080 | IS | NR | IS | IS | 1.67 | 6720 | 24.8 | 0.11 |
| 14084 | 10 | NR | <5 | <5 | 0.22 | 30 | 8.94 | 7.24 |
| 14086 | 14 | NR | <5 | 5 | 0.28 | 30 | 14.5 | 6.12 |
| 149428 | 4 | NR | <5 | <5 | 3.80 | 40 | 5.58 | 5.90 |
| 149428 Rpt | 5 | NR | <5 | <5 | 3.84 | 40 | 5.55 | 5.82 |
| 149429 | 1 | NR | <5 | <5 | 4.94 | 30 | 5.00 | 5.42 |
| 149430 | <1 | NR | <5 | <5 | 6.34 | 30 | 6.20 | 2.59 |
| 149431 | 1 | NR | <5 | <5 | 6.97 | 30 | 4.49 | 6.13 |
| 149432 | 2 | NR | <5 | <5 | 5.36 | 20 | 4.48 | 3.41 |
| 149433 | 1 | NR | <5 | <5 | 4.85 | 20 | 4.12 | 5.55 |
| 149434 | 2 | NR | <5 | <5 | 5.93 | 20 | 3.85 | 5.29 |
| Std Nominal | 52 | 52 | 45 | 45 | 0.54 | 90 | 0.18 | <0.01 |
| Determined | 52 | NR | 45 | 45 | 0.56 | 40 | 0.19 | <0.01 |
| 149435 | <1 | NR | <5 | <5 | 5.28 | 30 | 5.00 | 5.29 |
| 149436 | 1 | NR | <5 | <5 | 2.61 | 50 | 5.72 | 7.72 |
| 149437 | 2 | NR | <5 | <5 | 0.93 | 20 | 4.69 | 8.07 |
| 149438 | 4 | NR | <5 | <5 | 1.26 | 20 | 6.88 | 7.04 |
| 149439 | 1 | NR | <5 | <5 | 4.69 | 20 | 6.98 | 4.43 |
| 149440 | 1 | NR | <5 | <5 | 4.45 | 20 | 6.98 | 6.06 |
| Std Nominal | 1.37M | 1.37M | | | 0.20 | 2600 | 11.9 | 0.01 |
| Determined | 1.36M | NR | <5 | <5 | 0.21 | 2080 | 12.0 | 0.02 |
| 149441 | 4 | NR | <5 | <5 | 3.65 | 30 | 4.36 | 5.11 |
| 149442 | 3 | NR | <5 | <5 | 4.24 | 20 | 8.38 | 6.24 |
| 149443 | 4 | NR | <5 | <5 | 5.21 | 30 | 6.09 | 5.61 |
| 14148 | 2 | NR | <5 | <5 | 0.72 | 40 | 3.63 | 9.89 |
| 14149 | 2 | NR | <5 | <5 | 0.67 | 40 | 2.71 | 10.2 |
| 14150 | 3 | NR | 5 | <5 | 0.61 | 40 | 2.70 | 9.56 |
| 14150 Rpt | 3 | NR | <5 | <5 | 0.61 | 40 | 2.71 | 10.6 |
| 14151 | 1 | NR | <5 | <5 | 0.68 | 30 | 1.92 | 11.3 |
| 14152 | 4 | NR | <5 | <5 | 0.36 | 40 | 3.58 | 9.50 |
| 14153 | 10 | NR | <5 | <5 | 0.51 | 40 | 3.81 | 8.97 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 11 of 49

| | Au1 ppb | Au2 ppb | Pt ppb | Pd ppb | Ca % | Cr ppm | Fe % | K % |
|-----------------|------------|------------|-----------|-----------|---------|-----------|---------|--------|
| Detection Limit | 1 | 1 | 5 | 5 | 0.01 | 10 | 0.01 | 0.01 |
| 14154 | 18 | NR | 5 | <5 | 0.72 | 40 | 1.57 | 10.5 |
| 14155 | 12 | NR | <5 | <5 | 0.82 | 40 | 1.74 | 11.4 |
| 14156 | 3 | NR | <5 | <5 | 0.22 | 30 | 1.45 | 6.94 |
| 14156 Rpt | 3 | NR | <5 | <5 | 0.22 | 30 | 1.46 | 6.97 |
| 14157 | 1 | NR | <5 | <5 | 0.08 | 10 | 0.85 | 2.90 |
| 14158 | 1 | NR | <5 | <5 | 0.08 | 20 | 1.33 | 4.53 |
| 14159 | 8 | NR | <5 | <5 | 0.10 | 40 | 2.12 | 7.57 |
| 14160 | 7 | NR | <5 | <5 | 0.09 | 40 | 2.07 | 7.57 |
| 14161 | 1 | NR | <5 | <5 | 0.09 | 50 | 1.93 | 7.60 |
| 13516 | 2 | NR | <5 | <5 | 0.05 | 130 | 26.4 | 0.58 |
| 13517 | 2 | NR | <5 | <5 | 0.10 | 80 | 14.8 | 3.22 |
| 13518 | 1 | NR | <5 | <5 | 0.46 | 40 | 4.62 | 9.28 |
| 13518 Rpt | <1 | NR | <5 | <5 | 0.45 | 40 | 4.54 | 9.20 |
| 13519 | 1 | NR | <5 | <5 | 0.62 | 40 | 5.44 | 7.72 |
| 13520 | IS | NR | IS | IS | 0.06 | 20 | 8.91 | 0.16 |
| 13521 | 3 | NR | <5 | <5 | 0.64 | 30 | 5.48 | 7.65 |
| 13522 | 2 | NR | <5 | <5 | 0.51 | 30 | 1.77 | 11.2 |
| 13523 | 4 | NR | 5 | <5 | 0.30 | 40 | 3.04 | 9.37 |
| 13524 | 13 | NR | <5 | <5 | 0.68 | 30 | 1.85 | 9.76 |
| 13525 | 32 | NR | 5 | <5 | 0.66 | 40 | 2.05 | 11.0 |
| 13526 | 8 | NR | <5 | <5 | 0.15 | 10 | 0.82 | 2.95 |
| 13527 | 3 | NR | <5 | <5 | 0.08 | 10 | 0.71 | 1.99 |
| 13527 Rpt | 4 | NR | <5 | <5 | 0.08 | 10 | 0.72 | 2.01 |
| 13528 | 1 | NR | <5 | <5 | 0.12 | 20 | 1.06 | 4.14 |
| 13529 | 3 | NR | <5 | <5 | 0.08 | 10 | 1.38 | 3.28 |
| 13530 | 5 | NR | <5 | <5 | 0.15 | 40 | 2.55 | 8.65 |
| 13531 | 2 | NR | <5 | <5 | 0.08 | 20 | 1.70 | 4.58 |
| 13532 | 2 | NR | <5 | <5 | 0.15 | 20 | 1.28 | 5.12 |
| 13533 | 1 | NR | <5 | <5 | 0.10 | 10 | 1.17 | 4.01 |
| 13534 | 2 | NR | <5 | <5 | 0.15 | 20 | 2.03 | 5.71 |
| Std Nominal | 860 | 860 | 910 | 690 | 14.0 | 180 | 7.52 | 0.02 |
| Determined | 839 | NR | 890 | 670 | 14.1 | 100 | 7.47 | 0.03 |
| 13535 | 3 | NR | 5 | <5 | 0.74 | 40 | 4.12 | 6.81 |
| 13536 | 3 | NR | <5 | <5 | 4.26 | 30 | 2.98 | 5.92 |
| 13588 | 4 | NR | <5 | <5 | 3.83 | 20 | 6.47 | 7.14 |
| 13588 Rpt | 5 | NR | <5 | <5 | 3.92 | 20 | 6.55 | 7.31 |
| 13589 | 2 | NR | <5 | <5 | 1.61 | 20 | 4.29 | 9.58 |
| 13590 | 7 | NR | <5 | <5 | 2.25 | 20 | 6.22 | 8.08 |
| 13591 | 13 | NR | <5 | <5 | 12.5 | 10 | 5.81 | 3.00 |
| 13592 | 1 | NR | <5 | <5 | 7.45 | 20 | 6.77 | 4.89 |
| 13593 | 1 | NR | <5 | <5 | 5.43 | 10 | 3.81 | 2.38 |
| 13593 Rpt | 2 | NR | <5 | <5 | 5.39 | 20 | 3.76 | 2.34 |
| 13594 | 2 | NR | <5 | <5 | 0.17 | 20 | 2.42 | 2.12 |



Reference: u282154 Order Number: NC_003 Page 12 of 49

| | Au1 ppb | Au2 ppb | Pt ppb | Pd ppb | Ca % | Cr ppm | Fe % | K % |
|-----------------|------------|------------|-----------|-----------|---------|-----------|---------|--------|
| Detection Limit | 1 | 1 | 5 | 5 | 0.01 | 10 | 0.01 | 0.01 |
| 13595 | 3 | NR | <5 | <5 | 5.24 | 20 | 5.81 | 6.21 |
| 13596 | 3 | NR | <5 | <5 | 4.08 | 40 | 7.58 | 5.99 |
| 13597 | 17 | NR | <5 | <5 | 3.94 | 30 | 5.96 | 7.11 |
| Std Nominal | 2.42M | 2.42M | | | 0.10 | 1.70% | 47.5 | <0.01 |
| Determined | 2.36M | NR | <5 | <5 | 0.10 | 1.41% | 47.2 | 0.02 |
| 13598 | 8 | NR | <5 | <5 | 4.53 | 20 | 7.30 | 5.86 |
| 13599 | 4 | NR | <5 | <5 | 5.06 | <10 | 7.67 | 5.97 |
| 13600 | IS | NR | IS | IS | 1.69 | 6580 | 24.9 | 0.11 |
| 14060 | IS | NR | IS | IS | 0.07 | 30 | 9.12 | 0.16 |
| 14060 Rpt | NR | NR | NR | NR | 0.07 | 30 | 9.08 | 0.15 |
| Std Nominal | 4.94M | 4.94M | | | 1.53 | 1670 | 9.20 | 0.09 |
| Determined | 4.99M | NR | <5 | <5 | 1.49 | 1180 | 9.17 | 0.08 |
| ***** | | | | | | | | |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 13 of 49

| | Mg % | Mn ppm | Na % | P ppm | S ppm | V ppm | Ag ppm | As ppm |
|-----------------|---------|-----------|---------|----------|----------|----------|-----------|-----------|
| Detection Limit | 0.01 | 2 | 0.01 | 50 | 50 | 5 | 0.5 | 1 |
| 149389 | 0.88 | 1810 | 0.03 | 1700 | 150 | 335 | <0.5 | 99 |
| 149390 | 0.25 | 948 | 0.05 | 3450 | 100 | 95 | <0.5 | 29 |
| 13630 | 0.49 | 510 | 0.06 | 2700 | 100 | 70 | <0.5 | 30 |
| 13631 | 0.19 | 140 | 0.03 | 250 | 150 | 20 | <0.5 | 10 |
| 13631 Rpt | 0.18 | 134 | 0.03 | 250 | 150 | 20 | <0.5 | 11 |
| 13632 | 0.24 | 192 | 0.03 | 300 | 100 | 25 | <0.5 | 12 |
| 13632 Rpt | 0.24 | 194 | 0.03 | 300 | 100 | 25 | <0.5 | 12 |
| 13633 | 0.40 | 80 | 0.04 | 350 | 100 | 30 | <0.5 | 12 |
| 13634 | 0.50 | 74 | 0.04 | 350 | 100 | 30 | <0.5 | 23 |
| 13635 | 1.66 | 82 | 0.07 | 650 | 50 | 105 | <0.5 | 54 |
| 13636 | 0.50 | 60 | 0.04 | 350 | 100 | 25 | <0.5 | 18 |
| 13637 | 0.20 | 68 | 0.03 | 250 | 150 | 15 | <0.5 | 25 |
| 13638 | 0.09 | 62 | 0.03 | 200 | 100 | 5 | <0.5 | 11 |
| 13639 | 0.55 | 78 | 0.07 | 500 | 2800 | 25 | <0.5 | 42 |
| 13640 | 0.59 | 66 | 0.07 | 500 | 3200 | 25 | <0.5 | 44 |
| 13641 | 1.44 | 76 | 0.12 | 650 | 2250 | 60 | <0.5 | 35 |
| 13642 | 1.68 | 1150 | 0.07 | 550 | 100 | 85 | <0.5 | 18 |
| 149391 | 2.77 | 1280 | 0.06 | 550 | 200 | 65 | <0.5 | 4 |
| Std Nominal | 1.86 | 5810 | <0.01 | 50 | 1900 | 125 | <0.5 | 2 |
| Determined | 1.83 | 5810 | 0.02 | 100 | 1950 | 130 | <0.5 | 3 |
| 149392 | 2.57 | 1230 | 0.06 | 500 | 600 | 60 | <0.5 | 5 |
| 13651 | 2.51 | 1510 | 0.07 | 550 | 200 | 65 | <0.5 | 4 |
| 13652 | 2.70 | 1290 | 0.06 | 600 | 250 | 75 | <0.5 | 4 |
| 13653 | 2.68 | 1730 | 0.06 | 550 | 500 | 70 | <0.5 | 3 |
| 13654 | 2.87 | 1750 | 0.07 | 600 | 350 | 75 | <0.5 | 3 |
| 149393 | 4.14 | 2350 | 0.06 | 700 | 1400 | 95 | <0.5 | 11 |
| 149394 | 3.14 | 1290 | 0.03 | 2300 | 800 | 235 | <0.5 | 2 |
| 13664 | 4.03 | 684 | 0.02 | 2500 | 1100 | 330 | <0.5 | 8 |
| 13665 | 4.22 | 1100 | 0.02 | 2400 | 1350 | 265 | <0.5 | 14 |
| 13666 | 4.28 | 660 | 0.03 | 2750 | 1050 | 305 | <0.5 | 10 |
| Std Nominal | 19.7 | 996 | 0.09 | 150 | 3.11% | 40 | <0.5 | 25 |
| Determined | 19.9 | 996 | 0.10 | 150 | 3.15% | 40 | <0.5 | 24 |
| 13667 | 2.65 | 696 | 0.03 | 2600 | 1550 | 235 | <0.5 | 13 |
| 13668 | 3.64 | 886 | 0.03 | 2650 | 1850 | 300 | <0.5 | 14 |
| 13668 Rpt | 3.65 | 880 | 0.03 | 2650 | 1850 | 295 | <0.5 | 14 |
| 13669 | 3.84 | 574 | 0.02 | 2700 | 2050 | 295 | <0.5 | 16 |
| 13670 | 4.08 | 432 | 0.03 | 2750 | 1100 | 285 | <0.5 | 12 |
| 13671 | 4.13 | 736 | 0.03 | 2450 | 850 | 275 | <0.5 | 6 |
| 13672 | 2.86 | 1120 | 0.03 | 2650 | 3750 | 215 | <0.5 | 22 |
| 13673 | 4.44 | 644 | 0.03 | 2600 | 1650 | 310 | <0.5 | 7 |
| 13674 | 4.91 | 472 | 0.02 | 2750 | 1400 | 315 | <0.5 | 12 |
| 13675 | 5.24 | 434 | 0.02 | 2750 | 750 | 290 | <0.5 | 7 |
| 149395 | 3.98 | 308 | 0.02 | 2650 | 1100 | 310 | <0.5 | 10 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 14 of 49

| | Mg % | Mn ppm | Na % | P ppm | S ppm | V ppm | Ag ppm | As ppm |
|-----------------|---------|-----------|---------|----------|----------|----------|-----------|-----------|
| Detection Limit | 0.01 | 2 | 0.01 | 50 | 50 | 5 | 0.5 | 1 |
| 149396 | 3.16 | 138 | 0.03 | 2700 | 1400 | 325 | <0.5 | 22 |
| 149397 | 2.23 | 66 | 0.02 | 2950 | 1300 | 295 | <0.5 | 34 |
| 149398 | 2.65 | 70 | 0.02 | 3000 | 3050 | 285 | 0.5 | 54 |
| 149398 Rpt | 2.61 | 70 | 0.02 | 3050 | 3200 | 275 | <0.5 | 56 |
| 13693 | 2.36 | 624 | 0.03 | 2800 | 1350 | 210 | <0.5 | 18 |
| 13694 | 7.72 | 4940 | 0.06 | 500 | 1750 | 95 | <0.5 | 2 |
| 13695 | 6.23 | 4060 | 0.07 | 700 | 900 | 95 | <0.5 | 3 |
| 13696 | 8.36 | 5500 | 0.04 | 350 | 1050 | 55 | <0.5 | 4 |
| 13697 | 8.77 | 3940 | 0.05 | 350 | 450 | 50 | <0.5 | 1 |
| 13698 | 7.60 | 3000 | 0.06 | 400 | 700 | 65 | <0.5 | 2 |
| 13699 | 3.79 | 896 | 0.08 | 500 | 5550 | 70 | <0.5 | 2 |
| 13700 | 1.22 | 1260 | 0.32 | 100 | 800 | 150 | <0.5 | 17 |
| 13700 Rpt | 1.21 | 1260 | 0.32 | 100 | 800 | 150 | <0.5 | 18 |
| 13701 | 7.09 | 3550 | 0.07 | 400 | 1500 | 65 | <0.5 | 2 |
| Std Nominal | 4.52 | 1390 | 1.82 | 100 | 100 | 220 | <0.5 | 1 |
| Determined | 4.47 | 1380 | 1.82 | 100 | 100 | 215 | <0.5 | 1 |
| 13702 | 6.93 | 3490 | 0.05 | 550 | 4250 | 145 | <0.5 | 15 |
| 13702 Rpt | 6.76 | 3430 | 0.05 | 550 | 4200 | 140 | <0.5 | 15 |
| 13703 | 5.58 | 2940 | 0.06 | 300 | 700 | 90 | <0.5 | 3 |
| 13704 | 4.19 | 1890 | 0.03 | 2300 | 4300 | 180 | <0.5 | 13 |
| 13705 | 4.36 | 1020 | 0.02 | 2700 | 1.20% | 275 | <0.5 | 23 |
| 13706 | 4.72 | 644 | 0.02 | 2850 | 3800 | 295 | <0.5 | 40 |
| 13707 | 4.49 | 1360 | 0.03 | 2650 | 1850 | 240 | <0.5 | 14 |
| 13708 | 3.66 | 956 | 0.02 | 2600 | 3150 | 235 | <0.5 | 14 |
| 13709 | 5.14 | 614 | 0.02 | 2900 | 950 | 265 | <0.5 | 4 |
| 13710 | 5.41 | 978 | 0.02 | 2800 | 1650 | 255 | <0.5 | 6 |
| 13711 | 5.14 | 1970 | 0.02 | 2400 | 3200 | 205 | <0.5 | 7 |
| 13712 | 5.62 | 1440 | 0.02 | 2650 | 2300 | 235 | <0.5 | 4 |
| 13713 | 5.47 | 638 | 0.02 | 3000 | 2100 | 275 | <0.5 | 6 |
| 13714 | 5.62 | 912 | 0.02 | 2800 | 1700 | 250 | <0.5 | 12 |
| 13715 | 5.82 | 168 | 0.02 | 3150 | 1700 | 300 | <0.5 | 10 |
| 13716 | 6.61 | 178 | 0.02 | 3200 | 500 | 305 | <0.5 | 2 |
| 13717 | 6.93 | 212 | 0.02 | 3100 | 1250 | 275 | <0.5 | 4 |
| 13718 | 5.46 | 152 | 0.02 | 2650 | 450 | 230 | <0.5 | 2 |
| 13719 | 6.09 | 148 | 0.02 | 3000 | 2150 | 260 | <0.5 | 5 |
| 13720 | 2.08 | 84 | <0.01 | 200 | 8.42% | 10 | 2.5 | 3050 |
| 13720 Rpt | 2.07 | 84 | <0.01 | 200 | 8.34% | 10 | 2.5 | 2870 |
| 13721 | 6.44 | 150 | <0.01 | 2950 | 800 | 275 | <0.5 | 3 |
| 13722 | 6.75 | 150 | <0.01 | 3350 | 850 | 280 | <0.5 | 6 |
| 13723 | 5.63 | 164 | 0.02 | 3100 | 1000 | 270 | <0.5 | 5 |
| 13724 | 5.70 | 386 | 0.02 | 3450 | 2800 | 250 | 0.5 | 6 |
| 13725 | 5.95 | 1400 | 0.02 | 2400 | 2850 | 200 | <0.5 | 15 |
| 13726 | 8.78 | 3290 | 0.03 | 600 | 2000 | 85 | <0.5 | 4 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 15 of 49

| | Mg % | Mn ppm | Na % | P ppm | S ppm | V ppm | Ag ppm | As ppm |
|-----------------|---------|-----------|---------|----------|----------|----------|-----------|-----------|
| Detection Limit | 0.01 | 2 | 0.01 | 50 | 50 | 5 | 0.5 | 1 |
| 13728 | 0.44 | 3520 | <0.01 | 1300 | 100 | 540 | <0.5 | 299 |
| 13729 | 0.85 | 956 | 0.02 | 1150 | <50 | 320 | <0.5 | 177 |
| 13730 | 1.25 | 138 | 0.03 | 2800 | 100 | 240 | <0.5 | 129 |
| 13731 | 1.03 | 66 | 0.03 | 2950 | 50 | 165 | <0.5 | 70 |
| 13732 | 0.56 | 126 | 0.05 | 3050 | 100 | 120 | <0.5 | 133 |
| 13732 Rpt | 0.56 | 128 | 0.05 | 3100 | 100 | 125 | <0.5 | 128 |
| 13733 | 0.38 | 152 | 0.05 | 3000 | 50 | 85 | <0.5 | 143 |
| 13734 | 0.80 | 46 | 0.04 | 3100 | 50 | 125 | <0.5 | 63 |
| 13735 | 0.64 | 40 | 0.05 | 3150 | 50 | 130 | <0.5 | 75 |
| 13736 | 0.29 | 80 | 0.05 | 4000 | 100 | 105 | 0.5 | 96 |
| 13737 | 0.52 | 54 | 0.09 | 1750 | 100 | 65 | 1.0 | 76 |
| Std Nominal | 4.05 | 1070 | 2.15 | 1300 | 1.74% | 155 | 0.5 | 13 |
| Determined | 4.08 | 1100 | 2.22 | 1250 | 1.73% | 150 | 0.5 | 12 |
| 13738 | 0.13 | 76 | 0.04 | 250 | 100 | 15 | <0.5 | 32 |
| 13739 | 0.36 | 70 | 0.03 | 250 | 100 | 15 | <0.5 | 23 |
| 13740 | 0.33 | 92 | 0.03 | 300 | 100 | 20 | <0.5 | 21 |
| 13741 | 0.46 | 74 | 0.04 | 350 | 100 | 25 | <0.5 | 56 |
| 13742 | 0.74 | 64 | 0.04 | 300 | 100 | 25 | <0.5 | 44 |
| 13743 | 1.53 | 66 | 0.07 | 550 | 5150 | 85 | <0.5 | 152 |
| 13744 | 0.73 | 68 | 0.05 | 400 | 2750 | 30 | <0.5 | 97 |
| 13745 | 0.10 | 66 | 0.04 | 250 | 150 | 5 | <0.5 | 18 |
| 13746 | 0.68 | 68 | 0.05 | 400 | 900 | 20 | <0.5 | 117 |
| 13747 | 0.38 | 44 | 0.04 | 250 | 100 | 10 | <0.5 | 33 |
| 13748 | 0.70 | 58 | 0.05 | 300 | 100 | 15 | <0.5 | 13 |
| 13749 | 3.17 | 1320 | 0.06 | 400 | 5450 | 65 | <0.5 | 31 |
| 13750 | 3.28 | 1540 | 0.06 | 400 | 4050 | 55 | <0.5 | 14 |
| 13751 | 3.24 | 1940 | 0.07 | 500 | 1350 | 60 | <0.5 | 7 |
| 13751 Rpt | 3.30 | 1980 | 0.07 | 500 | 1400 | 60 | <0.5 | 7 |
| 13752 | 2.53 | 1030 | 0.06 | 600 | 350 | 65 | <0.5 | 7 |
| 13753 | 2.54 | 564 | 0.06 | 650 | 400 | 75 | <0.5 | 6 |
| 13754 | 2.94 | 1580 | 0.06 | 550 | 250 | 65 | <0.5 | 5 |
| 13755 | 3.30 | 1610 | 0.06 | 500 | 150 | 65 | <0.5 | 5 |
| 13756 | 2.87 | 1440 | 0.06 | 550 | 100 | 60 | <0.5 | 5 |
| 13757 | 3.04 | 1580 | 0.06 | 500 | 100 | 60 | <0.5 | 5 |
| 13757 Rpt | 3.05 | 1590 | 0.06 | 500 | 100 | 60 | <0.5 | 4 |
| 13758 | 2.97 | 1640 | 0.06 | 500 | 150 | 65 | <0.5 | 6 |
| Std Nominal | 0.03 | 160 | 2.49 | 100 | 200 | <5 | <0.5 | 17 |
| Determined | 0.03 | 158 | 2.50 | 100 | 150 | <5 | <0.5 | 18 |
| 13759 | 3.15 | 1830 | 0.07 | 550 | 100 | 65 | <0.5 | 7 |
| 13760 | 1.22 | 1280 | 0.32 | 100 | 800 | 145 | <0.5 | 19 |
| 13761 | 2.93 | 1780 | 0.06 | 550 | 150 | 75 | <0.5 | 6 |
| 13762 | 2.96 | 1670 | 0.07 | 600 | 150 | 80 | <0.5 | 5 |
| 13763 | 2.91 | 1720 | 0.06 | 550 | 150 | 75 | <0.5 | 5 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 16 of 49

| | Mg % | Mn ppm | Na % | P ppm | S ppm | V ppm | Ag ppm | As ppm |
|-----------------|---------|-----------|---------|----------|----------|----------|-----------|-----------|
| Detection Limit | 0.01 | 2 | 0.01 | 50 | 50 | 5 | 0.5 | 1 |
| 13764 | 2.79 | 1750 | 0.06 | 600 | 150 | 80 | <0.5 | 4 |
| 13764 Rpt | 2.95 | 1780 | 0.07 | 650 | 200 | 75 | <0.5 | 5 |
| 13765 | 3.64 | 1690 | 0.07 | 650 | 850 | 95 | <0.5 | 7 |
| 13765 Rpt | 3.59 | 1660 | 0.07 | 700 | 900 | 90 | <0.5 | 6 |
| 13766 | 7.12 | 3700 | 0.06 | 450 | 1350 | 110 | <0.5 | 31 |
| 13767 | 2.71 | 2080 | 0.04 | 1600 | 300 | 140 | <0.5 | 322 |
| 13768 | 3.53 | 1610 | 0.04 | 4550 | 800 | 165 | <0.5 | 104 |
| 13769 | 3.23 | 1050 | 0.03 | 2850 | 1150 | 250 | <0.5 | 44 |
| Std Nominal | 1.71 | 1180 | 1.30 | 600 | 1.97% | 120 | 6.0 | 100 |
| Determined | 1.72 | 1170 | 1.29 | 600 | 1.94% | 120 | 6.0 | 106 |
| 13770 | 3.19 | 1140 | 0.03 | 2500 | 1400 | 250 | <0.5 | 34 |
| 149399 | 2.97 | 788 | 0.03 | 2550 | 1050 | 285 | <0.5 | 189 |
| 149400 | 2.85 | 730 | 0.03 | 2500 | 1050 | 280 | <0.5 | 207 |
| 149401 | 3.65 | 1250 | 0.03 | 2400 | 1450 | 250 | <0.5 | 24 |
| 149402 | 3.11 | 768 | 0.03 | 2550 | 1550 | 225 | <0.5 | 16 |
| 149403 | 3.92 | 764 | 0.03 | 2500 | 2300 | 265 | <0.5 | 26 |
| 149404 | 3.28 | 362 | 0.03 | 2750 | 2050 | 280 | <0.5 | 21 |
| 149405 | 3.54 | 220 | 0.03 | 2800 | 1650 | 290 | <0.5 | 24 |
| 13796 | 1.70 | 78 | 0.03 | 3100 | 1700 | 255 | <0.5 | 22 |
| 13797 | 2.04 | 72 | 0.02 | 3000 | 2200 | 280 | <0.5 | 18 |
| 13798 | 2.03 | 64 | 0.02 | 3050 | 1700 | 230 | <0.5 | 14 |
| 13799 | 2.40 | 76 | 0.02 | 3150 | 3400 | 250 | <0.5 | 29 |
| 13800 | 2.18 | 90 | <0.01 | 250 | 8.40% | 10 | 2.5 | 3090 |
| 13801 | 2.10 | 78 | 0.03 | 3200 | 3100 | 255 | 0.5 | 27 |
| 13802 | 1.97 | 116 | 0.03 | 3250 | 4450 | 215 | 0.5 | 39 |
| 13803 | 2.56 | 474 | 0.03 | 2800 | 2550 | 210 | 0.5 | 30 |
| 13804 | 2.90 | 300 | 0.08 | 1200 | 8500 | 200 | <0.5 | 30 |
| 13805 | 2.52 | 88 | 0.11 | 1300 | 4600 | 140 | <0.5 | 14 |
| 13806 | 0.77 | 80 | 0.03 | 350 | 4300 | 35 | <0.5 | 32 |
| 13807 | 0.69 | 96 | 0.07 | 450 | 5000 | 40 | <0.5 | 52 |
| 13808 | 1.48 | 78 | 0.09 | 700 | 7300 | 80 | 1.0 | 85 |
| Std Nominal | 26.6 | 80 | <0.01 | <50 | 100 | 5 | <0.5 | <1 |
| Determined | 26.8 | 76 | 0.01 | <50 | 50 | <5 | <0.5 | 1 |
| 13809 | 5.49 | 2160 | 0.06 | 400 | 3150 | 100 | <0.5 | 13 |
| 13810 | 3.37 | 666 | 0.07 | 1650 | 7950 | 165 | <0.5 | 40 |
| 13810 Rpt | 3.33 | 692 | 0.08 | 1700 | 8150 | 180 | <0.5 | 43 |
| 149406 | 1.77 | 80 | 0.03 | 3250 | 3600 | 210 | <0.5 | 19 |
| 149407 | 2.16 | 66 | 0.03 | 3600 | 1600 | 190 | <0.5 | 14 |
| 149408 | 2.32 | 342 | 0.03 | 3300 | 3350 | 210 | <0.5 | 37 |
| 149409 | 2.58 | 212 | 0.03 | 3400 | 1150 | 260 | <0.5 | 15 |
| 13828 | 2.28 | 360 | 0.03 | 3300 | 800 | 170 | <0.5 | 5 |
| 13829 | 5.48 | 2210 | 0.04 | 1900 | 900 | 140 | <0.5 | 11 |
| 13830 | 9.58 | 4260 | 0.05 | 300 | 1350 | 90 | <0.5 | 8 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 17 of 49

| | Mg % | Mn ppm | Na % | P ppm | S ppm | V ppm | Ag ppm | As ppm |
|-----------------|---------|-----------|---------|----------|----------|----------|-----------|-----------|
| Detection Limit | 0.01 | 2 | 0.01 | 50 | 50 | 5 | 0.5 | 1 |
| 13831 | 9.95 | 4460 | 0.03 | 200 | 1900 | 90 | <0.5 | 7 |
| 13834 | 0.45 | 1920 | 0.05 | 650 | 100 | 200 | 1.0 | 1080 |
| 13835 | 0.88 | 108 | 0.03 | 250 | 50 | 190 | 1.5 | 161 |
| 13836 | 0.40 | 240 | 0.04 | 400 | 100 | 90 | 1.0 | 338 |
| 13837 | 1.58 | 84 | 0.03 | 600 | 50 | 175 | 1.0 | 213 |
| 13838 | 1.62 | 70 | 0.03 | 1350 | 50 | 190 | 2.0 | 188 |
| 13838 Rpt | 1.64 | 68 | 0.03 | 1350 | 50 | 190 | 2.0 | 185 |
| 13839 | 2.14 | 54 | 0.03 | 3150 | <50 | 270 | 1.5 | 87 |
| 13840 | 2.14 | 54 | 0.03 | 3200 | <50 | 260 | 1.5 | 88 |
| 13841 | 1.46 | 48 | 0.03 | 3400 | 50 | 310 | 1.0 | 201 |
| 13842 | 0.94 | 68 | 0.04 | 3300 | 50 | 125 | 1.0 | 175 |
| 13843 | 1.07 | 74 | 0.04 | 3050 | 100 | 110 | 0.5 | 164 |
| Std Nominal | 26.5 | 1710 | 0.03 | <50 | 100 | 40 | <0.5 | <1 |
| Determined | 26.4 | 1710 | 0.03 | <50 | 150 | 40 | <0.5 | 1 |
| 13844 | 1.44 | 72 | 0.04 | 3150 | 100 | 130 | 0.5 | 72 |
| 13845 | 1.17 | 62 | 0.04 | 3350 | 150 | 120 | 0.5 | 46 |
| 13845 Rpt | 1.15 | 60 | 0.04 | 3450 | 100 | 115 | <0.5 | 46 |
| 13846 | 0.97 | 58 | 0.04 | 3800 | 150 | 80 | 0.5 | 32 |
| 13847 | 0.66 | 46 | 0.04 | 4300 | 150 | 60 | 1.0 | 31 |
| 13848 | 0.40 | 58 | 0.05 | 4500 | 150 | 55 | 1.0 | 40 |
| 13849 | 0.47 | 230 | 0.06 | 5350 | 100 | 105 | 1.0 | 133 |
| 13850 | 0.49 | 66 | 0.05 | 800 | 150 | 50 | <0.5 | 46 |
| 13851 | 1.44 | 54 | 0.11 | 1100 | 100 | 100 | 0.5 | 153 |
| 13852 | 1.02 | 56 | 0.08 | 650 | 100 | 90 | 0.5 | 138 |
| 13853 | 0.83 | 56 | 0.08 | 700 | 7800 | 70 | 1.0 | 315 |
| 13854 | 0.30 | 68 | 0.06 | 450 | 450 | 25 | <0.5 | 56 |
| 13855 | 0.22 | 64 | 0.06 | 450 | 450 | 20 | <0.5 | 44 |
| 13856 | 0.12 | 68 | 0.06 | 300 | 300 | 15 | <0.5 | 40 |
| 13857 | 1.00 | 74 | 0.10 | 700 | 7500 | 75 | 1.0 | 218 |
| 13858 | 1.15 | 56 | 0.06 | 450 | 4400 | 60 | <0.5 | 76 |
| 13859 | 1.47 | 60 | 0.06 | 500 | 2350 | 65 | <0.5 | 38 |
| 13859 Rpt | 1.48 | 58 | 0.06 | 450 | 2350 | 60 | <0.5 | 37 |
| 13860 | 1.23 | 1290 | 0.33 | 100 | 800 | 145 | <0.5 | 18 |
| 13861 | 0.93 | 62 | 0.07 | 600 | 2150 | 60 | <0.5 | 29 |
| 13862 | 0.98 | 52 | 0.09 | 850 | 9850 | 80 | 1.0 | 297 |
| 13862 Rpt | 1.00 | 50 | 0.09 | 850 | 9450 | 80 | 1.0 | 313 |
| 13863 | 0.95 | 54 | 0.08 | 800 | 9000 | 75 | 1.0 | 176 |
| 13864 | 1.12 | 54 | 0.08 | 750 | 1.20% | 75 | 0.5 | 92 |
| 13865 | 1.32 | 62 | 0.08 | 700 | 6900 | 80 | <0.5 | 66 |
| 13866 | 1.30 | 60 | 0.07 | 600 | 2950 | 70 | <0.5 | 33 |
| 13867 | 1.35 | 66 | 0.07 | 700 | 6200 | 85 | 1.0 | 87 |
| 13868 | 2.27 | 198 | 0.06 | 700 | 1500 | 90 | <0.5 | 13 |
| 13869 | 2.48 | 204 | 0.07 | 850 | 2550 | 105 | <0.5 | 15 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 18 of 49

| | Mg % | Mn ppm | Na % | P ppm | S ppm | V ppm | Ag ppm | As ppm |
|-----------------|---------|-----------|---------|----------|----------|----------|-----------|-----------|
| Detection Limit | 0.01 | 2 | 0.01 | 50 | 50 | 5 | 0.5 | 1 |
| 13870 | 2.10 | 88 | 0.08 | 900 | 4300 | 120 | <0.5 | 37 |
| 13871 | 1.74 | 76 | 0.08 | 900 | 4350 | 130 | 1.0 | 69 |
| 13872 | 3.19 | 1230 | 0.10 | 850 | 4450 | 130 | <0.5 | 52 |
| 13873 | 2.43 | 920 | 0.04 | 3800 | 2000 | 195 | <0.5 | 11 |
| 149410 | 1.42 | 236 | 0.04 | 3650 | 2950 | 125 | <0.5 | 12 |
| Std Nominal | 7.83 | 1510 | 0.19 | 50 | <50 | 230 | <0.5 | 1 |
| Determined | 7.96 | 1550 | 0.18 | 50 | 50 | 230 | <0.5 | 1 |
| 149411 | 1.78 | 146 | 0.03 | 2950 | 3350 | 185 | <0.5 | 19 |
| 13883 | 2.43 | 520 | 0.03 | 2650 | 1300 | 250 | <0.5 | 6 |
| 13883 Rpt | 2.53 | 536 | 0.03 | 2800 | 1300 | 260 | <0.5 | 6 |
| 13884 | 2.73 | 550 | 0.03 | 2850 | 900 | 300 | <0.5 | 5 |
| 13885 | 1.31 | 144 | 0.03 | 2950 | 1550 | 145 | <0.5 | 5 |
| 13886 | 1.63 | 118 | 0.03 | 3250 | 2150 | 190 | <0.5 | 7 |
| 13887 | 3.51 | 1470 | 0.04 | 2100 | 550 | 165 | <0.5 | 4 |
| 13888 | 4.48 | 2910 | 0.03 | 550 | 300 | 45 | <0.5 | 5 |
| 149412 | 3.46 | 2220 | 0.05 | 400 | 600 | 55 | <0.5 | 4 |
| 13893 | 2.93 | 1640 | 0.06 | 600 | 400 | 60 | <0.5 | 6 |
| 13894 | 2.97 | 1570 | 0.06 | 600 | 250 | 60 | <0.5 | 5 |
| Std Nominal | 1.86 | 5810 | <0.01 | 50 | 1900 | 125 | <0.5 | 2 |
| Determined | 1.84 | 5710 | 0.01 | 100 | 1900 | 125 | <0.5 | 6 |
| 13895 | 3.37 | 2040 | 0.06 | 500 | 150 | 55 | <0.5 | 5 |
| 13896 | 3.12 | 1680 | 0.06 | 550 | 150 | 55 | <0.5 | 6 |
| 13897 | 3.01 | 1600 | 0.06 | 550 | 350 | 60 | <0.5 | 5 |
| 13898 | 3.01 | 1700 | 0.06 | 600 | 250 | 60 | <0.5 | 4 |
| 13899 | 3.17 | 1830 | 0.06 | 550 | 150 | 55 | <0.5 | 4 |
| 13899 Rpt | 3.25 | 1870 | 0.06 | 600 | 150 | 55 | <0.5 | 3 |
| 13900 | 2.15 | 92 | 0.01 | 200 | 8.50% | 10 | 2.5 | 3060 |
| 13901 | 2.95 | 1860 | 0.06 | 550 | 100 | 60 | <0.5 | 4 |
| 13902 | 2.90 | 1770 | 0.06 | 600 | 350 | 60 | <0.5 | 5 |
| 13903 | 3.11 | 1760 | 0.07 | 600 | 300 | 70 | <0.5 | 5 |
| 13904 | 2.99 | 1470 | 0.06 | 550 | 450 | 75 | <0.5 | 5 |
| 13905 | 7.57 | 3320 | 0.05 | 400 | 4350 | 75 | <0.5 | 41 |
| 13906 | 7.52 | 4460 | 0.04 | 650 | 2250 | 80 | <0.5 | 11 |
| 13906 Rpt | 7.33 | 4370 | 0.04 | 600 | 2100 | 75 | <0.5 | 11 |
| 13907 | 4.82 | 2560 | 0.05 | 850 | 950 | 125 | <0.5 | 6 |
| 13908 | 2.95 | 1630 | 0.06 | 550 | 450 | 70 | <0.5 | 2 |
| 13909 | 3.02 | 1800 | 0.06 | 500 | 800 | 65 | <0.5 | 5 |
| 13910 | 2.74 | 1460 | 0.06 | 550 | 550 | 65 | <0.5 | 3 |
| 13911 | 1.91 | 1370 | 0.04 | 200 | 5000 | 25 | <0.5 | 29 |
| 13912 | 3.09 | 2800 | 0.03 | 1100 | 6250 | 100 | <0.5 | 23 |
| 13913 | 4.31 | 2550 | 0.03 | 1900 | 1500 | 205 | <0.5 | 12 |
| 149413 | 4.39 | 1400 | 0.02 | 2050 | 3000 | 245 | <0.5 | 10 |
| 149414 | 4.69 | 468 | 0.02 | 2450 | 3500 | 315 | <0.5 | 8 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 19 of 49

| | Mg % | Mn ppm | Na % | P ppm | S ppm | V ppm | Ag ppm | As ppm |
|-----------------|---------|-----------|---------|----------|----------|----------|-----------|-----------|
| Detection Limit | 0.01 | 2 | 0.01 | 50 | 50 | 5 | 0.5 | 1 |
| 149415 | 4.83 | 1100 | 0.03 | 2150 | 1600 | 250 | <0.5 | 2 |
| 149415 Rpt | 4.80 | 1090 | 0.03 | 2150 | 1700 | 240 | <0.5 | 2 |
| 149416 | 4.50 | 1600 | 0.03 | 2150 | 1000 | 230 | <0.5 | 1 |
| 149417 | 4.73 | 722 | 0.03 | 2400 | 1050 | 265 | <0.5 | 2 |
| 149418 | 4.71 | 714 | 0.03 | 2550 | 550 | 270 | <0.5 | 1 |
| 13938 | 0.24 | 4880 | <0.01 | 1350 | 100 | 420 | <0.5 | 238 |
| 13939 | 0.29 | 3790 | 0.04 | 1050 | 50 | 245 | <0.5 | 258 |
| 13940 | 0.27 | 3760 | 0.03 | 1200 | 100 | 265 | <0.5 | 290 |
| 13941 | 0.58 | 732 | 0.09 | 400 | 100 | 90 | 0.5 | 79 |
| 13942 | 0.45 | 746 | 0.08 | 500 | 100 | 105 | 0.5 | 147 |
| 13943 | 0.37 | 64 | 0.08 | 3800 | 100 | 60 | <0.5 | 12 |
| 13944 | 0.40 | 460 | 0.07 | 2200 | 100 | 60 | 0.5 | 76 |
| 13945 | 0.56 | 918 | 0.07 | 500 | 50 | 70 | <0.5 | 52 |
| 13945 Rpt | 0.56 | 934 | 0.07 | 550 | 100 | 75 | <0.5 | 54 |
| 13946 | 0.57 | 136 | 0.08 | 600 | 50 | 75 | <0.5 | 37 |
| 13947 | 0.53 | 80 | 0.08 | 1200 | 50 | 80 | <0.5 | 33 |
| 13948 | 0.48 | 76 | 0.08 | 1750 | 100 | 80 | <0.5 | 40 |
| 13949 | 0.68 | 58 | 0.09 | 1800 | 100 | 90 | <0.5 | 71 |
| Std Nominal | 19.7 | 996 | 0.09 | 150 | 3.11% | 40 | <0.5 | 25 |
| Determined | 19.5 | 984 | 0.10 | 100 | 3.12% | 40 | <0.5 | 24 |
| 13950 | 0.58 | 52 | 0.08 | 3650 | 100 | 80 | <0.5 | 43 |
| 13951 | 0.61 | 52 | 0.08 | 2350 | 200 | 85 | <0.5 | 21 |
| 13952 | 0.63 | 48 | 0.08 | 1300 | 100 | 75 | <0.5 | 68 |
| 13953 | 0.60 | 48 | 0.08 | 1250 | 50 | 70 | <0.5 | 84 |
| 13954 | 0.66 | 58 | 0.10 | 1150 | 50 | 85 | 0.5 | 140 |
| 13955 | 1.00 | 62 | 0.09 | 1050 | 100 | 100 | <0.5 | 52 |
| 13956 | 0.68 | 62 | 0.09 | 1100 | 100 | 95 | <0.5 | 157 |
| 13957 | 0.71 | 60 | 0.10 | 1550 | 100 | 95 | <0.5 | 106 |
| 13958 | 0.68 | 60 | 0.10 | 1150 | 100 | 95 | <0.5 | 79 |
| 13959 | 0.72 | 62 | 0.09 | 1500 | 50 | 95 | <0.5 | 63 |
| 13959 Rpt | 0.72 | 62 | 0.09 | 1550 | 100 | 95 | <0.5 | 60 |
| 13960 | 1.19 | 1270 | 0.32 | 100 | 800 | 145 | <0.5 | 16 |
| 13961 | 0.68 | 58 | 0.10 | 950 | 100 | 90 | <0.5 | 69 |
| 13962 | 0.70 | 56 | 0.10 | 1050 | 50 | 80 | <0.5 | 82 |
| 13963 | 0.67 | 60 | 0.09 | 1000 | 50 | 85 | <0.5 | 99 |
| 13964 | 0.59 | 38 | 0.09 | 2700 | 100 | 70 | <0.5 | 98 |
| Std Nominal | 4.52 | 1390 | 1.82 | 100 | 100 | 220 | <0.5 | 1 |
| Determined | 4.57 | 1420 | 1.85 | 50 | 100 | 225 | <0.5 | 2 |
| 13965 | 0.56 | 46 | 0.10 | 1300 | 50 | 65 | 0.5 | 61 |
| 13966 | 0.49 | 42 | 0.09 | 1400 | 50 | 65 | <0.5 | 130 |
| 13967 | 0.61 | 58 | 0.08 | 1100 | 50 | 95 | <0.5 | 109 |
| 13968 | 0.66 | 52 | 0.09 | 1150 | 100 | 120 | <0.5 | 212 |
| 13969 | 0.64 | 50 | 0.08 | 1500 | 100 | 110 | <0.5 | 38 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 20 of 49

| | Mg % | Mn ppm | Na % | P ppm | S ppm | V ppm | Ag ppm | As ppm |
|-----------------|---------|-----------|---------|----------|----------|----------|-----------|-----------|
| Detection Limit | 0.01 | 2 | 0.01 | 50 | 50 | 5 | 0.5 | 1 |
| 13970 | 0.53 | 50 | 0.08 | 1350 | 100 | 95 | <0.5 | 121 |
| 13971 | 0.56 | 42 | 0.07 | 1400 | 100 | 85 | <0.5 | 65 |
| 13972 | 0.61 | 58 | 0.06 | 1850 | 100 | 75 | <0.5 | 88 |
| 13973 | 0.80 | 50 | 0.03 | 1700 | 50 | 75 | 0.5 | 86 |
| 13974 | 0.75 | 144 | 0.03 | 4850 | 50 | 85 | 0.5 | 95 |
| 13974 Rpt | 0.74 | 142 | 0.03 | 4850 | 100 | 85 | 0.5 | 96 |
| 13975 | 0.57 | 66 | 0.04 | 3100 | 50 | 110 | 1.5 | 65 |
| 13976 | 0.41 | 32 | 0.04 | 1650 | 100 | 280 | 1.0 | 475 |
| 13977 | 0.60 | 66 | 0.04 | 5300 | 300 | 250 | 0.5 | 384 |
| 13978 | 0.76 | 546 | 0.04 | 700 | 100 | 150 | 1.0 | 215 |
| Std Nominal | 4.05 | 1070 | 2.15 | 1300 | 1.74% | 155 | 0.5 | 13 |
| Determined | 4.05 | 1080 | 2.15 | 1250 | 1.71% | 155 | 0.5 | 14 |
| 13979 | 0.74 | 246 | 0.04 | 950 | 100 | 135 | 0.5 | 304 |
| 13980 | 2.16 | 88 | 0.01 | 200 | 8.39% | 15 | 2.5 | 2970 |
| 13980 Rpt | 2.16 | 88 | 0.01 | 200 | 8.40% | 10 | 2.0 | 2980 |
| 13981 | 0.56 | 388 | 0.04 | 1500 | 50 | 115 | <0.5 | 528 |
| 13982 | 1.80 | 864 | 0.07 | 950 | 3100 | 165 | <0.5 | 766 |
| 13983 | 6.07 | 2460 | 0.05 | 500 | 1050 | 75 | <0.5 | 55 |
| 13984 | 2.89 | 166 | 0.06 | 700 | 800 | 115 | <0.5 | 26 |
| 13985 | 2.99 | 192 | 0.06 | 850 | 1050 | 105 | <0.5 | 21 |
| 13986 | 3.84 | 1390 | 0.05 | 550 | 800 | 60 | <0.5 | 15 |
| 13987 | 2.65 | 702 | 0.05 | 600 | 700 | 65 | <0.5 | 11 |
| 13988 | 1.98 | 124 | 0.06 | 800 | 750 | 80 | <0.5 | 10 |
| 13989 | 4.72 | 1770 | 0.05 | 750 | 2750 | 70 | <0.5 | 11 |
| 13990 | 4.90 | 1800 | 0.05 | 650 | 700 | 70 | <0.5 | 5 |
| 13990 Rpt | 4.87 | 1810 | 0.05 | 700 | 700 | 65 | <0.5 | 5 |
| 13991 | 4.69 | 1780 | 0.05 | 650 | 250 | 75 | <0.5 | 6 |
| 13992 | 3.99 | 1480 | 0.05 | 600 | 150 | 70 | <0.5 | 4 |
| 13993 | 4.33 | 1590 | 0.06 | 700 | 150 | 70 | <0.5 | 5 |
| 13994 | 3.72 | 1340 | 0.06 | 700 | 250 | 70 | <0.5 | 3 |
| 13995 | 2.89 | 1010 | 0.05 | 550 | 150 | 65 | <0.5 | 4 |
| 13996 | 2.99 | 1170 | 0.05 | 550 | 300 | 60 | <0.5 | 4 |
| 13997 | 3.01 | 1030 | 0.05 | 550 | 150 | 60 | <0.5 | 3 |
| 149419 | 2.76 | 1030 | 0.05 | 600 | 400 | 60 | <0.5 | 2 |
| 149420 | 1.21 | 1260 | 0.33 | 100 | 800 | 150 | <0.5 | 18 |
| 149421 | 2.69 | 1120 | 0.05 | 900 | 300 | 60 | <0.5 | 3 |
| Std Nominal | 0.03 | 160 | 2.49 | 100 | 200 | <5 | <0.5 | 17 |
| Determined | 0.04 | 154 | 2.45 | 50 | 200 | <5 | <0.5 | 18 |
| 149422 | 3.58 | 1720 | 0.04 | 1050 | 700 | 115 | <0.5 | 2 |
| 14011 | 3.09 | 1600 | 0.04 | 750 | 300 | 90 | <0.5 | 2 |
| 14012 | 2.88 | 1630 | 0.05 | 600 | 1550 | 60 | <0.5 | 3 |
| 14013 | 2.75 | 1450 | 0.06 | 550 | 700 | 70 | <0.5 | 3 |
| 14014 | 3.04 | 1630 | 0.06 | 550 | 1200 | 70 | <0.5 | 4 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 21 of 49

| | Mg % | Mn ppm | Na % | P ppm | S ppm | V ppm | Ag ppm | As ppm |
|-----------------|---------|-----------|---------|----------|----------|----------|-----------|-----------|
| Detection Limit | 0.01 | 2 | 0.01 | 50 | 50 | 5 | 0.5 | 1 |
| 14014 Rpt | 2.98 | 1630 | 0.06 | 550 | 1250 | 70 | <0.5 | 4 |
| 14015 | 2.95 | 1640 | 0.06 | 500 | 1150 | 70 | <0.5 | 3 |
| 14016 | 2.93 | 1610 | 0.06 | 550 | 700 | 75 | <0.5 | 4 |
| 14016 Rpt | 2.90 | 1640 | 0.06 | 550 | 700 | 75 | <0.5 | 3 |
| 14017 | 2.75 | 1460 | 0.06 | 550 | 700 | 80 | <0.5 | 2 |
| 14018 | 2.38 | 1250 | 0.05 | 400 | 1300 | 65 | <0.5 | 14 |
| 14019 | 2.91 | 2370 | 0.03 | 200 | 8100 | 45 | <0.5 | 58 |
| 14020 | 2.89 | 2380 | 0.04 | 200 | 8150 | 40 | <0.5 | 69 |
| 14021 | 1.06 | 762 | 0.04 | 200 | 6000 | 25 | <0.5 | 48 |
| 149423 | 4.12 | 1710 | 0.03 | 1700 | 4650 | 210 | <0.5 | 6 |
| 149424 | 2.69 | 1270 | 0.03 | 1150 | 1150 | 125 | <0.5 | 3 |
| 149425 | 3.35 | 1460 | 0.03 | 1400 | 750 | 140 | <0.5 | 2 |
| 149426 | 3.08 | 1810 | 0.04 | 850 | 400 | 90 | <0.5 | 2 |
| 149427 | 3.11 | 1360 | 0.05 | 1150 | 400 | 110 | <0.5 | 2 |
| 14044 | 0.14 | 3520 | 0.01 | 1800 | 100 | 505 | <0.5 | 369 |
| 14045 | 0.13 | 1740 | 0.02 | 2200 | 50 | 375 | <0.5 | 535 |
| 14046 | 0.38 | 574 | 0.04 | 1750 | 100 | 205 | <0.5 | 897 |
| 14047 | 1.42 | 648 | 0.06 | 1250 | 100 | 100 | <0.5 | 357 |
| 14048 | 1.07 | 1400 | 0.07 | 1600 | 150 | 80 | <0.5 | 251 |
| 14049 | 1.09 | 2260 | 0.07 | 2100 | 100 | 100 | <0.5 | 362 |
| 14049 Rpt | 1.10 | 2260 | 0.07 | 2100 | 100 | 100 | <0.5 | 370 |
| 14050 | 0.58 | 2310 | 0.09 | 1400 | 100 | 105 | <0.5 | 106 |
| 14051 | 0.64 | 1620 | 0.07 | 2900 | 150 | 150 | 0.5 | 509 |
| 14052 | 0.24 | 330 | 0.04 | 8050 | 200 | 100 | 1.0 | 134 |
| 14053 | 0.14 | 312 | 0.05 | 5400 | 150 | 70 | <0.5 | 86 |
| Std Nominal | 1.71 | 1180 | 1.30 | 600 | 1.97% | 120 | 6.0 | 100 |
| Determined | 1.67 | 1170 | 1.28 | 650 | 1.94% | 115 | 5.5 | 104 |
| 14054 | 0.18 | 328 | 0.05 | 4500 | 200 | 75 | 0.5 | 127 |
| 14055 | 0.36 | 262 | 0.04 | 4750 | 200 | 130 | 1.0 | 129 |
| 14056 | 0.22 | 60 | 0.04 | 3500 | 100 | 100 | <0.5 | 66 |
| 14057 | 0.16 | 40 | 0.04 | 3550 | 100 | 80 | <0.5 | 32 |
| 14058 | 0.18 | 60 | 0.04 | 3350 | 150 | 80 | <0.5 | 105 |
| 14059 | 0.19 | 62 | 0.05 | 4250 | 100 | 75 | 1.5 | 202 |
| 14061 | 0.34 | 38 | 0.05 | 3050 | 100 | 105 | 1.0 | 260 |
| 14062 | 0.34 | 46 | 0.07 | 3050 | 150 | 175 | <0.5 | 123 |
| 14062 Rpt | 0.35 | 48 | 0.08 | 3150 | 100 | 180 | <0.5 | 132 |
| 14063 | 1.00 | 68 | 0.07 | 1500 | 100 | 260 | <0.5 | 179 |
| 14064 | 0.30 | 92 | 0.06 | 3100 | 150 | 110 | 0.5 | 113 |
| 14065 | 0.27 | 586 | 0.08 | 2900 | 100 | 205 | 1.0 | 156 |
| 14066 | 0.21 | 1410 | 0.06 | 3500 | 100 | 145 | 0.5 | 159 |
| 14067 | 0.33 | 338 | 0.08 | 1950 | 150 | 190 | 1.0 | 132 |
| 14068 | 0.71 | 346 | 0.10 | 1250 | 100 | 185 | 0.5 | 237 |
| 14069 | 1.27 | 76 | 0.08 | 900 | 100 | 170 | <0.5 | 427 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 22 of 49

| | Mg % | Mn ppm | Na % | P ppm | S ppm | V ppm | Ag ppm | As ppm |
|-----------------|---------|-----------|---------|----------|----------|----------|-----------|-----------|
| Detection Limit | 0.01 | 2 | 0.01 | 50 | 50 | 5 | 0.5 | 1 |
| 14070 | 1.53 | 70 | 0.11 | 1250 | 100 | 155 | <0.5 | 170 |
| 14071 | 1.24 | 68 | 0.11 | 1400 | 100 | 150 | 1.0 | 63 |
| 14072 | 0.44 | 52 | 0.16 | 1600 | 100 | 170 | 1.0 | 104 |
| 14073 | 0.45 | 52 | 0.08 | 1150 | 100 | 195 | 1.0 | 105 |
| 14074 | 0.35 | 444 | 0.07 | 1400 | 100 | 150 | 1.0 | 58 |
| 14074 Rpt | 0.36 | 448 | 0.08 | 1400 | 150 | 150 | 1.0 | 57 |
| 14075 | 0.94 | 250 | 0.04 | 900 | 100 | 165 | 0.5 | 205 |
| 14076 | 0.75 | 276 | 0.08 | 1250 | 50 | 150 | <0.5 | 98 |
| 14077 | 1.24 | 160 | 0.04 | 800 | 100 | 130 | <0.5 | 33 |
| 14078 | 1.03 | 4510 | 0.04 | 1300 | 100 | 205 | 0.5 | 484 |
| 14079 | 1.05 | 9010 | 0.03 | 900 | 100 | 130 | <0.5 | 205 |
| 14080 | 1.19 | 1290 | 0.32 | 100 | 750 | 145 | <0.5 | 19 |
| 14084 | 1.66 | 5980 | 0.02 | 500 | 100 | 105 | <0.5 | 923 |
| 14086 | 1.53 | 1.53% | 0.03 | 1400 | 100 | 140 | <0.5 | 2370 |
| 149428 | 3.62 | 1920 | 0.05 | 500 | 1350 | 85 | <0.5 | 145 |
| 149428 Rpt | 3.64 | 1900 | 0.05 | 500 | 1300 | 85 | <0.5 | 136 |
| 149429 | 3.87 | 1790 | 0.05 | 550 | 250 | 70 | <0.5 | 76 |
| 149430 | 4.79 | 2100 | 0.05 | 700 | 150 | 80 | <0.5 | 51 |
| 149431 | 4.79 | 2160 | 0.05 | 950 | 450 | 90 | <0.5 | 16 |
| 149432 | 3.91 | 1660 | 0.04 | 950 | 950 | 105 | <0.5 | 20 |
| 149433 | 3.50 | 1530 | 0.03 | 900 | 500 | 100 | <0.5 | 11 |
| 149434 | 3.76 | 1960 | 0.04 | 800 | 700 | 90 | <0.5 | 7 |
| Std Nominal | 26.6 | 80 | <0.01 | <50 | 100 | 5 | <0.5 | <1 |
| Determined | 26.6 | 84 | <0.01 | <50 | 50 | <5 | <0.5 | <1 |
| 149435 | 4.02 | 2090 | 0.05 | 550 | 700 | 70 | <0.5 | 5 |
| 149436 | 3.10 | 1110 | 0.06 | 1200 | 800 | 175 | <0.5 | 8 |
| 149437 | 1.57 | 682 | 0.02 | 3450 | 550 | 170 | <0.5 | 36 |
| 149438 | 2.91 | 354 | 0.02 | 3150 | 3700 | 250 | <0.5 | 24 |
| 149439 | 4.53 | 1760 | 0.05 | 2000 | 2150 | 170 | <0.5 | 13 |
| 149440 | 4.40 | 1610 | 0.02 | 2050 | 2500 | 180 | <0.5 | 13 |
| Std Nominal | 26.5 | 1710 | 0.03 | <50 | 100 | 40 | <0.5 | <1 |
| Determined | 26.7 | 1700 | 0.03 | <50 | 100 | 40 | <0.5 | <1 |
| 149441 | 2.98 | 1520 | 0.04 | 1000 | 1000 | 105 | <0.5 | 4 |
| 149442 | 4.51 | 1440 | 0.02 | 2200 | 3000 | 240 | <0.5 | 62 |
| 149443 | 3.88 | 1900 | 0.03 | 1850 | 600 | 145 | <0.5 | 5 |
| 14148 | 1.33 | 112 | 0.03 | 3000 | 100 | 245 | <0.5 | 105 |
| 14149 | 1.01 | 48 | 0.03 | 3000 | 100 | 230 | <0.5 | 110 |
| 14150 | 0.83 | 54 | 0.03 | 3100 | 100 | 195 | <0.5 | 157 |
| 14150 Rpt | 0.83 | 56 | 0.03 | 3000 | 100 | 195 | <0.5 | 152 |
| 14151 | 0.61 | 192 | 0.03 | 3000 | 100 | 145 | <0.5 | 84 |
| 14152 | 1.01 | 320 | 0.03 | 2200 | 100 | 165 | 0.5 | 188 |
| 14153 | 1.12 | 178 | 0.03 | 4650 | 100 | 185 | <0.5 | 506 |
| 14154 | 0.32 | 506 | 0.04 | 3600 | 100 | 115 | 1.5 | 341 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 23 of 49

| | Mg % | Mn ppm | Na % | P ppm | S ppm | V ppm | Ag ppm | As ppm |
|-----------------|---------|-----------|---------|----------|----------|----------|-----------|-----------|
| Detection Limit | 0.01 | 2 | 0.01 | 50 | 50 | 5 | 0.5 | 1 |
| 14155 | 0.43 | 98 | 0.09 | 4500 | 100 | 85 | 2.0 | 532 |
| 14156 | 0.51 | 56 | 0.09 | 1450 | 100 | 100 | 1.0 | 175 |
| 14156 Rpt | 0.52 | 56 | 0.09 | 1500 | 150 | 100 | 1.0 | 185 |
| 14157 | 0.31 | 56 | 0.04 | 600 | 150 | 25 | <0.5 | 107 |
| 14158 | 0.74 | 44 | 0.04 | 550 | 50 | 35 | <0.5 | 75 |
| 14159 | 1.01 | 62 | 0.06 | 600 | 100 | 65 | <0.5 | 193 |
| 14160 | 1.02 | 54 | 0.06 | 550 | 100 | 60 | 0.5 | 190 |
| 14161 | 1.10 | 58 | 0.06 | 650 | 100 | 65 | 0.5 | 132 |
| 13516 | 0.22 | 2490 | 0.01 | 850 | 50 | 760 | <0.5 | 226 |
| 13517 | 0.49 | 1370 | 0.01 | 850 | 50 | 460 | <0.5 | 122 |
| 13518 | 0.91 | 230 | 0.04 | 2150 | 50 | 220 | <0.5 | 34 |
| 13518 Rpt | 0.90 | 222 | 0.04 | 2100 | 50 | 220 | <0.5 | 36 |
| 13519 | 1.81 | 96 | 0.07 | 2500 | 150 | 240 | <0.5 | 40 |
| 13520 | 2.11 | 86 | <0.01 | 200 | 8.32% | 15 | 2.5 | 3100 |
| 13521 | 2.10 | 110 | 0.05 | 2500 | 100 | 255 | <0.5 | 37 |
| 13522 | 0.35 | 362 | 0.03 | 2300 | 150 | 105 | <0.5 | 20 |
| 13523 | 0.46 | 968 | 0.04 | 1300 | 100 | 190 | <0.5 | 26 |
| 13524 | 0.32 | 1540 | 0.04 | 3000 | 100 | 100 | <0.5 | 18 |
| 13525 | 0.66 | 2430 | 0.06 | 2800 | 100 | 100 | <0.5 | 13 |
| 13526 | 0.14 | 624 | 0.03 | 650 | 100 | 35 | <0.5 | 5 |
| 13527 | 0.11 | 236 | 0.02 | 350 | 100 | 20 | <0.5 | 4 |
| 13527 Rpt | 0.11 | 224 | 0.02 | 350 | 100 | 20 | <0.5 | 3 |
| 13528 | 0.43 | 480 | 0.05 | 500 | 50 | 45 | <0.5 | 4 |
| 13529 | 0.49 | 390 | 0.03 | 350 | 50 | 35 | <0.5 | 16 |
| 13530 | 1.11 | 118 | 0.08 | 700 | 50 | 120 | <0.5 | 41 |
| 13531 | 0.43 | 78 | 0.05 | 450 | 50 | 45 | <0.5 | 52 |
| 13532 | 0.42 | 96 | 0.08 | 750 | 100 | 30 | <0.5 | 25 |
| 13533 | 0.36 | 102 | 0.06 | 500 | 50 | 20 | <0.5 | 14 |
| 13534 | 0.81 | 206 | 0.09 | 550 | 50 | 35 | <0.5 | 24 |
| Std Nominal | 7.83 | 1510 | 0.19 | 50 | <50 | 230 | <0.5 | 1 |
| Determined | 7.76 | 1530 | 0.18 | 50 | 50 | 230 | <0.5 | <1 |
| 13535 | 1.92 | 1660 | 0.06 | 500 | <50 | 75 | <0.5 | 15 |
| 13536 | 3.30 | 1950 | 0.05 | 400 | 300 | 55 | <0.5 | 5 |
| 13588 | 3.36 | 1210 | 0.02 | 2900 | 7000 | 260 | 0.5 | 93 |
| 13588 Rpt | 3.35 | 1220 | 0.02 | 3000 | 7100 | 265 | 1.0 | 91 |
| 13589 | 1.89 | 342 | 0.02 | 3300 | 1650 | 275 | <0.5 | 22 |
| 13590 | 2.76 | 538 | 0.02 | 3250 | 5150 | 245 | 0.5 | 49 |
| 13591 | 7.49 | 4780 | 0.05 | 450 | 750 | 75 | <0.5 | 2 |
| 13592 | 5.64 | 2990 | 0.06 | 850 | 800 | 100 | <0.5 | 6 |
| 13593 | 3.87 | 1450 | 0.03 | 350 | 900 | 50 | <0.5 | 1 |
| 13593 Rpt | 3.81 | 1440 | 0.03 | 350 | 900 | 50 | <0.5 | 2 |
| 13594 | 0.92 | 90 | 0.03 | 300 | 1700 | 25 | <0.5 | 2 |
| 13595 | 4.47 | 1540 | 0.11 | 650 | 3800 | 85 | <0.5 | 8 |



Reference: u282154 Order Number: NC_003 Page 24 of 49

| | Mg % | Mn ppm | Na % | P ppm | S ppm | V ppm | Ag ppm | As ppm |
|-----------------|---------|-----------|---------|----------|----------|----------|-----------|-----------|
| Detection Limit | 0.01 | 2 | 0.01 | 50 | 50 | 5 | 0.5 | 1 |
| 13596 | 4.57 | 1610 | 0.06 | 450 | 1050 | 120 | <0.5 | 2 |
| 13597 | 3.61 | 1320 | 0.07 | 1150 | 6500 | 160 | <0.5 | 12 |
| Std Nominal | 1.86 | 5810 | <0.01 | 50 | 1900 | 125 | <0.5 | 2 |
| Determined | 1.83 | 5790 | 0.01 | 100 | 1950 | 130 | <0.5 | 3 |
| 13598 | 4.39 | 1700 | 0.02 | 2500 | 800 | 250 | <0.5 | 3 |
| 13599 | 4.53 | 1900 | 0.02 | 2400 | 350 | 230 | <0.5 | 3 |
| 13600 | 1.21 | 1260 | 0.32 | 100 | 800 | 145 | <0.5 | 18 |
| 14060 | 2.17 | 92 | <0.01 | 200 | 8.42% | 10 | 2.5 | 3090 |
| 14060 Rpt | 2.13 | 90 | <0.01 | 200 | 8.33% | 10 | 2.5 | 2990 |
| Std Nominal | 19.7 | 996 | 0.09 | 150 | 3.11% | 40 | <0.5 | 25 |
| Determined | 19.6 | 982 | 0.09 | 100 | 3.09% | 35 | <0.5 | 26 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 25 of 49

| | Ba ppm | Bi ppm | Cd ppm | Co ppm | Cu ppm | Li ppm | Mo ppm | Ni ppm |
|-----------------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| Detection Limit | 1 | 0.1 | 0.5 | 5 | 2 | 0.5 | 0.5 | 2 |
| 149389 | 868 | 0.5 | <0.5 | 745 | 1110 | 21.5 | 6.5 | 712 |
| 149390 | 1370 | 1.0 | <0.5 | 735 | 626 | 4.5 | 2.5 | 410 |
| 13630 | 977 | 0.3 | <0.5 | 770 | 1110 | 6.0 | 1.5 | 448 |
| 13631 | 202 | 0.1 | <0.5 | 140 | 224 | 4.0 | 1.0 | 60 |
| 13631 Rpt | 213 | 0.1 | <0.5 | 135 | 228 | 4.5 | 1.0 | 58 |
| 13632 | 231 | 0.3 | <0.5 | 175 | 336 | 5.0 | 1.0 | 102 |
| 13632 Rpt | 231 | 0.3 | <0.5 | 180 | 342 | 5.0 | 1.0 | 100 |
| 13633 | 261 | 0.2 | <0.5 | 100 | 548 | 6.5 | 0.5 | 106 |
| 13634 | 277 | 0.3 | <0.5 | 110 | 702 | 8.0 | 1.0 | 98 |
| 13635 | 650 | 0.8 | <0.5 | 1510 | 2170 | 21.0 | 0.5 | 1110 |
| 13636 | 239 | 0.2 | <0.5 | 195 | 996 | 7.5 | 1.0 | 200 |
| 13637 | 191 | 0.2 | <0.5 | 140 | 1740 | 3.5 | 1.5 | 92 |
| 13638 | 200 | 0.1 | <0.5 | 40 | 568 | 2.5 | 1.5 | 42 |
| 13639 | 417 | 0.6 | <0.5 | 360 | 1450 | 7.5 | 1.0 | 182 |
| 13640 | 429 | 0.6 | <0.5 | 385 | 1630 | 8.0 | 1.0 | 194 |
| 13641 | 751 | 0.4 | <0.5 | 325 | 642 | 18.0 | 0.5 | 192 |
| 13642 | 732 | 0.4 | <0.5 | 80 | 40 | 23.5 | 0.5 | 54 |
| 149391 | 429 | 0.2 | <0.5 | 80 | 24 | 14.5 | 0.5 | 36 |
| Std Nominal | 38 | <0.1 | <0.5 | 750 | 26 | 3.0 | 1.0 | 1.48% |
| Determined | 39 | <0.1 | <0.5 | 770 | 28 | 3.0 | 1.0 | 1.49% |
| 149392 | 409 | 0.2 | <0.5 | 20 | 38 | 12.5 | 0.5 | 24 |
| 13651 | 397 | 0.4 | <0.5 | 10 | 22 | 10.5 | 1.0 | 26 |
| 13652 | 404 | 0.4 | <0.5 | 20 | 28 | 14.0 | 0.5 | 34 |
| 13653 | 378 | 0.4 | <0.5 | 10 | 8 | 9.5 | 0.5 | 24 |
| 13654 | 378 | 0.3 | <0.5 | 15 | 2 | 10.5 | 0.5 | 30 |
| 149393 | 378 | 0.8 | <0.5 | 20 | 6 | 10.0 | 4.5 | 24 |
| 149394 | 485 | <0.1 | <0.5 | 30 | 8 | 20.0 | <0.5 | 20 |
| 13664 | 382 | 0.3 | <0.5 | 215 | 20 | 41.5 | <0.5 | 44 |
| 13665 | 420 | 0.2 | <0.5 | 50 | 4 | 39.0 | <0.5 | 34 |
| 13666 | 745 | 0.3 | <0.5 | 65 | 4 | 40.0 | <0.5 | 48 |
| Std Nominal | 17 | 0.9 | <0.5 | 285 | 876 | 11.0 | 1.0 | 1.41% |
| Determined | 18 | 0.9 | <0.5 | 285 | 882 | 10.5 | 1.0 | 1.41% |
| 13667 | 708 | 0.8 | <0.5 | 55 | 6 | 20.5 | 0.5 | 54 |
| 13668 | 607 | 0.5 | <0.5 | 60 | 4 | 27.5 | <0.5 | 50 |
| 13668 Rpt | 632 | 0.5 | <0.5 | 55 | 2 | 28.5 | <0.5 | 48 |
| 13669 | 588 | 0.7 | <0.5 | 65 | 4 | 35.5 | <0.5 | 54 |
| 13670 | 686 | <0.1 | <0.5 | 60 | 2 | 40.0 | 2.0 | 48 |
| 13671 | 491 | <0.1 | <0.5 | 50 | 2 | 42.5 | 1.0 | 40 |
| 13672 | 542 | 0.3 | <0.5 | 140 | 76 | 22.0 | 1.0 | 160 |
| 13673 | 420 | 0.2 | <0.5 | 70 | 2 | 43.0 | <0.5 | 64 |
| 13674 | 454 | 0.2 | <0.5 | 80 | 6 | 47.0 | <0.5 | 64 |
| 13675 | 386 | <0.1 | <0.5 | 60 | 12 | 50.0 | <0.5 | 60 |
| 149395 | 485 | <0.1 | <0.5 | 70 | 2 | 43.5 | <0.5 | 56 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 26 of 49

| | Ba ppm | Bi ppm | Cd ppm | Co ppm | Cu ppm | Li ppm | Mo ppm | Ni ppm |
|-----------------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| Detection Limit | 1 | 0.1 | 0.5 | 5 | 2 | 0.5 | 0.5 | 2 |
| 149396 | 653 | 0.3 | <0.5 | 90 | 12 | 37.0 | 1.0 | 74 |
| 149397 | 810 | 0.3 | <0.5 | 125 | 10 | 28.0 | 3.5 | 88 |
| 149398 | 678 | 0.6 | <0.5 | 280 | 46 | 30.5 | 5.0 | 196 |
| 149398 Rpt | 671 | 0.6 | <0.5 | 290 | 46 | 32.0 | 5.5 | 202 |
| 13693 | 718 | 0.2 | <0.5 | 90 | 18 | 16.5 | 5.0 | 70 |
| 13694 | 292 | <0.1 | <0.5 | 45 | 1300 | 15.0 | <0.5 | 36 |
| 13695 | 448 | <0.1 | <0.5 | 50 | 104 | 17.5 | 0.5 | 36 |
| 13696 | 238 | <0.1 | <0.5 | 40 | 72 | 9.0 | 0.5 | 30 |
| 13697 | 222 | <0.1 | <0.5 | 30 | 30 | 9.0 | <0.5 | 20 |
| 13698 | 369 | <0.1 | <0.5 | 50 | 138 | 16.5 | <0.5 | 44 |
| 13699 | 509 | <0.1 | <0.5 | 80 | 2810 | 19.5 | 1.0 | 82 |
| 13700 | 127 | <0.1 | <0.5 | 450 | 80 | 10.5 | 0.5 | 4970 |
| 13700 Rpt | 130 | <0.1 | <0.5 | 445 | 78 | 10.5 | 0.5 | 4980 |
| 13701 | 434 | <0.1 | <0.5 | 80 | 720 | 11.5 | 0.5 | 58 |
| Std Nominal | 102 | <0.1 | <0.5 | 60 | 14 | 6.0 | 1.0 | 120 |
| Determined | 100 | <0.1 | <0.5 | 60 | 16 | 6.0 | 1.0 | 120 |
| 13702 | 307 | 0.5 | <0.5 | 30 | 20 | 17.0 | 2.0 | 28 |
| 13702 Rpt | 303 | 0.5 | <0.5 | 30 | 18 | 16.5 | 2.0 | 28 |
| 13703 | 385 | <0.1 | <0.5 | 20 | 20 | 19.5 | 0.5 | 26 |
| 13704 | 715 | 0.4 | <0.5 | 20 | 36 | 15.0 | 0.5 | 16 |
| 13705 | 536 | 0.4 | <0.5 | 35 | 22 | 31.0 | 1.5 | 30 |
| 13706 | 573 | 1.0 | <0.5 | 70 | 14 | 41.0 | 0.5 | 44 |
| 13707 | 450 | 0.5 | <0.5 | 60 | 72 | 24.0 | 0.5 | 32 |
| 13708 | 450 | 0.8 | <0.5 | 45 | 14 | 24.5 | 0.5 | 24 |
| 13709 | 382 | 0.6 | <0.5 | 40 | 12 | 44.0 | <0.5 | 26 |
| 13710 | 364 | 0.8 | <0.5 | 45 | 8 | 37.5 | <0.5 | 26 |
| 13711 | 305 | 0.2 | <0.5 | 45 | 1290 | 29.5 | <0.5 | 18 |
| 13712 | 292 | <0.1 | <0.5 | 35 | 946 | 39.5 | <0.5 | 24 |
| 13713 | 325 | <0.1 | <0.5 | 50 | 12 | 43.0 | <0.5 | 26 |
| 13714 | 300 | 0.4 | <0.5 | 75 | 6 | 47.0 | <0.5 | 34 |
| 13715 | 281 | 0.7 | <0.5 | 90 | 6 | 57.5 | <0.5 | 52 |
| 13716 | 205 | <0.1 | <0.5 | 65 | 130 | 57.0 | <0.5 | 56 |
| 13717 | 217 | 0.3 | <0.5 | 180 | 136 | 59.5 | 0.5 | 50 |
| 13718 | 257 | <0.1 | <0.5 | 140 | 6 | 57.0 | <0.5 | 36 |
| 13719 | 304 | <0.1 | <0.5 | 150 | 114 | 59.0 | <0.5 | 70 |
| 13720 | 17 | 47.1 | <0.5 | 2440 | 3.17% | 10.0 | 10.0 | 114 |
| 13720 Rpt | 16 | 47.4 | <0.5 | 2390 | 3.17% | 10.0 | 10.0 | 116 |
| 13721 | 330 | 0.1 | <0.5 | 155 | 32 | 67.5 | <0.5 | 70 |
| 13722 | 270 | 0.1 | <0.5 | 130 | 86 | 60.0 | <0.5 | 76 |
| 13723 | 264 | 0.4 | <0.5 | 245 | 18 | 51.0 | <0.5 | 72 |
| 13724 | 291 | 0.9 | <0.5 | 375 | 838 | 43.5 | <0.5 | 78 |
| 13725 | 281 | 0.3 | <0.5 | 75 | 442 | 36.5 | <0.5 | 52 |
| 13726 | 178 | <0.1 | <0.5 | 40 | 548 | 16.5 | <0.5 | 24 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 27 of 49

| | Ba ppm | Bi ppm | Cd ppm | Co ppm | Cu ppm | Li ppm | Mo ppm | Ni ppm |
|-----------------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| Detection Limit | 1 | 0.1 | 0.5 | 5 | 2 | 0.5 | 0.5 | 2 |
| 13728 | 272 | 0.7 | <0.5 | 980 | 1460 | 46.0 | 15.0 | 304 |
| 13729 | 429 | 0.8 | <0.5 | 355 | 1650 | 41.0 | 4.5 | 204 |
| 13730 | 835 | 0.5 | <0.5 | 935 | 1070 | 55.0 | 9.0 | 714 |
| 13731 | 1060 | 0.5 | <0.5 | 630 | 1020 | 21.5 | 6.0 | 440 |
| 13732 | 1060 | 0.6 | <0.5 | 1570 | 2120 | 11.0 | 5.0 | 356 |
| 13732 Rpt | 1090 | 0.6 | <0.5 | 1580 | 2200 | 12.0 | 5.0 | 368 |
| 13733 | 895 | 1.0 | <0.5 | 1580 | 1790 | 5.0 | 5.5 | 356 |
| 13734 | 944 | 0.5 | <0.5 | 215 | 5570 | 8.5 | 1.5 | 470 |
| 13735 | 1080 | 0.6 | <0.5 | 150 | 6480 | 14.0 | 2.0 | 324 |
| 13736 | 1150 | 0.8 | <0.5 | 940 | 3090 | 5.5 | 1.5 | 182 |
| 13737 | 1000 | 2.0 | <0.5 | 260 | 1210 | 7.5 | 1.5 | 248 |
| Std Nominal | 239 | <0.1 | <0.5 | 155 | 316 | 7.5 | 2.0 | 6930 |
| Determined | 232 | <0.1 | <0.5 | 150 | 318 | 8.0 | 2.0 | 6960 |
| 13738 | 197 | 0.3 | <0.5 | 95 | 194 | 4.5 | 1.5 | 92 |
| 13739 | 220 | 0.6 | <0.5 | 105 | 236 | 7.0 | 1.5 | 118 |
| 13740 | 210 | 0.6 | <0.5 | 100 | 220 | 6.5 | 1.0 | 116 |
| 13741 | 266 | 0.4 | <0.5 | 135 | 1150 | 8.5 | 1.5 | 202 |
| 13742 | 275 | 0.4 | <0.5 | 165 | 674 | 13.5 | 1.5 | 280 |
| 13743 | 448 | 0.7 | <0.5 | 965 | 1180 | 26.0 | 0.5 | 486 |
| 13744 | 275 | 1.2 | <0.5 | 1170 | 578 | 13.0 | 2.0 | 760 |
| 13745 | 175 | 0.3 | <0.5 | 80 | 74 | 3.5 | 1.0 | 78 |
| 13746 | 276 | 0.6 | <0.5 | 1610 | 1690 | 11.0 | 2.5 | 558 |
| 13747 | 234 | 0.3 | <0.5 | 530 | 354 | 6.0 | 1.0 | 236 |
| 13748 | 305 | 0.2 | <0.5 | 115 | 226 | 10.0 | 0.5 | 186 |
| 13749 | 391 | 0.5 | <0.5 | 210 | 128 | 22.5 | 0.5 | 152 |
| 13750 | 374 | 0.5 | <0.5 | 170 | 24 | 19.5 | 0.5 | 82 |
| 13751 | 382 | 0.4 | <0.5 | 235 | 30 | 13.5 | 0.5 | 42 |
| 13751 Rpt | 376 | 0.3 | <0.5 | 230 | 28 | 13.5 | 0.5 | 42 |
| 13752 | 422 | 0.3 | <0.5 | 40 | 22 | 14.0 | 0.5 | 32 |
| 13753 | 444 | 0.3 | <0.5 | 25 | 20 | 18.5 | 0.5 | 38 |
| 13754 | 380 | 0.3 | <0.5 | 20 | 58 | 12.0 | <0.5 | 26 |
| 13755 | 395 | 0.2 | <0.5 | 15 | 36 | 12.0 | 0.5 | 28 |
| 13756 | 391 | 0.3 | <0.5 | 10 | 12 | 11.0 | <0.5 | 20 |
| 13757 | 379 | 0.3 | <0.5 | 10 | 26 | 12.0 | <0.5 | 26 |
| 13757 Rpt | 371 | 0.2 | <0.5 | 10 | 24 | 11.0 | <0.5 | 24 |
| 13758 | 402 | 0.4 | <0.5 | 10 | 12 | 11.0 | 1.0 | 26 |
| Std Nominal | 118 | 0.3 | <0.5 | <5 | 10 | 12.0 | 3.5 | 8 |
| Determined | 116 | 0.3 | <0.5 | <5 | 10 | 11.5 | 3.5 | 6 |
| 13759 | 379 | 0.3 | <0.5 | 10 | 26 | 10.5 | 0.5 | 26 |
| 13760 | 141 | <0.1 | <0.5 | 450 | 78 | 12.0 | 0.5 | 5050 |
| 13761 | 388 | 0.4 | <0.5 | 15 | 10 | 11.0 | 0.5 | 30 |
| 13762 | 387 | 0.3 | <0.5 | 10 | 12 | 13.0 | 0.5 | 28 |
| 13763 | 374 | 0.3 | <0.5 | 15 | 8 | 13.0 | 1.0 | 28 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 28 of 49

| | Ba ppm | Bi ppm | Cd ppm | Co ppm | Cu ppm | Li ppm | Mo ppm | Ni ppm |
|-----------------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| Detection Limit | 1 | 0.1 | 0.5 | 5 | 2 | 0.5 | 0.5 | 2 |
| 13764 | 368 | 0.2 | <0.5 | 15 | 12 | 10.5 | 1.0 | 22 |
| 13764 Rpt | 375 | 0.2 | <0.5 | 20 | 12 | 11.0 | 1.0 | 20 |
| 13765 | 433 | 0.5 | <0.5 | 60 | 4 | 17.5 | 1.0 | 34 |
| 13765 Rpt | 422 | 0.5 | <0.5 | 60 | 4 | 16.5 | 1.0 | 32 |
| 13766 | 296 | 0.2 | <0.5 | 110 | 12 | 16.0 | <0.5 | 38 |
| 13767 | 658 | 0.6 | <0.5 | 480 | 52 | 26.0 | 2.5 | 66 |
| 13768 | 622 | <0.1 | <0.5 | 185 | 28 | 15.0 | 0.5 | 36 |
| 13769 | 586 | <0.1 | <0.5 | 135 | 8 | 17.5 | <0.5 | 38 |
| Std Nominal | 132 | 3.0 | 9.0 | 45 | 1500 | 9.5 | 67.0 | 74 |
| Determined | 138 | 2.8 | 9.0 | 45 | 1540 | 10.0 | 66.5 | 74 |
| 13770 | 683 | <0.1 | <0.5 | 100 | 6 | 17.0 | 1.0 | 32 |
| 149399 | 654 | 0.2 | <0.5 | 300 | 12 | 18.5 | 1.5 | 60 |
| 149400 | 682 | 0.2 | <0.5 | 300 | 18 | 18.5 | 1.5 | 74 |
| 149401 | 635 | 0.3 | <0.5 | 200 | 66 | 24.0 | 0.5 | 44 |
| 149402 | 590 | 0.2 | <0.5 | 75 | 28 | 30.0 | <0.5 | 58 |
| 149403 | 509 | 0.2 | <0.5 | 115 | 24 | 44.0 | <0.5 | 90 |
| 149404 | 647 | 0.9 | <0.5 | 205 | 18 | 34.0 | 0.5 | 120 |
| 149405 | 736 | 0.5 | <0.5 | 260 | 12 | 43.0 | 1.5 | 138 |
| 13796 | 740 | 0.7 | <0.5 | 210 | 32 | 22.5 | 3.0 | 118 |
| 13797 | 642 | 0.8 | <0.5 | 190 | 8 | 29.0 | 2.0 | 120 |
| 13798 | 765 | 1.5 | 0.5 | 180 | 4 | 28.5 | 2.0 | 110 |
| 13799 | 730 | 2.2 | <0.5 | 290 | 56 | 29.0 | 1.0 | 160 |
| 13800 | 18 | 50.4 | <0.5 | 2500 | 3.24% | 10.5 | 11.5 | 120 |
| 13801 | 741 | 2.8 | <0.5 | 230 | 44 | 29.5 | 1.5 | 152 |
| 13802 | 760 | 2.8 | <0.5 | 190 | 76 | 26.5 | 2.5 | 114 |
| 13803 | 588 | 2.2 | <0.5 | 120 | 156 | 22.5 | 1.5 | 72 |
| 13804 | 806 | 0.4 | <0.5 | 270 | 218 | 29.5 | 0.5 | 162 |
| 13805 | 896 | 0.1 | <0.5 | 300 | 2780 | 27.0 | 1.0 | 224 |
| 13806 | 248 | 0.1 | <0.5 | 720 | 2210 | 11.0 | 2.5 | 402 |
| 13807 | 382 | 0.2 | <0.5 | 1030 | 1140 | 11.0 | 3.0 | 538 |
| 13808 | 687 | 0.4 | 1.0 | 1530 | 1790 | 13.5 | 2.0 | 780 |
| Std Nominal | <1 | <0.1 | <0.5 | 5 | 4 | 2.0 | <0.5 | 252 |
| Determined | 2 | <0.1 | <0.5 | <5 | 4 | 2.0 | <0.5 | 254 |
| 13809 | 439 | 0.1 | <0.5 | 135 | 1140 | 23.5 | <0.5 | 102 |
| 13810 | 684 | 0.4 | <0.5 | 1080 | 3620 | 24.0 | 1.5 | 622 |
| 13810 Rpt | 709 | 0.5 | 0.5 | 1140 | 3750 | 26.0 | 1.5 | 640 |
| 149406 | 1050 | 0.4 | <0.5 | 80 | 216 | 24.0 | 1.5 | 68 |
| 149407 | 796 | 1.1 | <0.5 | 65 | 16 | 26.0 | 3.0 | 54 |
| 149408 | 633 | 1.2 | <0.5 | 190 | 70 | 24.5 | 2.5 | 142 |
| 149409 | 591 | 0.4 | <0.5 | 85 | 50 | 30.0 | 2.0 | 92 |
| 13828 | 533 | <0.1 | <0.5 | 40 | 14 | 23.5 | 1.0 | 46 |
| 13829 | 378 | <0.1 | <0.5 | 45 | 26 | 18.0 | 1.0 | 46 |
| 13830 | 201 | <0.1 | <0.5 | 50 | 178 | 9.0 | 0.5 | 32 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 29 of 49

| | Ba ppm | Bi ppm | Cd ppm | Co ppm | Cu ppm | Li ppm | Mo ppm | Ni ppm |
|-----------------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| Detection Limit | 1 | 0.1 | 0.5 | 5 | 2 | 0.5 | 0.5 | 2 |
| 13831 | 118 | <0.1 | <0.5 | 30 | 376 | 10.5 | 0.5 | 24 |
| 13834 | 1750 | 1.2 | 1.5 | 2.27% | 4070 | 16.0 | 55.5 | 1270 |
| 13835 | 1330 | 3.5 | <0.5 | 820 | 1540 | 32.5 | 4.5 | 880 |
| 13836 | 1610 | 1.4 | 0.5 | 2390 | 1790 | 6.5 | 10.0 | 760 |
| 13837 | 1370 | 0.5 | <0.5 | 955 | 4910 | 19.0 | 3.5 | 1610 |
| 13838 | 1010 | 4.2 | <0.5 | 670 | 3060 | 31.5 | 3.0 | 1060 |
| 13838 Rpt | 1010 | 4.1 | <0.5 | 660 | 3050 | 32.5 | 3.0 | 1070 |
| 13839 | 724 | 2.4 | <0.5 | 275 | 3770 | 40.0 | 1.0 | 642 |
| 13840 | 724 | 2.3 | <0.5 | 270 | 3820 | 37.5 | 1.0 | 658 |
| 13841 | 774 | 1.5 | <0.5 | 350 | 3390 | 31.0 | 3.0 | 532 |
| 13842 | 988 | 3.9 | <0.5 | 1570 | 986 | 12.0 | 4.0 | 514 |
| 13843 | 1010 | 2.4 | <0.5 | 1520 | 672 | 12.5 | 4.0 | 488 |
| Std Nominal | 2 | <0.1 | <0.5 | 210 | 10 | 4.0 | 1.0 | 2000 |
| Determined | 3 | <0.1 | <0.5 | 210 | 8 | 4.5 | 1.0 | 2010 |
| 13844 | 978 | 1.3 | <0.5 | 510 | 560 | 17.0 | 2.0 | 502 |
| 13845 | 957 | 1.9 | <0.5 | 605 | 794 | 14.0 | 1.5 | 524 |
| 13845 Rpt | 928 | 1.9 | <0.5 | 610 | 786 | 13.0 | 1.5 | 540 |
| 13846 | 883 | 2.8 | <0.5 | 495 | 888 | 10.5 | 1.0 | 552 |
| 13847 | 961 | 3.1 | 1.0 | 320 | 936 | 7.0 | 1.0 | 474 |
| 13848 | 933 | 3.5 | <0.5 | 335 | 802 | 5.5 | 1.0 | 360 |
| 13849 | 1090 | 3.0 | <0.5 | 3580 | 1280 | 7.0 | 3.5 | 450 |
| 13850 | 427 | 0.3 | <0.5 | 155 | 930 | 9.5 | 2.0 | 176 |
| 13851 | 1030 | 0.7 | <0.5 | 365 | 818 | 20.5 | 1.5 | 580 |
| 13852 | 704 | 0.9 | <0.5 | 355 | 800 | 20.0 | 1.5 | 682 |
| 13853 | 663 | 1.3 | 2.5 | 4730 | 2560 | 18.0 | 8.5 | 2630 |
| 13854 | 373 | 0.9 | <0.5 | 530 | 428 | 7.0 | 1.5 | 650 |
| 13855 | 387 | 0.6 | <0.5 | 505 | 814 | 6.0 | 1.5 | 748 |
| 13856 | 403 | 0.3 | <0.5 | 350 | 480 | 5.0 | 1.5 | 336 |
| 13857 | 595 | 1.2 | <0.5 | 1890 | 578 | 23.0 | 1.0 | 1150 |
| 13858 | 577 | 0.5 | 0.5 | 1450 | 500 | 23.5 | 1.0 | 962 |
| 13859 | 669 | 0.4 | <0.5 | 1060 | 234 | 26.5 | 1.5 | 760 |
| 13859 Rpt | 623 | 0.4 | <0.5 | 1060 | 232 | 24.0 | 1.5 | 762 |
| 13860 | 139 | <0.1 | <0.5 | 450 | 80 | 12.0 | 0.5 | 5040 |
| 13861 | 617 | 0.3 | <0.5 | 940 | 268 | 20.5 | 1.0 | 598 |
| 13862 | 692 | 2.1 | <0.5 | 3880 | 166 | 19.5 | 2.5 | 2170 |
| 13862 Rpt | 705 | 2.2 | <0.5 | 3740 | 170 | 20.5 | 2.5 | 2070 |
| 13863 | 708 | 1.5 | <0.5 | 2770 | 202 | 17.5 | 2.0 | 1590 |
| 13864 | 689 | 1.0 | 1.0 | 6670 | 716 | 20.0 | 4.5 | 3770 |
| 13865 | 693 | 0.8 | <0.5 | 3430 | 744 | 20.0 | 2.0 | 2000 |
| 13866 | 594 | 0.5 | <0.5 | 1550 | 266 | 19.5 | 1.0 | 916 |
| 13867 | 579 | 1.5 | <0.5 | 2160 | 232 | 18.0 | 1.0 | 1190 |
| 13868 | 639 | 0.3 | <0.5 | 440 | 140 | 23.5 | 0.5 | 264 |
| 13869 | 734 | 0.5 | <0.5 | 445 | 100 | 24.0 | 0.5 | 230 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 30 of 49

| | Ba ppm | Bi ppm | Cd ppm | Co ppm | Cu ppm | Li ppm | Mo ppm | Ni ppm |
|-----------------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| Detection Limit | 1 | 0.1 | 0.5 | 5 | 2 | 0.5 | 0.5 | 2 |
| 13870 | 764 | 1.0 | <0.5 | 1160 | 980 | 23.5 | 1.0 | 494 |
| 13871 | 752 | 1.5 | <0.5 | 1450 | 78 | 22.5 | 2.0 | 750 |
| 13872 | 691 | 0.6 | <0.5 | 535 | 192 | 19.0 | 1.0 | 298 |
| 13873 | 585 | 0.1 | <0.5 | 270 | 532 | 59.0 | 0.5 | 100 |
| 149410 | 990 | 0.2 | <0.5 | 165 | 48 | 20.5 | 0.5 | 94 |
| Std Nominal | 14 | 0.1 | <0.5 | 95 | 1760 | 3.0 | <0.5 | 1020 |
| Determined | 15 | 0.1 | <0.5 | 95 | 1760 | 3.0 | <0.5 | 1020 |
| 149411 | 653 | 0.6 | <0.5 | 210 | 26 | 18.5 | 0.5 | 134 |
| 13883 | 603 | <0.1 | <0.5 | 70 | 32 | 20.0 | 0.5 | 44 |
| 13883 Rpt | 626 | <0.1 | <0.5 | 70 | 30 | 20.5 | 0.5 | 46 |
| 13884 | 675 | <0.1 | <0.5 | 80 | 24 | 22.5 | <0.5 | 48 |
| 13885 | 800 | <0.1 | <0.5 | 40 | 2 | 16.0 | 0.5 | 40 |
| 13886 | 777 | 0.1 | <0.5 | 55 | 6 | 23.0 | 0.5 | 54 |
| 13887 | 541 | <0.1 | <0.5 | 40 | 10 | 21.0 | 0.5 | 38 |
| 13888 | 206 | <0.1 | <0.5 | 30 | 6 | 11.0 | 1.0 | 24 |
| 149412 | 370 | 0.2 | <0.5 | 35 | 2 | 17.0 | 0.5 | 24 |
| 13893 | 658 | 0.3 | <0.5 | 25 | 12 | 19.0 | 1.0 | 32 |
| 13894 | 381 | 0.3 | <0.5 | 20 | 2 | 18.0 | 0.5 | 24 |
| Std Nominal | 38 | <0.1 | <0.5 | 750 | 26 | 3.0 | 1.0 | 1.48% |
| Determined | 40 | <0.1 | <0.5 | 745 | 24 | 3.5 | 1.0 | 1.47% |
| 13895 | 382 | 0.2 | <0.5 | 20 | 2 | 14.5 | 1.0 | 26 |
| 13896 | 399 | 0.3 | <0.5 | 15 | 4 | 14.0 | 1.0 | 32 |
| 13897 | 397 | 0.3 | <0.5 | 15 | 4 | 16.0 | 0.5 | 30 |
| 13898 | 389 | 0.3 | <0.5 | 15 | 2 | 12.5 | 0.5 | 28 |
| 13899 | 371 | 0.3 | <0.5 | 20 | <2 | 13.0 | 0.5 | 24 |
| 13899 Rpt | 367 | 0.3 | <0.5 | 15 | <2 | 13.0 | 0.5 | 26 |
| 13900 | 18 | 48.1 | <0.5 | 2430 | 3.19% | 11.0 | 11.0 | 122 |
| 13901 | 377 | 0.3 | <0.5 | 15 | 2 | 13.0 | 1.0 | 20 |
| 13902 | 350 | 0.4 | <0.5 | 40 | 24 | 14.0 | 1.0 | 20 |
| 13903 | 382 | 0.3 | <0.5 | 50 | 38 | 13.5 | 0.5 | 26 |
| 13904 | 357 | 0.1 | <0.5 | 25 | 6 | 14.0 | 0.5 | 26 |
| 13905 | 266 | 1.5 | <0.5 | 20 | 36 | 8.5 | 21.5 | 14 |
| 13906 | 268 | 0.5 | <0.5 | 20 | 112 | 7.5 | 9.0 | 14 |
| 13906 Rpt | 258 | 0.6 | <0.5 | 20 | 110 | 7.5 | 8.5 | 16 |
| 13907 | 489 | 0.5 | <0.5 | 25 | 10 | 14.5 | 3.0 | 40 |
| 13908 | 394 | 0.2 | <0.5 | 20 | 4 | 15.5 | 1.0 | 26 |
| 13909 | 346 | 0.4 | <0.5 | 150 | 12 | 14.5 | 1.0 | 28 |
| 13910 | 375 | 0.4 | <0.5 | 70 | 10 | 16.5 | 1.5 | 24 |
| 13911 | 187 | 2.3 | <0.5 | 20 | 6 | 6.0 | 65.0 | 10 |
| 13912 | 229 | 0.8 | <0.5 | 30 | 4 | 9.0 | 20.5 | 14 |
| 13913 | 467 | 0.3 | <0.5 | 40 | 40 | 16.0 | 5.0 | 18 |
| 149413 | 407 | 0.2 | <0.5 | 80 | 4 | 25.5 | 1.5 | 28 |
| 149414 | 373 | 0.3 | <0.5 | 50 | 26 | 49.0 | 1.0 | 50 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 31 of 49

| | Ba ppm | Bi ppm | Cd ppm | Co ppm | Cu ppm | Li ppm | Mo ppm | Ni ppm |
|-----------------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| Detection Limit | 1 | 0.1 | 0.5 | 5 | 2 | 0.5 | 0.5 | 2 |
| 149415 | 297 | 0.5 | <0.5 | 60 | 8 | 39.5 | 0.5 | 38 |
| 149415 Rpt | 298 | 0.5 | <0.5 | 60 | 10 | 39.0 | 0.5 | 36 |
| 149416 | 316 | 0.1 | <0.5 | 60 | 10 | 32.5 | 0.5 | 26 |
| 149417 | 291 | <0.1 | <0.5 | 70 | 98 | 43.5 | <0.5 | 92 |
| 149418 | 280 | 0.1 | <0.5 | 45 | 4 | 38.5 | 0.5 | 32 |
| 13938 | 332 | 0.5 | <0.5 | 1440 | 1870 | 34.0 | 10.0 | 236 |
| 13939 | 668 | 0.5 | <0.5 | 1930 | 1780 | 28.0 | 9.0 | 208 |
| 13940 | 584 | 0.5 | <0.5 | 1830 | 1840 | 28.0 | 9.5 | 210 |
| 13941 | 978 | 1.2 | <0.5 | 580 | 1190 | 14.5 | 5.0 | 266 |
| 13942 | 956 | 1.5 | <0.5 | 600 | 1510 | 9.5 | 13.5 | 296 |
| 13943 | 728 | 1.5 | <0.5 | 130 | 864 | 7.0 | 1.0 | 162 |
| 13944 | 671 | 1.1 | <0.5 | 540 | 1810 | 8.5 | 7.5 | 396 |
| 13945 | 749 | 0.7 | <0.5 | 780 | 1640 | 15.5 | 4.0 | 336 |
| 13945 Rpt | 772 | 0.7 | <0.5 | 790 | 1650 | 16.5 | 4.0 | 332 |
| 13946 | 641 | 0.6 | <0.5 | 210 | 870 | 15.5 | 1.0 | 198 |
| 13947 | 722 | 0.4 | <0.5 | 140 | 464 | 15.5 | 1.5 | 142 |
| 13948 | 756 | 0.7 | <0.5 | 190 | 636 | 13.0 | 1.5 | 196 |
| 13949 | 833 | 0.7 | <0.5 | 265 | 956 | 16.0 | 3.0 | 296 |
| Std Nominal | 17 | 0.9 | <0.5 | 285 | 876 | 11.0 | 1.0 | 1.41% |
| Determined | 18 | 0.9 | <0.5 | 280 | 882 | 11.5 | 1.0 | 1.40% |
| 13950 | 753 | 0.9 | <0.5 | 190 | 456 | 13.5 | 1.5 | 228 |
| 13951 | 711 | 0.5 | <0.5 | 145 | 460 | 14.5 | 1.0 | 238 |
| 13952 | 667 | 0.5 | <0.5 | 135 | 630 | 17.5 | 3.5 | 218 |
| 13953 | 639 | 0.4 | <0.5 | 140 | 604 | 16.0 | 5.0 | 198 |
| 13954 | 683 | 0.7 | <0.5 | 200 | 1170 | 17.5 | 5.0 | 254 |
| 13955 | 825 | 0.4 | <0.5 | 165 | 1910 | 22.5 | 2.5 | 258 |
| 13956 | 769 | 0.4 | <0.5 | 140 | 1260 | 17.5 | 8.0 | 214 |
| 13957 | 854 | 0.5 | <0.5 | 125 | 2280 | 18.0 | 6.0 | 208 |
| 13958 | 812 | 0.4 | <0.5 | 100 | 836 | 18.0 | 2.5 | 170 |
| 13959 | 843 | 0.6 | <0.5 | 80 | 2760 | 19.5 | 1.0 | 172 |
| 13959 Rpt | 819 | 0.5 | <0.5 | 85 | 2700 | 18.5 | 1.0 | 180 |
| 13960 | 134 | <0.1 | <0.5 | 445 | 76 | 11.0 | 0.5 | 5020 |
| 13961 | 835 | 0.3 | <0.5 | 110 | 1260 | 18.5 | 1.0 | 210 |
| 13962 | 833 | 0.6 | <0.5 | 110 | 2420 | 18.0 | 1.5 | 220 |
| 13963 | 796 | 0.7 | <0.5 | 100 | 1920 | 17.5 | 2.0 | 206 |
| 13964 | 616 | 0.9 | <0.5 | 95 | 1520 | 15.0 | 1.5 | 194 |
| Std Nominal | 102 | <0.1 | <0.5 | 60 | 14 | 6.0 | 1.0 | 120 |
| Determined | 100 | <0.1 | <0.5 | 60 | 12 | 6.0 | 1.0 | 120 |
| 13965 | 970 | 0.6 | <0.5 | 80 | 660 | 13.0 | 1.0 | 158 |
| 13966 | 862 | 0.9 | <0.5 | 105 | 2780 | 12.5 | 2.0 | 184 |
| 13967 | 738 | 0.8 | <0.5 | 90 | 2430 | 14.5 | 1.5 | 174 |
| 13968 | 752 | 1.1 | <0.5 | 95 | 1220 | 17.0 | 2.5 | 170 |
| 13969 | 768 | 0.4 | <0.5 | 65 | 294 | 16.0 | 1.0 | 110 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 AustraliaTelephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 32 of 49

| | Ba ppm | Bi ppm | Cd ppm | Co ppm | Cu ppm | Li ppm | Mo ppm | Ni ppm |
|-----------------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| Detection Limit | 1 | 0.1 | 0.5 | 5 | 2 | 0.5 | 0.5 | 2 |
| 13970 | 804 | 0.5 | <0.5 | 100 | 396 | 14.0 | 2.5 | 108 |
| 13971 | 642 | 0.5 | <0.5 | 80 | 356 | 13.5 | 1.5 | 92 |
| 13972 | 467 | 0.8 | <0.5 | 310 | 560 | 14.0 | 3.5 | 320 |
| 13973 | 450 | 1.1 | <0.5 | 785 | 950 | 9.5 | 2.0 | 474 |
| 13974 | 654 | 1.1 | <0.5 | 1290 | 1770 | 6.5 | 7.0 | 926 |
| 13974 Rpt | 633 | 1.1 | <0.5 | 1290 | 1740 | 7.0 | 7.0 | 916 |
| 13975 | 671 | 2.1 | <0.5 | 280 | 704 | 8.0 | 6.0 | 390 |
| 13976 | 618 | 1.7 | 0.5 | 250 | 1220 | 7.0 | 4.5 | 282 |
| 13977 | 669 | 1.2 | 2.0 | 465 | 794 | 9.5 | 17.0 | 380 |
| 13978 | 836 | 2.3 | 1.0 | 4910 | 608 | 9.5 | 5.0 | 1070 |
| Std Nominal | 239 | <0.1 | <0.5 | 155 | 316 | 7.5 | 2.0 | 6930 |
| Determined | 235 | <0.1 | <0.5 | 155 | 314 | 7.5 | 1.5 | 6910 |
| 13979 | 823 | 1.1 | 0.5 | 760 | 436 | 8.0 | 2.5 | 446 |
| 13980 | 18 | 49.3 | <0.5 | 2480 | 3.24% | 11.0 | 10.5 | 116 |
| 13980 Rpt | 17 | 50.2 | <0.5 | 2480 | 3.21% | 10.5 | 10.5 | 118 |
| 13981 | 572 | 1.0 | 0.5 | 675 | 356 | 7.5 | 3.0 | 592 |
| 13982 | 808 | 0.6 | 0.5 | 670 | 102 | 25.0 | 4.0 | 496 |
| 13983 | 477 | 0.2 | <0.5 | 170 | 56 | 20.5 | 1.0 | 108 |
| 13984 | 691 | <0.1 | <0.5 | 135 | 36 | 31.0 | 0.5 | 108 |
| 13985 | 676 | <0.1 | <0.5 | 105 | 30 | 31.5 | 1.0 | 88 |
| 13986 | 456 | 0.1 | <0.5 | 65 | 12 | 17.5 | 0.5 | 46 |
| 13987 | 468 | 0.2 | <0.5 | 80 | 4 | 19.5 | <0.5 | 38 |
| 13988 | 594 | 0.1 | <0.5 | 190 | 2 | 23.5 | 0.5 | 42 |
| 13989 | 486 | 0.3 | <0.5 | 625 | 6 | 21.5 | <0.5 | 50 |
| 13990 | 437 | 0.1 | <0.5 | 120 | 6 | 23.5 | <0.5 | 38 |
| 13990 Rpt | 466 | 0.1 | <0.5 | 120 | 6 | 24.0 | <0.5 | 40 |
| 13991 | 565 | <0.1 | <0.5 | 45 | 2 | 20.0 | <0.5 | 34 |
| 13992 | 462 | 0.1 | <0.5 | 25 | 4 | 18.0 | <0.5 | 40 |
| 13993 | 485 | <0.1 | <0.5 | 25 | 6 | 19.0 | <0.5 | 38 |
| 13994 | 515 | <0.1 | <0.5 | 30 | 4 | 20.0 | <0.5 | 32 |
| 13995 | 425 | 0.1 | <0.5 | 20 | 6 | 14.0 | 0.5 | 28 |
| 13996 | 429 | 0.1 | <0.5 | 15 | 6 | 14.0 | 0.5 | 26 |
| 13997 | 440 | 0.1 | <0.5 | 10 | 4 | 17.0 | <0.5 | 26 |
| 149419 | 576 | <0.1 | <0.5 | 15 | 10 | 15.0 | <0.5 | 28 |
| 149420 | 133 | <0.1 | <0.5 | 455 | 76 | 12.0 | 0.5 | 4980 |
| 149421 | 422 | <0.1 | <0.5 | 15 | 6 | 13.0 | 0.5 | 26 |
| Std Nominal | 118 | 0.3 | <0.5 | <5 | 10 | 12.0 | 3.5 | 8 |
| Determined | 117 | 0.3 | <0.5 | <5 | 12 | 12.5 | 3.5 | 8 |
| 149422 | 397 | 0.1 | <0.5 | 35 | 4 | 13.0 | 0.5 | 20 |
| 14011 | 313 | 0.1 | <0.5 | 25 | 8 | 9.5 | 1.0 | 16 |
| 14012 | 588 | 0.2 | <0.5 | 30 | 8 | 11.5 | 1.0 | 16 |
| 14013 | 383 | 0.3 | <0.5 | 55 | 4 | 13.0 | 0.5 | 26 |
| 14014 | 411 | <0.1 | <0.5 | 20 | 6 | 12.5 | 0.5 | 24 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 33 of 49

| | Ba ppm | Bi ppm | Cd ppm | Co ppm | Cu ppm | Li ppm | Mo ppm | Ni ppm |
|-----------------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| Detection Limit | 1 | 0.1 | 0.5 | 5 | 2 | 0.5 | 0.5 | 2 |
| 14014 Rpt | 389 | <0.1 | <0.5 | 20 | 4 | 13.5 | <0.5 | 26 |
| 14015 | 392 | 0.1 | <0.5 | 40 | 8 | 16.0 | <0.5 | 28 |
| 14016 | 355 | 0.5 | <0.5 | 120 | 6 | 15.0 | 0.5 | 26 |
| 14016 Rpt | 379 | 0.5 | <0.5 | 125 | 8 | 15.0 | 0.5 | 26 |
| 14017 | 364 | 0.4 | <0.5 | 120 | 10 | 15.0 | 0.5 | 28 |
| 14018 | 293 | 0.3 | <0.5 | 20 | 8 | 12.0 | 1.0 | 16 |
| 14019 | 109 | 0.7 | <0.5 | 20 | 8 | 9.0 | 10.5 | 14 |
| 14020 | 126 | 0.8 | <0.5 | 20 | 18 | 11.0 | 12.0 | 12 |
| 14021 | 142 | 0.7 | <0.5 | 15 | 8 | 6.5 | 12.0 | 6 |
| 149423 | 411 | 0.3 | <0.5 | 50 | 1230 | 10.5 | 1.0 | 24 |
| 149424 | 331 | 0.2 | <0.5 | 35 | 46 | 14.0 | 1.5 | 12 |
| 149425 | 308 | 0.3 | <0.5 | 30 | 20 | 16.5 | 1.0 | 18 |
| 149426 | 253 | 0.2 | <0.5 | 20 | 4 | 13.0 | 1.0 | 12 |
| 149427 | 264 | 0.3 | <0.5 | 30 | 8 | 16.0 | 0.5 | 16 |
| 14044 | 212 | 0.8 | <0.5 | 1570 | 1730 | 30.5 | 11.5 | 334 |
| 14045 | 227 | 0.6 | <0.5 | 1090 | 2110 | 21.0 | 9.5 | 266 |
| 14046 | 505 | 0.5 | <0.5 | 880 | 1970 | 15.5 | 16.5 | 802 |
| 14047 | 838 | 0.5 | 0.5 | 6220 | 2020 | 20.5 | 10.5 | 2910 |
| 14048 | 947 | 0.6 | 0.5 | 5530 | 1960 | 16.0 | 10.5 | 2380 |
| 14049 | 868 | 0.4 | 0.5 | 4890 | 4940 | 16.5 | 8.0 | 2480 |
| 14049 Rpt | 912 | 0.4 | 0.5 | 4770 | 4930 | 17.0 | 7.5 | 2450 |
| 14050 | 916 | 0.5 | <0.5 | 2160 | 2820 | 12.5 | 4.0 | 628 |
| 14051 | 1050 | 0.6 | <0.5 | 2690 | 3550 | 10.5 | 10.0 | 678 |
| 14052 | 1140 | 0.8 | <0.5 | 950 | 1040 | 9.0 | 3.5 | 242 |
| 14053 | 1000 | 0.2 | <0.5 | 930 | 804 | 5.0 | 3.0 | 186 |
| Std Nominal | 132 | 3.0 | 9.0 | 45 | 1500 | 9.5 | 67.0 | 74 |
| Determined | 132 | 2.9 | 9.0 | 45 | 1520 | 9.5 | 66.5 | 72 |
| 14054 | 1030 | 0.3 | <0.5 | 1460 | 924 | 7.0 | 4.5 | 204 |
| 14055 | 1560 | 0.5 | <0.5 | 840 | 892 | 12.0 | 3.5 | 256 |
| 14056 | 1150 | 0.2 | <0.5 | 330 | 416 | 7.5 | 2.5 | 132 |
| 14057 | 957 | 0.3 | <0.5 | 150 | 268 | 7.0 | 1.5 | 94 |
| 14058 | 904 | 0.4 | <0.5 | 475 | 494 | 7.0 | 2.0 | 140 |
| 14059 | 1020 | 3.3 | <0.5 | 830 | 612 | 7.0 | 4.0 | 256 |
| 14061 | 884 | 1.8 | <0.5 | 675 | 1.16% | 7.5 | 3.5 | 752 |
| 14062 | 800 | 0.8 | <0.5 | 480 | 2110 | 7.0 | 1.5 | 250 |
| 14062 Rpt | 822 | 0.8 | <0.5 | 490 | 2140 | 7.5 | 2.0 | 256 |
| 14063 | 711 | 0.7 | <0.5 | 900 | 1340 | 18.0 | 3.0 | 490 |
| 14064 | 836 | 1.8 | <0.5 | 1080 | 744 | 6.5 | 2.5 | 224 |
| 14065 | 749 | 4.1 | <0.5 | 2390 | 926 | 6.0 | 4.0 | 388 |
| 14066 | 666 | 2.1 | <0.5 | 3800 | 1190 | 4.5 | 4.5 | 640 |
| 14067 | 712 | 3.6 | <0.5 | 580 | 708 | 6.5 | 1.5 | 246 |
| 14068 | 744 | 2.6 | <0.5 | 300 | 1250 | 12.0 | 1.0 | 422 |
| 14069 | 739 | 1.5 | <0.5 | 185 | 1780 | 18.0 | 0.5 | 312 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 34 of 49

| | Ba ppm | Bi ppm | Cd ppm | Co ppm | Cu ppm | Li ppm | Mo ppm | Ni ppm |
|-----------------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| Detection Limit | 1 | 0.1 | 0.5 | 5 | 2 | 0.5 | 0.5 | 2 |
| 14070 | 959 | 1.4 | <0.5 | 310 | 996 | 18.5 | 0.5 | 470 |
| 14071 | 926 | 2.9 | <0.5 | 210 | 470 | 18.0 | 0.5 | 344 |
| 14072 | 1010 | 1.9 | <0.5 | 210 | 470 | 8.0 | 0.5 | 294 |
| 14073 | 652 | 2.7 | <0.5 | 370 | 766 | 9.0 | 1.0 | 566 |
| 14074 | 721 | 2.3 | <0.5 | 975 | 1280 | 6.5 | 1.0 | 842 |
| 14074 Rpt | 694 | 2.4 | <0.5 | 960 | 1300 | 6.5 | 1.0 | 858 |
| 14075 | 562 | 1.1 | <0.5 | 740 | 3820 | 13.0 | 1.0 | 682 |
| 14076 | 794 | 0.8 | <0.5 | 525 | 1460 | 11.5 | 0.5 | 514 |
| 14077 | 747 | 0.3 | <0.5 | 395 | 1010 | 18.0 | <0.5 | 568 |
| 14078 | 763 | 1.5 | 1.0 | 3700 | 4360 | 14.0 | 6.0 | 2900 |
| 14079 | 864 | 0.7 | <0.5 | 7470 | 4830 | 12.0 | 7.5 | 5330 |
| 14080 | 135 | 0.1 | <0.5 | 460 | 80 | 11.0 | 1.0 | 5050 |
| 14084 | 643 | 0.3 | 1.5 | 6000 | 4420 | 12.5 | 18.0 | 7640 |
| 14086 | 681 | 0.2 | 4.0 | 2.33% | 4500 | 16.5 | 129 | 1.01% |
| 149428 | 529 | 0.2 | <0.5 | 1240 | 264 | 22.5 | 6.5 | 540 |
| 149428 Rpt | 552 | 0.2 | <0.5 | 1220 | 262 | 21.5 | 5.0 | 534 |
| 149429 | 519 | <0.1 | <0.5 | 540 | 132 | 19.5 | 3.5 | 282 |
| 149430 | 490 | <0.1 | <0.5 | 310 | 82 | 20.0 | 2.0 | 178 |
| 149431 | 499 | <0.1 | <0.5 | 145 | 40 | 18.5 | 1.0 | 94 |
| 149432 | 374 | <0.1 | <0.5 | 95 | 24 | 19.5 | 0.5 | 66 |
| 149433 | 406 | <0.1 | <0.5 | 65 | 22 | 15.0 | 1.0 | 44 |
| 149434 | 416 | <0.1 | <0.5 | 60 | 12 | 14.0 | 2.5 | 44 |
| Std Nominal | <1 | <0.1 | <0.5 | 5 | 4 | 2.0 | <0.5 | 252 |
| Determined | 2 | <0.1 | <0.5 | 5 | 4 | 2.0 | <0.5 | 256 |
| 149435 | 432 | <0.1 | <0.5 | 40 | 12 | 18.0 | 0.5 | 42 |
| 149436 | 702 | 0.2 | <0.5 | 55 | 10 | 25.0 | 1.5 | 52 |
| 149437 | 804 | 0.4 | <0.5 | 170 | 76 | 16.0 | 1.0 | 102 |
| 149438 | 597 | 0.5 | <0.5 | 80 | 12 | 31.5 | 2.0 | 90 |
| 149439 | 399 | 0.2 | <0.5 | 50 | 12 | 28.5 | 1.0 | 56 |
| 149440 | 402 | 0.2 | <0.5 | 60 | 14 | 26.0 | 1.0 | 58 |
| Std Nominal | 2 | <0.1 | <0.5 | 210 | 10 | 4.0 | 1.0 | 2000 |
| Determined | 3 | <0.1 | <0.5 | 205 | 8 | 4.0 | 1.0 | 1980 |
| 149441 | 369 | 0.2 | <0.5 | 85 | 152 | 17.0 | 1.0 | 30 |
| 149442 | 510 | 0.2 | <0.5 | 145 | 16 | 26.0 | 0.5 | 44 |
| 149443 | 430 | 0.1 | <0.5 | 40 | 10 | 16.0 | 1.0 | 20 |
| 14148 | 995 | 0.6 | <0.5 | 250 | 1990 | 21.0 | 4.0 | 268 |
| 14149 | 970 | 0.6 | <0.5 | 135 | 2080 | 21.0 | 2.5 | 172 |
| 14150 | 1160 | 0.6 | <0.5 | 260 | 3160 | 18.5 | 4.0 | 200 |
| 14150 Rpt | 1190 | 0.6 | <0.5 | 260 | 3170 | 17.5 | 4.0 | 196 |
| 14151 | 1030 | 0.4 | <0.5 | 610 | 2550 | 8.0 | 2.5 | 384 |
| 14152 | 897 | 0.6 | <0.5 | 860 | 3640 | 18.5 | 3.0 | 396 |
| 14153 | 955 | 0.5 | <0.5 | 350 | 1.55% | 19.5 | 2.5 | 406 |
| 14154 | 1300 | 2.8 | 0.5 | 2600 | 2860 | 9.0 | 7.5 | 346 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 35 of 49

| | Ba ppm | Bi ppm | Cd ppm | Co ppm | Cu ppm | Li ppm | Mo ppm | Ni ppm |
|-----------------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| Detection Limit | 1 | 0.1 | 0.5 | 5 | 2 | 0.5 | 0.5 | 2 |
| 14155 | 1160 | 3.2 | 1.0 | 2170 | 5290 | 7.5 | 8.0 | 412 |
| 14156 | 779 | 0.9 | <0.5 | 350 | 2290 | 8.0 | 3.0 | 284 |
| 14156 Rpt | 765 | 0.9 | <0.5 | 345 | 2300 | 8.5 | 3.5 | 296 |
| 14157 | 341 | 0.6 | <0.5 | 845 | 1320 | 7.5 | 2.0 | 154 |
| 14158 | 358 | 0.9 | <0.5 | 490 | 1360 | 14.5 | 1.0 | 258 |
| 14159 | 575 | 1.1 | <0.5 | 410 | 1500 | 19.0 | 1.5 | 376 |
| 14160 | 573 | 1.1 | <0.5 | 365 | 1400 | 20.0 | 1.5 | 370 |
| 14161 | 564 | 1.1 | <0.5 | 180 | 4020 | 20.5 | 1.0 | 442 |
| 13516 | 203 | 1.1 | <0.5 | 550 | 594 | 36.5 | 11.0 | 214 |
| 13517 | 563 | 0.6 | <0.5 | 320 | 590 | 31.0 | 6.5 | 116 |
| 13518 | 1270 | 0.3 | <0.5 | 100 | 130 | 12.0 | 3.5 | 110 |
| 13518 Rpt | 1320 | 0.3 | <0.5 | 100 | 126 | 12.0 | 4.0 | 110 |
| 13519 | 1030 | 0.3 | <0.5 | 80 | 82 | 22.0 | 3.5 | 106 |
| 13520 | 19 | 50.7 | <0.5 | 2400 | 3.19% | 10.0 | 10.0 | 118 |
| 13521 | 986 | 0.7 | <0.5 | 160 | 348 | 24.0 | 1.0 | 102 |
| 13522 | 1220 | 0.8 | <0.5 | 65 | 526 | 4.5 | 2.0 | 36 |
| 13523 | 1080 | 0.7 | <0.5 | 115 | 676 | 8.5 | 2.0 | 74 |
| 13524 | 1070 | 0.7 | <0.5 | 115 | 592 | 5.0 | 1.5 | 72 |
| 13525 | 1310 | 0.7 | <0.5 | 215 | 1210 | 9.5 | 1.0 | 154 |
| 13526 | 377 | 0.2 | <0.5 | 100 | 280 | 6.0 | 1.5 | 34 |
| 13527 | 243 | <0.1 | <0.5 | 25 | 134 | 5.5 | 1.5 | 24 |
| 13527 Rpt | 246 | <0.1 | <0.5 | 25 | 130 | 5.5 | 1.5 | 26 |
| 13528 | 455 | 0.1 | <0.5 | 75 | 280 | 9.5 | 1.5 | 48 |
| 13529 | 328 | 0.2 | <0.5 | 95 | 594 | 9.5 | 1.5 | 84 |
| 13530 | 680 | 0.9 | <0.5 | 70 | 1270 | 22.0 | 0.5 | 130 |
| 13531 | 343 | 0.8 | <0.5 | 60 | 3380 | 9.0 | 1.0 | 92 |
| 13532 | 598 | 0.9 | <0.5 | 480 | 506 | 7.5 | 1.0 | 138 |
| 13533 | 404 | 0.2 | <0.5 | 165 | 420 | 6.5 | 1.0 | 108 |
| 13534 | 630 | 0.2 | <0.5 | 120 | 408 | 10.0 | 0.5 | 140 |
| Std Nominal | 14 | 0.1 | <0.5 | 95 | 1760 | 3.0 | <0.5 | 1020 |
| Determined | 15 | <0.1 | <0.5 | 95 | 1770 | 2.5 | <0.5 | 1030 |
| 13535 | 628 | 0.4 | <0.5 | 80 | 74 | 22.0 | <0.5 | 64 |
| 13536 | 489 | 0.3 | <0.5 | 125 | 32 | 17.0 | <0.5 | 34 |
| 13588 | 613 | 1.9 | 5.5 | 590 | 352 | 29.5 | 2.5 | 336 |
| 13588 Rpt | 632 | 1.9 | 6.0 | 600 | 366 | 30.5 | 2.0 | 340 |
| 13589 | 798 | 0.9 | <0.5 | 100 | 36 | 23.5 | 2.0 | 72 |
| 13590 | 701 | 1.2 | <0.5 | 415 | 78 | 28.0 | 2.5 | 264 |
| 13591 | 344 | <0.1 | <0.5 | 40 | 68 | 15.0 | <0.5 | 34 |
| 13592 | 488 | 0.1 | <0.5 | 55 | 38 | 18.5 | 0.5 | 48 |
| 13593 | 262 | <0.1 | <0.5 | 35 | 384 | 13.5 | 1.0 | 32 |
| 13593 Rpt | 251 | <0.1 | <0.5 | 30 | 378 | 13.0 | 1.0 | 30 |
| 13594 | 230 | 0.1 | <0.5 | 300 | 866 | 11.5 | 1.5 | 130 |
| 13595 | 764 | 0.3 | <0.5 | 645 | 1790 | 17.0 | 1.0 | 276 |



Reference: u282154 Order Number: NC_003 Page 36 of 49

| | Ba ppm | Bi ppm | Cd ppm | Co ppm | Cu ppm | Li ppm | Mo ppm | Ni ppm |
|-----------------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| Detection Limit | 1 | 0.1 | 0.5 | 5 | 2 | 0.5 | 0.5 | 2 |
| 13596 | 512 | 0.2 | <0.5 | 215 | 38 | 26.0 | <0.5 | 46 |
| 13597 | 659 | 0.9 | <0.5 | 30 | 18 | 24.5 | 5.5 | 34 |
| Std Nominal | 38 | <0.1 | <0.5 | 750 | 26 | 3.0 | 1.0 | 1.48% |
| Determined | 39 | <0.1 | <0.5 | 755 | 24 | 3.0 | 0.5 | 1.47% |
| 13598 | 715 | 0.2 | <0.5 | 30 | 40 | 29.5 | <0.5 | 40 |
| 13599 | 573 | <0.1 | <0.5 | 50 | 30 | 20.0 | 0.5 | 28 |
| 13600 | 139 | <0.1 | <0.5 | 450 | 76 | 11.0 | 0.5 | 4990 |
| 14060 | 17 | 51.0 | <0.5 | 2480 | 3.18% | 10.5 | 10.5 | 122 |
| 14060 Rpt | 16 | 49.9 | <0.5 | 2460 | 3.18% | 10.5 | 10.0 | 120 |
| Std Nominal | 17 | 0.9 | <0.5 | 285 | 876 | 11.0 | 1.0 | 1.41% |
| Determined | 18 | 1.0 | <0.5 | 280 | 888 | 11.5 | 1.0 | 1.43% |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 37 of 49

| | Pb ppm | Zn ppm | U ppm | Th ppm |
|-----------------|-----------|-----------|----------|-----------|
| Detection Limit | 1 | 2 | 0.1 | 0.1 |
| 149389 | 20 | 72 | 4.4 | 11.3 |
| 149390 | 9 | 62 | 6.2 | 11.0 |
| 13630 | 9 | 54 | 7.7 | 14.7 |
| 13631 | 4 | 12 | 1.1 | 4.5 |
| 13631 Rpt | 4 | 12 | 1.1 | 4.9 |
| 13632 | 5 | 12 | 1.6 | 6.5 |
| 13632 Rpt | 5 | 10 | 1.7 | 6.6 |
| 13633 | 5 | 12 | 1.6 | 7.9 |
| 13634 | 5 | 16 | 2.3 | 10.9 |
| 13635 | 12 | 60 | 4.8 | 22.7 |
| 13636 | 4 | 20 | 2.1 | 9.2 |
| 13637 | 5 | 10 | 1.4 | 5.8 |
| 13638 | 4 | 4 | 0.8 | 3.9 |
| 13639 | 11 | 8 | 2.7 | 14.7 |
| 13640 | 11 | 12 | 3.0 | 15.6 |
| 13641 | 15 | 32 | 4.1 | 21.4 |
| 13642 | 7 | 42 | 3.3 | 20.8 |
| 149391 | 7 | 36 | 2.2 | 16.7 |
| Std Nominal | 3 | 516 | 0.2 | 0.2 |
| Determined | 4 | 524 | 0.2 | 0.2 |
| 149392 | 7 | 46 | 2.4 | 15.2 |
| 13651 | 11 | 52 | 2.7 | 16.1 |
| 13652 | 8 | 48 | 3.2 | 16.9 |
| 13653 | 9 | 38 | 3.1 | 14.9 |
| 13654 | 9 | 42 | 3.5 | 15.6 |
| 149393 | 8 | 30 | 8.0 | 13.5 |
| 149394 | 3 | 26 | 6.3 | 9.7 |
| 13664 | 5 | 48 | 4.9 | 10.7 |
| 13665 | 4 | 38 | 3.7 | 10.3 |
| 13666 | 4 | 48 | 4.7 | 11.3 |
| Std Nominal | 5 | 76 | 0.3 | 1.1 |
| Determined | 5 | 76 | 0.3 | 1.2 |
| 13667 | 7 | 28 | 4.3 | 10.8 |
| 13668 | 7 | 46 | 3.6 | 11.1 |
| 13668 Rpt | 7 | 44 | 3.7 | 11.1 |
| 13669 | 9 | 58 | 3.2 | 11.2 |
| 13670 | 3 | 72 | 3.2 | 11.4 |
| 13671 | 3 | 60 | 2.7 | 10.1 |
| 13672 | 11 | 42 | 2.8 | 10.4 |
| 13673 | 9 | 84 | 3.2 | 11.3 |
| 13674 | 6 | 92 | 2.9 | 11.8 |
| 13675 | 3 | 94 | 2.9 | 11.6 |
| 149395 | 4 | 64 | 2.9 | 11.4 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 38 of 49

| | Pb ppm | Zn ppm | U ppm | Th ppm |
|-----------------|-----------|-----------|----------|-----------|
| Detection Limit | 1 | 2 | 0.1 | 0.1 |
| 149396 | 7 | 48 | 3.0 | 11.8 |
| 149397 | 8 | 36 | 3.6 | 12.4 |
| 149398 | 15 | 52 | 4.6 | 12.9 |
| 149398 Rpt | 14 | 54 | 4.6 | 12.9 |
| 13693 | 14 | 30 | 5.5 | 11.7 |
| 13694 | 8 | 28 | 2.8 | 10.0 |
| 13695 | 14 | 32 | 4.5 | 14.1 |
| 13696 | 9 | 30 | 2.6 | 7.9 |
| 13697 | 8 | 28 | 2.6 | 7.9 |
| 13698 | 10 | 34 | 4.5 | 12.9 |
| 13699 | 8 | 40 | 5.3 | 17.0 |
| 13700 | 7 | 94 | 0.9 | 2.6 |
| 13700 Rpt | 7 | 94 | 0.9 | 2.5 |
| 13701 | 8 | 28 | 3.7 | 14.2 |
| Std Nominal | 3 | 68 | 0.3 | 0.5 |
| Determined | 3 | 66 | 0.4 | 0.5 |
| 13702 | 10 | 28 | 5.0 | 11.0 |
| 13702 Rpt | 10 | 30 | 5.0 | 10.7 |
| 13703 | 6 | 38 | 3.9 | 14.6 |
| 13704 | 7 | 18 | 6.3 | 9.2 |
| 13705 | 11 | 38 | 4.8 | 10.6 |
| 13706 | 19 | 52 | 6.0 | 11.2 |
| 13707 | 8 | 42 | 6.3 | 10.2 |
| 13708 | 9 | 46 | 5.9 | 10.4 |
| 13709 | 6 | 104 | 4.4 | 11.4 |
| 13710 | 6 | 108 | 3.2 | 10.8 |
| 13711 | 4 | 78 | 2.6 | 9.5 |
| 13712 | 3 | 86 | 2.9 | 10.3 |
| 13713 | 5 | 94 | 4.1 | 11.2 |
| 13714 | 6 | 82 | 3.7 | 10.8 |
| 13715 | 7 | 114 | 3.8 | 12.2 |
| 13716 | 2 | 144 | 3.5 | 12.2 |
| 13717 | 6 | 146 | 3.6 | 11.9 |
| 13718 | 3 | 132 | 2.7 | 11.0 |
| 13719 | 3 | 144 | 3.0 | 11.6 |
| 13720 | 432 | 40 | 1.5 | 3.0 |
| 13720 Rpt | 438 | 40 | 1.5 | 2.9 |
| 13721 | 5 | 144 | 3.2 | 12.0 |
| 13722 | 3 | 140 | 3.3 | 12.7 |
| 13723 | 6 | 100 | 3.3 | 12.1 |
| 13724 | 10 | 92 | 4.1 | 12.9 |
| 13725 | 10 | 58 | 5.6 | 10.0 |
| 13726 | 5 | 36 | 2.5 | 7.3 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 39 of 49

| | Pb ppm | Zn ppm | U ppm | Th ppm |
|-----------------|-----------|-----------|----------|-----------|
| Detection Limit | 1 | 2 | 0.1 | 0.1 |
| 13728 | 44 | 14 | 8.4 | 11.5 |
| 13729 | 22 | 16 | 8.1 | 11.3 |
| 13730 | 16 | 68 | 7.4 | 11.6 |
| 13731 | 7 | 54 | 5.3 | 10.8 |
| 13732 | 9 | 50 | 4.2 | 10.3 |
| 13732 Rpt | 9 | 48 | 4.3 | 11.0 |
| 13733 | 11 | 72 | 3.7 | 9.9 |
| 13734 | 9 | 60 | 4.2 | 10.4 |
| 13735 | 10 | 44 | 5.4 | 10.6 |
| 13736 | 17 | 72 | 8.5 | 12.0 |
| 13737 | 22 | 52 | 7.4 | 19.4 |
| Std Nominal | 3 | 104 | 0.7 | 2.8 |
| Determined | 3 | 106 | 0.6 | 2.7 |
| 13738 | 5 | 12 | 1.0 | 3.7 |
| 13739 | 5 | 22 | 1.7 | 7.4 |
| 13740 | 5 | 26 | 1.8 | 7.1 |
| 13741 | 7 | 30 | 1.8 | 9.3 |
| 13742 | 7 | 30 | 2.3 | 12.7 |
| 13743 | 24 | 64 | 3.9 | 19.4 |
| 13744 | 19 | 36 | 2.1 | 11.4 |
| 13745 | 18 | 10 | 0.9 | 4.0 |
| 13746 | 9 | 62 | 2.1 | 12.9 |
| 13747 | 7 | 30 | 1.2 | 6.7 |
| 13748 | 7 | 26 | 1.9 | 9.2 |
| 13749 | 9 | 38 | 3.0 | 16.6 |
| 13750 | 8 | 46 | 2.3 | 16.2 |
| 13751 | 7 | 36 | 2.0 | 15.2 |
| 13751 Rpt | 7 | 36 | 2.0 | 15.1 |
| 13752 | 8 | 36 | 2.3 | 17.1 |
| 13753 | 9 | 38 | 2.5 | 17.5 |
| 13754 | 8 | 34 | 2.1 | 15.1 |
| 13755 | 8 | 36 | 2.1 | 15.5 |
| 13756 | 8 | 34 | 2.4 | 15.2 |
| 13757 | 8 | 38 | 2.2 | 14.8 |
| 13757 Rpt | 8 | 34 | 2.3 | 14.9 |
| 13758 | 10 | 38 | 2.9 | 18.2 |
| Std Nominal | 36 | 50 | 17.3 | 51.0 |
| Determined | 36 | 52 | 17.0 | 52.0 |
| 13759 | 9 | 38 | 2.9 | 15.6 |
| 13760 | 7 | 98 | 0.9 | 2.9 |
| 13761 | 10 | 40 | 3.2 | 15.5 |
| 13762 | 8 | 40 | 3.5 | 16.0 |
| 13763 | 9 | 44 | 3.8 | 15.2 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 40 of 49

| | Pb ppm | Zn ppm | U ppm | Th ppm |
|-----------------|-----------|-----------|----------|-----------|
| Detection Limit | 1 | 2 | 0.1 | 0.1 |
| 13764 | 8 | 32 | 3.8 | 14.9 |
| 13764 Rpt | 7 | 34 | 3.8 | 14.8 |
| 13765 | 10 | 38 | 4.6 | 17.4 |
| 13765 Rpt | 10 | 38 | 4.5 | 16.7 |
| 13766 | 5 | 30 | 4.2 | 11.3 |
| 13767 | 6 | 32 | 6.0 | 6.5 |
| 13768 | 5 | 22 | 16.5 | 12.2 |
| 13769 | 3 | 28 | 7.5 | 10.7 |
| Std Nominal | 521 | 5200 | 0.8 | 2.7 |
| Determined | 514 | 5180 | 0.8 | 2.8 |
| 13770 | 5 | 36 | 7.9 | 10.4 |
| 149399 | 5 | 44 | 8.0 | 10.7 |
| 149400 | 5 | 46 | 8.0 | 10.4 |
| 149401 | 27 | 86 | 4.5 | 9.6 |
| 149402 | 7 | 44 | 2.6 | 10.7 |
| 149403 | 9 | 60 | 2.9 | 10.6 |
| 149404 | 28 | 54 | 4.6 | 11.3 |
| 149405 | 27 | 100 | 5.3 | 11.8 |
| 13796 | 22 | 74 | 5.7 | 12.7 |
| 13797 | 15 | 64 | 5.3 | 12.2 |
| 13798 | 62 | 94 | 5.4 | 12.7 |
| 13799 | 40 | 148 | 6.9 | 13.1 |
| 13800 | 447 | 44 | 1.6 | 3.2 |
| 13801 | 49 | 142 | 4.5 | 12.7 |
| 13802 | 37 | 110 | 4.1 | 13.0 |
| 13803 | 23 | 86 | 3.6 | 11.8 |
| 13804 | 20 | 66 | 7.6 | 19.0 |
| 13805 | 15 | 68 | 7.5 | 24.8 |
| 13806 | 22 | 40 | 2.4 | 8.0 |
| 13807 | 38 | 78 | 3.0 | 11.0 |
| 13808 | 49 | 170 | 5.1 | 21.1 |
| Std Nominal | 5 | 10 | <0.1 | 0.1 |
| Determined | 6 | 8 | <0.1 | 0.1 |
| 13809 | 7 | 64 | 4.8 | 16.7 |
| 13810 | 41 | 88 | 11.3 | 20.6 |
| 13810 Rpt | 40 | 92 | 11.8 | 22.3 |
| 149406 | 7 | 64 | 7.9 | 12.9 |
| 149407 | 15 | 36 | 6.5 | 14.1 |
| 149408 | 34 | 56 | 4.9 | 12.9 |
| 149409 | 8 | 56 | 5.4 | 12.8 |
| 13828 | 3 | 62 | 5.1 | 12.2 |
| 13829 | 5 | 26 | 6.3 | 9.6 |
| 13830 | 17 | 22 | 2.7 | 7.2 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 41 of 49

| | Pb ppm | Zn ppm | U ppm | Th ppm |
|-----------------|-----------|-----------|----------|-----------|
| Detection Limit | 1 | 2 | 0.1 | 0.1 |
| 13831 | 6 | 16 | 1.5 | 4.4 |
| 13834 | 43 | 148 | 30.5 | 14.3 |
| 13835 | 115 | 112 | 13.6 | 10.9 |
| 13836 | 42 | 140 | 11.5 | 10.4 |
| 13837 | 18 | 232 | 9.6 | 9.6 |
| 13838 | 71 | 152 | 11.5 | 11.0 |
| 13838 Rpt | 69 | 156 | 11.4 | 10.9 |
| 13839 | 47 | 94 | 11.5 | 12.4 |
| 13840 | 48 | 94 | 11.7 | 12.3 |
| 13841 | 38 | 94 | 9.0 | 12.2 |
| 13842 | 22 | 114 | 6.5 | 10.1 |
| 13843 | 19 | 120 | 5.9 | 10.1 |
| Std Nominal | 2 | 90 | 0.1 | 0.5 |
| Determined | 2 | 92 | 0.1 | 0.5 |
| 13844 | 17 | 106 | 5.5 | 10.8 |
| 13845 | 25 | 120 | 4.9 | 10.2 |
| 13845 Rpt | 25 | 124 | 4.9 | 10.4 |
| 13846 | 14 | 118 | 5.3 | 10.8 |
| 13847 | 17 | 98 | 6.0 | 11.2 |
| 13848 | 19 | 80 | 6.3 | 10.6 |
| 13849 | 37 | 110 | 13.8 | 17.9 |
| 13850 | 10 | 36 | 4.6 | 11.7 |
| 13851 | 21 | 104 | 6.5 | 30.9 |
| 13852 | 20 | 84 | 4.7 | 22.7 |
| 13853 | 21 | 58 | 4.3 | 22.0 |
| 13854 | 23 | 46 | 2.5 | 11.3 |
| 13855 | 77 | 62 | 2.3 | 11.7 |
| 13856 | 15 | 30 | 1.8 | 9.4 |
| 13857 | 27 | 90 | 4.8 | 24.2 |
| 13858 | 15 | 90 | 3.1 | 17.2 |
| 13859 | 11 | 82 | 2.6 | 18.7 |
| 13859 Rpt | 10 | 84 | 2.7 | 18.3 |
| 13860 | 7 | 96 | 0.9 | 2.9 |
| 13861 | 9 | 124 | 2.5 | 17.8 |
| 13862 | 44 | 62 | 3.2 | 21.9 |
| 13862 Rpt | 42 | 64 | 3.4 | 23.1 |
| 13863 | 27 | 70 | 3.1 | 22.1 |
| 13864 | 57 | 226 | 3.1 | 22.2 |
| 13865 | 55 | 98 | 3.0 | 21.8 |
| 13866 | 33 | 122 | 2.8 | 19.9 |
| 13867 | 76 | 156 | 3.5 | 20.7 |
| 13868 | 10 | 52 | 3.6 | 20.3 |
| 13869 | 10 | 58 | 4.7 | 23.6 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 42 of 49

| | Pb ppm | Zn ppm | U ppm | Th ppm |
|-----------------|-----------|-----------|----------|-----------|
| Detection Limit | 1 | 2 | 0.1 | 0.1 |
| 13870 | 10 | 138 | 5.2 | 23.5 |
| 13871 | 32 | 76 | 5.4 | 24.3 |
| 13872 | 26 | 50 | 6.5 | 20.0 |
| 13873 | 8 | 22 | 13.0 | 11.7 |
| 149410 | 9 | 28 | 17.2 | 13.2 |
| Std Nominal | 3 | 64 | 0.1 | 0.4 |
| Determined | 3 | 62 | 0.1 | 0.5 |
| 149411 | 6 | 28 | 9.9 | 12.5 |
| 13883 | 3 | 32 | 5.4 | 11.5 |
| 13883 Rpt | 3 | 32 | 5.6 | 12.2 |
| 13884 | 3 | 40 | 5.6 | 11.7 |
| 13885 | 3 | 20 | 4.1 | 12.2 |
| 13886 | 3 | 22 | 5.4 | 13.0 |
| 13887 | 4 | 20 | 6.0 | 12.1 |
| 13888 | 3 | 20 | 2.5 | 8.7 |
| 149412 | 6 | 30 | 2.5 | 14.3 |
| 13893 | 8 | 40 | 2.7 | 16.8 |
| 13894 | 8 | 32 | 2.6 | 16.5 |
| Std Nominal | 3 | 516 | 0.2 | 0.2 |
| Determined | 3 | 514 | 0.2 | 0.2 |
| 13895 | 7 | 34 | 2.4 | 15.9 |
| 13896 | 8 | 26 | 2.5 | 15.8 |
| 13897 | 7 | 32 | 2.6 | 16.5 |
| 13898 | 8 | 22 | 2.9 | 15.6 |
| 13899 | 7 | 28 | 3.1 | 15.9 |
| 13899 Rpt | 7 | 28 | 3.1 | 16.1 |
| 13900 | 438 | 40 | 1.5 | 3.2 |
| 13901 | 9 | 26 | 3.1 | 15.2 |
| 13902 | 7 | 30 | 3.4 | 15.4 |
| 13903 | 7 | 30 | 3.6 | 16.0 |
| 13904 | 6 | 26 | 3.8 | 14.4 |
| 13905 | 7 | 10 | 5.0 | 8.2 |
| 13906 | 5 | 10 | 3.9 | 8.1 |
| 13906 Rpt | 5 | 8 | 3.8 | 7.7 |
| 13907 | 5 | 26 | 5.3 | 13.1 |
| 13908 | 5 | 30 | 3.4 | 15.5 |
| 13909 | 7 | 34 | 3.0 | 13.7 |
| 13910 | 8 | 28 | 3.4 | 14.5 |
| 13911 | 8 | 8 | 2.4 | 4.2 |
| 13912 | 9 | 12 | 5.5 | 5.6 |
| 13913 | 5 | 14 | 6.4 | 8.9 |
| 149413 | 4 | 30 | 5.0 | 9.3 |
| 149414 | 5 | 52 | 5.4 | 10.9 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 43 of 49

| | Pb ppm | Zn ppm | U ppm | Th ppm |
|-----------------|-----------|-----------|----------|-----------|
| Detection Limit | 1 | 2 | 0.1 | 0.1 |
| 149415 | 4 | 46 | 3.7 | 10.1 |
| 149415 Rpt | 4 | 48 | 3.5 | 9.5 |
| 149416 | 3 | 68 | 2.4 | 8.9 |
| 149417 | 3 | 86 | 2.8 | 10.9 |
| 149418 | 5 | 102 | 3.0 | 11.2 |
| 13938 | 24 | 14 | 9.2 | 12.2 |
| 13939 | 26 | 18 | 10.0 | 13.0 |
| 13940 | 25 | 20 | 10.8 | 13.1 |
| 13941 | 34 | 66 | 18.1 | 29.9 |
| 13942 | 46 | 88 | 30.0 | 30.5 |
| 13943 | 28 | 36 | 30.2 | 29.4 |
| 13944 | 33 | 134 | 26.3 | 28.5 |
| 13945 | 20 | 102 | 12.4 | 26.8 |
| 13945 Rpt | 20 | 100 | 12.6 | 28.4 |
| 13946 | 17 | 56 | 7.1 | 26.9 |
| 13947 | 16 | 40 | 7.4 | 28.2 |
| 13948 | 24 | 48 | 9.1 | 31.1 |
| 13949 | 22 | 72 | 8.6 | 32.7 |
| Std Nominal | 5 | 76 | 0.3 | 1.1 |
| Determined | 5 | 76 | 0.3 | 1.2 |
| 13950 | 24 | 56 | 12.2 | 36.2 |
| 13951 | 19 | 50 | 7.8 | 31.8 |
| 13952 | 21 | 52 | 6.0 | 27.2 |
| 13953 | 20 | 52 | 6.0 | 26.5 |
| 13954 | 21 | 62 | 7.1 | 26.7 |
| 13955 | 14 | 80 | 5.7 | 27.7 |
| 13956 | 19 | 80 | 6.3 | 26.8 |
| 13957 | 17 | 76 | 8.0 | 31.2 |
| 13958 | 15 | 60 | 7.3 | 29.0 |
| 13959 | 17 | 50 | 8.5 | 29.2 |
| 13959 Rpt | 17 | 52 | 8.0 | 29.5 |
| 13960 | 7 | 96 | 1.0 | 2.9 |
| 13961 | 16 | 56 | 5.5 | 28.1 |
| 13962 | 16 | 58 | 5.2 | 27.3 |
| 13963 | 18 | 60 | 6.4 | 28.1 |
| 13964 | 19 | 54 | 11.0 | 31.5 |
| Std Nominal | 3 | 68 | 0.3 | 0.5 |
| Determined | 2 | 66 | 0.3 | 0.5 |
| 13965 | 15 | 44 | 7.5 | 29.5 |
| 13966 | 18 | 58 | 8.7 | 31.7 |
| 13967 | 19 | 56 | 7.6 | 29.6 |
| 13968 | 36 | 58 | 7.2 | 28.6 |
| 13969 | 12 | 54 | 7.1 | 31.0 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 44 of 49

| | Pb ppm | Zn ppm | U ppm | Th ppm |
|-----------------|-----------|-----------|----------|-----------|
| Detection Limit | 1 | 2 | 0.1 | 0.1 |
| 13970 | 18 | 52 | 7.0 | 31.2 |
| 13971 | 12 | 46 | 7.7 | 34.0 |
| 13972 | 14 | 100 | 9.1 | 32.5 |
| 13973 | 12 | 144 | 10.1 | 36.8 |
| 13974 | 19 | 242 | 12.2 | 44.2 |
| 13974 Rpt | 20 | 242 | 12.6 | 46.2 |
| 13975 | 20 | 82 | 10.7 | 40.7 |
| 13976 | 61 | 54 | 11.5 | 44.2 |
| 13977 | 54 | 98 | 13.4 | 42.1 |
| 13978 | 73 | 90 | 9.5 | 44.9 |
| Std Nominal | 3 | 104 | 0.7 | 2.8 |
| Determined | 4 | 108 | 0.6 | 2.9 |
| 13979 | 25 | 68 | 7.7 | 44.0 |
| 13980 | 448 | 40 | 1.5 | 3.1 |
| 13980 Rpt | 440 | 38 | 1.5 | 3.0 |
| 13981 | 29 | 68 | 8.2 | 38.3 |
| 13982 | 23 | 138 | 5.8 | 27.0 |
| 13983 | 6 | 46 | 2.9 | 18.1 |
| 13984 | 6 | 60 | 4.1 | 25.7 |
| 13985 | 7 | 58 | 4.6 | 27.1 |
| 13986 | 5 | 34 | 3.0 | 17.8 |
| 13987 | 6 | 34 | 3.0 | 18.4 |
| 13988 | 6 | 38 | 3.4 | 22.3 |
| 13989 | 7 | 36 | 3.3 | 20.5 |
| 13990 | 5 | 40 | 2.8 | 19.0 |
| 13990 Rpt | 5 | 38 | 2.8 | 18.7 |
| 13991 | 6 | 34 | 3.0 | 21.2 |
| 13992 | 6 | 32 | 2.4 | 17.7 |
| 13993 | 6 | 36 | 2.4 | 20.0 |
| 13994 | 5 | 38 | 3.8 | 20.0 |
| 13995 | 8 | 32 | 2.2 | 15.4 |
| 13996 | 7 | 30 | 2.2 | 15.9 |
| 13997 | 6 | 28 | 2.3 | 16.3 |
| 149419 | 5 | 30 | 2.5 | 16.2 |
| 149420 | 7 | 98 | 0.9 | 2.7 |
| 149421 | 6 | 22 | 3.0 | 14.4 |
| Std Nominal | 36 | 50 | 17.3 | 51.0 |
| Determined | 36 | 50 | 17.6 | 49.4 |
| 149422 | 5 | 20 | 3.2 | 10.9 |
| 14011 | 4 | 18 | 2.3 | 9.8 |
| 14012 | 6 | 22 | 3.0 | 13.2 |
| 14013 | 7 | 30 | 3.0 | 17.1 |
| 14014 | 5 | 26 | 4.0 | 17.8 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 45 of 49

| | Pb ppm | Zn ppm | U ppm | Th ppm |
|-----------------|-----------|-----------|----------|-----------|
| Detection Limit | 1 | 2 | 0.1 | 0.1 |
| 14014 Rpt | 5 | 28 | 3.9 | 16.5 |
| 14015 | 7 | 28 | 3.6 | 16.2 |
| 14016 | 8 | 30 | 3.4 | 16.5 |
| 14016 Rpt | 8 | 28 | 3.4 | 16.4 |
| 14017 | 8 | 28 | 3.7 | 15.8 |
| 14018 | 6 | 18 | 3.6 | 11.9 |
| 14019 | 5 | 16 | 2.2 | 2.9 |
| 14020 | 6 | 16 | 2.5 | 3.4 |
| 14021 | 7 | 8 | 2.5 | 3.3 |
| 149423 | 9 | 32 | 4.8 | 7.8 |
| 149424 | 5 | 26 | 4.2 | 8.6 |
| 149425 | 6 | 34 | 4.6 | 10.0 |
| 149426 | 5 | 28 | 2.2 | 8.8 |
| 149427 | 5 | 36 | 2.3 | 9.6 |
| 14044 | 28 | 12 | 9.8 | 12.5 |
| 14045 | 24 | 16 | 11.8 | 11.9 |
| 14046 | 25 | 144 | 10.0 | 18.2 |
| 14047 | 21 | 516 | 7.0 | 24.0 |
| 14048 | 19 | 384 | 8.8 | 30.9 |
| 14049 | 15 | 388 | 9.1 | 29.1 |
| 14049 Rpt | 15 | 378 | 8.8 | 29.5 |
| 14050 | 19 | 98 | 9.4 | 26.5 |
| 14051 | 26 | 124 | 18.4 | 25.3 |
| 14052 | 31 | 50 | 47.5 | 22.9 |
| 14053 | 18 | 42 | 29.3 | 15.1 |
| Std Nominal | 521 | 5200 | 0.8 | 2.7 |
| Determined | 513 | 5110 | 0.9 | 2.8 |
| 14054 | 30 | 56 | 24.2 | 13.5 |
| 14055 | 28 | 64 | 25.8 | 15.7 |
| 14056 | 15 | 38 | 8.3 | 13.1 |
| 14057 | 8 | 18 | 7.4 | 11.2 |
| 14058 | 9 | 32 | 6.6 | 11.0 |
| 14059 | 25 | 56 | 8.7 | 12.8 |
| 14061 | 21 | 108 | 9.7 | 16.2 |
| 14062 | 21 | 52 | 11.3 | 22.1 |
| 14062 Rpt | 23 | 54 | 12.1 | 22.6 |
| 14063 | 23 | 104 | 9.0 | 26.6 |
| 14064 | 40 | 50 | 8.6 | 18.6 |
| 14065 | 100 | 58 | 12.5 | 35.1 |
| 14066 | 162 | 72 | 10.2 | 24.8 |
| 14067 | 99 | 48 | 8.8 | 29.4 |
| 14068 | 71 | 72 | 7.8 | 27.7 |
| 14069 | 61 | 64 | 5.9 | 25.7 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 46 of 49

| | Pb ppm | Zn ppm | U ppm | Th ppm |
|-----------------|-----------|-----------|----------|-----------|
| Detection Limit | 1 | 2 | 0.1 | 0.1 |
| 14070 | 34 | 90 | 7.3 | 33.1 |
| 14071 | 33 | 58 | 8.4 | 41.2 |
| 14072 | 80 | 40 | 11.7 | 37.8 |
| 14073 | 77 | 52 | 10.6 | 37.2 |
| 14074 | 37 | 84 | 11.2 | 43.5 |
| 14074 Rpt | 36 | 86 | 11.7 | 43.3 |
| 14075 | 43 | 76 | 8.9 | 44.6 |
| 14076 | 30 | 72 | 7.7 | 33.2 |
| 14077 | 14 | 92 | 8.3 | 39.3 |
| 14078 | 52 | 342 | 10.0 | 36.0 |
| 14079 | 19 | 638 | 9.9 | 38.3 |
| 14080 | 7 | 94 | 1.0 | 2.8 |
| 14084 | 10 | 816 | 5.8 | 30.8 |
| 14086 | 16 | 1540 | 13.9 | 24.7 |
| 149428 | 6 | 110 | 3.8 | 21.2 |
| 149428 Rpt | 6 | 102 | 3.8 | 21.5 |
| 149429 | 6 | 68 | 3.5 | 19.4 |
| 149430 | 5 | 58 | 2.7 | 18.5 |
| 149431 | 6 | 34 | 7.5 | 19.8 |
| 149432 | 5 | 34 | 4.1 | 15.9 |
| 149433 | 4 | 30 | 3.5 | 12.5 |
| 149434 | 4 | 30 | 3.6 | 14.7 |
| Std Nominal | 5 | 10 | <0.1 | 0.1 |
| Determined | 5 | 8 | <0.1 | 0.1 |
| 149435 | 5 | 34 | 3.1 | 16.3 |
| 149436 | 10 | 52 | 6.5 | 20.0 |
| 149437 | 15 | 38 | 9.1 | 13.8 |
| 149438 | 9 | 46 | 9.2 | 13.2 |
| 149439 | 5 | 60 | 4.7 | 11.6 |
| 149440 | 5 | 38 | 4.9 | 11.6 |
| Std Nominal | 2 | 90 | 0.1 | 0.5 |
| Determined | 2 | 92 | 0.1 | 0.5 |
| 149441 | 6 | 34 | 3.1 | 13.0 |
| 149442 | 6 | 54 | 6.0 | 10.7 |
| 149443 | 7 | 38 | 5.6 | 10.0 |
| 14148 | 18 | 76 | 3.4 | 11.2 |
| 14149 | 9 | 48 | 3.4 | 11.1 |
| 14150 | 8 | 50 | 3.3 | 10.9 |
| 14150 Rpt | 8 | 48 | 3.4 | 10.8 |
| 14151 | 8 | 56 | 2.9 | 11.1 |
| 14152 | 15 | 74 | 5.3 | 11.0 |
| 14153 | 8 | 130 | 7.6 | 10.5 |
| 14154 | 27 | 96 | 7.6 | 12.6 |



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 Order Number: NC_003 Page 47 of 49

| | Pb ppm | Zn ppm | U ppm | Th ppm |
|-----------------|-----------|-----------|----------|-----------|
| Detection Limit | 1 | 2 | 0.1 | 0.1 |
| 14155 | 46 | 104 | 16.4 | 24.2 |
| 14156 | 28 | 58 | 6.9 | 21.4 |
| 14156 Rpt | 27 | 60 | 6.8 | 21.4 |
| 14157 | 44 | 34 | 2.3 | 8.1 |
| 14158 | 23 | 36 | 3.2 | 15.2 |
| 14159 | 17 | 56 | 4.1 | 21.0 |
| 14160 | 16 | 56 | 3.9 | 21.4 |
| 14161 | 18 | 56 | 3.9 | 22.0 |
| 13516 | 50 | 16 | 7.4 | 16.2 |
| 13517 | 45 | 18 | 7.2 | 14.3 |
| 13518 | 8 | 22 | 4.9 | 11.5 |
| 13518 Rpt | 8 | 26 | 4.8 | 11.4 |
| 13519 | 5 | 38 | 3.6 | 10.5 |
| 13520 | 430 | 46 | 1.5 | 3.2 |
| 13521 | 7 | 40 | 2.7 | 10.4 |
| 13522 | 6 | 12 | 2.5 | 11.9 |
| 13523 | 8 | 16 | 3.9 | 11.7 |
| 13524 | 7 | 12 | 4.8 | 12.0 |
| 13525 | 9 | 22 | 6.8 | 18.0 |
| 13526 | 5 | 8 | 1.8 | 5.7 |
| 13527 | 4 | 6 | 1.4 | 5.1 |
| 13527 Rpt | 4 | 8 | 1.4 | 5.0 |
| 13528 | 6 | 12 | 2.4 | 12.5 |
| 13529 | 6 | 14 | 2.1 | 10.3 |
| 13530 | 11 | 32 | 4.9 | 26.0 |
| 13531 | 8 | 16 | 2.6 | 14.2 |
| 13532 | 11 | 10 | 2.9 | 18.0 |
| 13533 | 7 | 10 | 2.1 | 12.4 |
| 13534 | 10 | 16 | 3.0 | 16.9 |
| Std Nominal | 3 | 64 | 0.1 | 0.4 |
| Determined | 2 | 62 | 0.1 | 0.7 |
| 13535 | 7 | 40 | 3.2 | 20.1 |
| 13536 | 7 | 36 | 2.5 | 16.5 |
| 13588 | 503 | 1930 | 3.6 | 10.1 |
| 13588 Rpt | 547 | 1970 | 3.6 | 10.4 |
| 13589 | 19 | 60 | 4.8 | 13.6 |
| 13590 | 27 | 86 | 7.2 | 13.8 |
| 13591 | 10 | 28 | 3.9 | 11.3 |
| 13592 | 17 | 46 | 7.5 | 18.8 |
| 13593 | 5 | 26 | 4.8 | 10.0 |
| 13593 Rpt | 5 | 28 | 4.4 | 9.8 |
| 13594 | 6 | 18 | 2.8 | 8.7 |
| 13595 | 17 | 40 | 8.1 | 23.8 |



Reference: u282154 Order Number: NC_003 Page 48 of 49

| | Pb ppm | Zn ppm | U ppm | Th ppm |
|-----------------|-----------|-----------|----------|-----------|
| Detection Limit | 1 | 2 | 0.1 | 0.1 |
| 13596 | 7 | 52 | 4.8 | 21.0 |
| 13597 | 14 | 30 | 12.3 | 22.1 |
| Std Nominal | 3 | 516 | 0.2 | 0.2 |
| Determined | 7 | 524 | 0.2 | 0.3 |
| 13598 | 5 | 44 | 5.4 | 11.1 |
| 13599 | 4 | 38 | 4.5 | 10.9 |
| 13600 | 8 | 96 | 1.0 | 2.8 |
| 14060 | 441 | 40 | 1.6 | 3.1 |
| 14060 Rpt | 435 | 42 | 1.5 | 3.1 |
| Std Nominal | 5 | 76 | 0.3 | 1.1 |
| Determined | 5 | 80 | 0.3 | 1.1 |

These results pertain to the samples as received at this laboratory.
Where standards are reported, the nominal value for the element is reported above the result found.

"IS" Implies insufficient sample for this determination

"NR" Implies result is not required for this determination

"M" Implies this result reported in ppm

"%" Implies this result reported in %

Sample Storage

The excess material (Residue) will be held after 30 days

The pulp samples (Pulp) will be held after 60 days as per instructions.

Sample Preparation

The samples have been sorted and dried. Primary preparation has been by crushing the whole sample. The samples have been split with a riffle splitter to obtain a sub-fraction which has then been pulverised in a vibrating pulveriser.

Digest and Analysis:

The sample(s) have been digested and refluxed with a mixture of Acids including Hydrofluoric, Nitric, Hydrochloric and Perchloric Acids. This extended digest approaches a Total digest for many elements however some refractory minerals are not completely attacked.

Ca,Co,Cr,Cu,Fe,K,Mg,Mn,Na,Ni,P,S,V,Zn

have been determined by Inductively Coupled Plasma (ICP) Optical Emission Spectrometry.

Ag,As,Ba,Bi,Cd,Li,Mo,Pb,Th,U

have been determined by Inductively Coupled Plasma (ICP) Mass Spectrometry.

The samples have been analysed by Firing a 40 gm (approx) portion of the sample. Lower sample weights may be employed for samples with very high sulphide and metal contents. This is the classical fire assay process and will give total separation of Gold, Platinum and Palladium in the sample.

Au1,Au2,Pd,Pt

have been determined by Inductively Coupled Plasma (ICP) Optical Emission Spectrometry.



Bureau Veritas Minerals Pty Ltd



MINERAL TESTING & LABORATORY SERVICES

ABN: 30 008 127 802

58 Sorbonne Crescent Canning Vale
Perth WA 6155 Australia

Telephone (08) 9456 0404
Facsimile (08) 9456 0403

Reference: u282154 **Order Number:** NC_003 Page 49 of 49