



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 (7) 3243 7222 Fax: +61 (7) 3243 7218

www.alsglobal.com

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation
No: 825, Corporate Site No: 23001.

CERTIFICATE AD1713856

Project: AMI-Winnecke Gold

This report is for 36 Rock samples submitted to our lab in Adelaide, SA, Australia on
10- SEP- 2017

The following have access to data associated with this certificate:

ZHONG LI GANG

HAISHUN (DAVID) SUN

To: AMI RESOURCES PTY LTD
ATTN: HAISHUN (DAVID) SUN
30 EILDON ROAD
ASHWOOD VIC 3147

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

***** See Appendix Page for comments regarding this certificate *****

Page: 1
Total # Pages: 2 (A)
Plus Appendix Pages
Finalized Date: 24-SEP-2017
Account: AMIRES

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI- 21	Received Sample Weight
LEV- 01	Waste Disposal Levy
LOG- 22	Sample login - Rcd w/o BarCode
CRU- 21	Crush entire sample > 70% - 6 mm
PUL- 23	Pulv Sample - Split/Retain
PUL- QC	Pulverizing QC Test

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
ME- ICP61	33 element four acid ICP- AES	ICP- AES
Ag- OG62	Ore Grade Ag - Four Acid	ICP- AES
ME- OG62	Ore Grade Elements - Four Acid	ICP- AES
Pb- OG62	Ore Grade Pb - Four Acid	ICP- AES
Pb- OG62h	High Grade Pb - - 4Acid	ICP- AES
ME- OG62h	Extended Ore Grade 4- Acid	ICP- AES
Au- AA26	Ore Grade Au 50g FA AA finish	AAS

Signature:

Cameron Brosnan, Laboratory Manager, Perth



Australian Laboratory Services Pty. Ltd.

32 Shand Street

Stafford

Brisbane QLD 4053

Phone: +61 (7) 3243 7222 Fax: +61 (7) 3243 7218

www.alsglobal.com

ALS Perth is a NATA Accredited Testing Laboratory. Corporate Accreditation
No: 825, Corporate Site No: 23001.

Project: AMI-Winnecke Gold

Page: 2
Total # Pages: 2 (A)
Plus Appendix Pages
Finalized Date: 24-SEP-2017
Account: AMIRES

CERTIFICATE OF ANALYSIS AD1713856

Sample Description	WEI-21 Rcvd Wt Kg 0.02	PUL-QC Pass75um % 0.01	Au-AA26 Au Ppm 0.01	Ag OG62 Ag ppm	ME-ICP61 Bi ppm	ME-ICP61 Cu_pref ppm	ME-ICP Cu ppm	ME-ICP61 Cu_rpt %	ME-ICP61 Fe %	ME-ICP61 Mn ppm	ME-ICP61 Pb_pref ppm	ME-ICP61 Pb ppm	ME-ICP61 Pb_rpt %	ME-ICP61 Zn ppm
A1-1	2.54		0.01	3.3	3	49	49		7.08	404	18	18		76
A1-2	2.66		12.68	1.92	22	29	42		3.03	119	16	16		17
A1-3	2.78		0.01	<0.5	<2	7	7		1.46	204	4	4		8
A1-4	2.91		<0.01	<0.5	<2	25	25		2.85	361	15	15		32
A1-5	2.75		<0.01	<0.5	2	37	37		2.66	236	10	10		17
A1-6	2.68		<0.01	<0.5	2	47	47		24.2	1430	36	36		412
A1-7	2.89		<0.01	<0.5	2	95	95		14.1	588	39	39		356
A1-8	3.46		0.29	<0.5	<2	177	177		44	2410	112	112		1428
A1-9	1.92		<0.01	<0.5	<2	88	88		32.6	1280	59	59		601
A3-1	2.31		2.58	12.1	24	44	44		3.67	60	180	180		21
A3-2	1.83		1.01	<0.5	34	38	38		3.97	104	94	94		32
A3-3	1.98		0.25	0.5	4	7	7		0.84	79	16	16		3
A3-4	2.47		2.88	0.9	16	53	53		4	159	162	162		30
A3-5	2.25	85	3.12	<0.5	36	75	75		6.23	104	174	174		45
A3-6	2.18		2.71	1.1	15	69	69		7.05	329	245	245		58
BG1	2.94		0.13	<0.5	7	133	133		3.09	751	21	21		47
BG2	2.85		0.04	<0.5	2	60	60		3.9	417	19	19		47
BG3	2.71		0.09	<0.5	6	65	65		1.68	249	6	6		9
B1	2.34		0.03	<0.5	<2	106	106		8.95	711	7	7		82
B2	2.71		<0.01	<0.5	3	46	46		5.91	1730	6	6		18
B3	1.98		0.32	<0.5	<2	8	8		5.03	3960	6	6		22
E1	1.76		<0.01	<0.5	2	7	7		0.83	181	<2	<2		2
E2	1.89		<0.01	<0.5	<2	9	9		0.81	87	<2	<2		2
E3	2.13		<0.01	<0.5	<2	5	5		0.67	71	2	2		<2
E4	2.45		3.16	<0.5	4	10	10		1.62	40	2	2		5
E5	2.12		0.03	<0.5	<2	3	3		1.7	91	2	2		2
E6	2.38	90	1.57	<0.5	3	12	12		1.04	85	2	2		3
E7	3.14		0.45	<0.5	3	4	4		0.88	68	3	3		4
E8	3.40		0.03	<0.5	2	4	4		0.44	73	<2	<2		<2
E9	2.58		0.02	<0.5	2	4	4		0.8	59	<2	<2		2
E10	2.67		0.01	<0.5	<2	4	4		1.75	529	3	3		12
MB-1	2.29		3.43	17.6	426	36900	>10000	3.69	6.67	112	80	80		22
N1	2.46		6.56	149	123	9352	9352		31	1290	25600	>10000	2.56	943
N2	2.83		12.15	67.2	56	13576	>10000	1.36	24.8	2290	16880	>10000	1.69	2560
N3	1.98		0.63	17.5	27	1829	1829		39.5	1980	4980	4980		420
N4	2.10		2.59	7.2	7	989	989		32.9	3930	2790	2790		1740

CRU- 21	LEV- 01	LOG-22	PUL- 23
PUL- QC	WEI- 21		