

MINERALS TEST REPORT

CLIENT

KINGSTON RESOURCES LIMITED

Level 1
12 - 14 Rowland Street
SUBIACO, W.A. 6008
AUSTRALIA

JOB INFORMATION

JOB CODE	: 1973.0/1807748
NO. SAMPLES	: 7
NO. ELEMENTS	: 16
CLIENT ORDER NO.	: KSN_NT_GL_180531 (Job 1 of 1)
SAMPLE SUBMISSION NO.	: KSN_NT_GL_180531
PROJECT	: BYNOE/ARUNTA
SAMPLE TYPE	: RC Chip
DATE RECEIVED	: 01/06/2018
DATE REPORTED	: 08/06/2018
DATE PRINTED	: 08/06/2018

REPORT NOTES

TESTED BY

Intertek
15 Davison Street, Maddington 6109, Western Australia
PO Box 144, Gosnells 6990, Western Australia
Tel: +61 8 9251 8100
Email: min.aus.per@intertek.com

This report relates specifically to the sample(s) tested that were drawn and/or provided by the client or their nominated third party to Intertek. The reported result(s) provide no warranty or verification on the sample(s) representing any specific goods and/or shipment. This report was prepared solely for the use of the client named in this report. Intertek accepts no responsibility for any loss, damage or liability suffered by a third party as a result of any reliance upon or use of this report. The results provided are not intended for commercial settlement purposes.

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: intertek.com/terms/

JOB NO : 1973.0/1807748
CLIENT REF : KSN_NT_GL_180531



SIGNIFICANT FIGURES

It is common practice to report data derived from analytical instrumentation to a maximum of two or three significant figures. Some data reported herein may show more figures than this. The reporting of more than two or three figures in no way implies that figures beyond the least significant digit have significance.

For more information on the uncertainty on individual reported values, please contact the laboratory.

SAMPLE STORAGE

All solid samples (assay pulps, bulk pulps and residues will be stored for 60 days without charge. Following this samples will be stored at a daily rate until clients written advice regarding return, collection or disposal is received. If storage information is not supplied on the submission, or arranged with the laboratory in writing the default will be to store the samples with the applicable charges. Storage is charged at \$4.00 per m3 per day, expenses related to the return or disposal of samples will be charged at cost. Current disposal cost is charged at \$150.00 per m3.

Samples received as liquids, waters or solutions will be held for 60 days free of charge then disposed of, unless written advice for return or collection is received.

LEGEND	X	= Less than Detection Limit	NA	= Not Analysed
	SNR	= Sample Not Received	UA	= Unable to Assay
	*	= Result Checked	>	= Value beyond Limit of Method
	DTF	= Result still to come	+	= Extra Sample Received Not Listed
	IS	= Insufficient Sample for Analysis		



ELEMENTS	As	Ba	Be	Ca	Cs	K	Li	Nb	Rb	Sc
UNITS	ppm	ppm	ppm	%	ppm	%	ppm	ppm	ppm	ppm
DETECTION LIMIT	20	1	1	0.1	0.1	0.05	1	2	0.5	20
DIGEST	FP1/	FP1/	FP1/	FP1/	FP1/	FP1/	FP1/	FP1/	FP1/	FP1/
ANALYTICAL FINISH	MS	MS	MS	OE	MS	OE	MS	MS	MS	MS
SAMPLE NUMBERS										
0001 KBRC024/121-122M	28	52	137	0.1	69.1	1.17	1.52%	37	488.1	X
0002 KBRC024/122-123M	29	38	147	0.1	103.2	2.01	9216	42	884.6	X
0003 KBRC024/123-124M	X	49	170	0.2	114.6	2.50	8414	66	1113.5	X
0004 KBRC024/124-125M	X	20	178	0.4	74.8	1.38	8612	55	678.9	X
0005 KBRC024/125-126M	X	17	194	0.2	89.1	1.69	8925	42	814.7	X
0006 DELMORE001	X	55	10	0.3	8.4	X	4.38%	5	20.2	X
0007 DELMORE002	X	221	45	1.3	2.7	0.11	4.20%	6	32.3	X
CHECKS										
0001 KBRC024/124-125M	X	25	175	0.4	75.4	1.48	8397	61	671.7	X
STANDARDS										
0001 AMIS0339	X	101	71	0.5	259.1	1.25	2.25%	105	1292.8	25
0002 AMIS0340	332	252	75	2.1	211.2	0.70	1.39%	2413	872.6	25
0003 AMIS0355	X	35	162	0.5	255.3	1.31	7526	49	3645.1	29
BLANKS										
0001 Control Blank	X	X	X	X	0.3	X	X	5	X	X



ELEMENTS	Sn	Sr	Ta	Th	U	W
UNITS	%	ppm	ppm	ppm	ppm	ppm
DETECTION LIMIT	0.01	20	0.1	0.1	0.1	1
DIGEST	FP1/	FP1/	FP1/	FP1/	FP1/	FP1/
ANALYTICAL FINISH	MS	MS	MS	MS	MS	MS
SAMPLE NUMBERS						
0001 KBRC024/121-122M	0.01	26	20.0	1.0	4.9	3
0002 KBRC024/122-123M	0.01	24	26.1	0.9	6.4	4
0003 KBRC024/123-124M	0.02	33	42.5	1.0	9.0	3
0004 KBRC024/124-125M	0.02	95	40.8	0.4	8.8	8
0005 KBRC024/125-126M	X	46	22.6	0.9	10.4	6
0006 DELMORE001	X	247	46.8	X	9.9	X
0007 DELMORE002	X	1427	38.6	X	31.7	40
CHECKS						
0001 KBRC024/124-125M	0.02	95	45.0	0.3	8.2	9
STANDARDS						
0001 AMIS0339	0.02	33	325.1	2.0	5.4	3
0002 AMIS0340	0.13	65	1.30%	55.7	158.3	53
0003 AMIS0355	0.05	30	220.6	4.9	6.1	2
BLANKS						
0001 Control Blank	X	X	X	X	X	X



METHOD CODE DESCRIPTION

Method Code	Analysing Laboratory NATA Laboratory Accreditation	NATA Scope of Accreditation
FP1/MS	Intertek Genalysis Perth 3244 3237 Sodium peroxide fusion (Zirconia crucibles) and Hydrochloric acid to dissolve the melt. Analysed by Inductively Coupled Plasma Mass Spectrometry.	FP1/ : MPL_W011, MS : ICP_W003
FP1/OE	Intertek Genalysis Perth 3244 3237 Sodium peroxide fusion (Zirconia crucibles) and Hydrochloric acid to dissolve the melt. Analysed by Inductively Coupled Plasma Optical (Atomic) Emission Spectrometry.	FP1/ : MPL_W011, OE : ICP_W004